




$$1.) n = \frac{M_{\text{polymère}}}{M_{\text{monomère}}} = \frac{353,0 \text{ Kg/mol}}{66,052 \text{ g/mol} \times 10^{-3} \text{ Kg}} = 5344,274 \text{ Kg/mol}$$

degré de polymérisation n

$$2 \cdot 12,01 + 4 \cdot 1,008 + 2 \cdot 19 = 66,052 \text{ g/mol} \quad \text{monomère}$$

$$2) 0,450 \text{ mol} \times 2 \times 1,008 \text{ g/mol} = 0,9072 \text{ g} \times 5344$$

$$= 4848,077 \text{ g} \cdot 10^{-3} \text{ Kg} \approx 4,85 \text{ Kg}$$

$$3) T_g = -30^\circ\text{C}$$

$$T_f = 160^\circ\text{C}$$

$$T = 25^\circ\text{C}$$

$$T_g < T < T_f \Rightarrow \text{tenace et ...}$$

