

PARTS LIST	BOEING	CORPORATE OFFICES SEATTLE, WA 98124	EXPORT CONTROL COM	CAGE 81205	NUMBER 112U4930-40	REV A	SHEET 1 of 4
LIST TITLE					MODEL	CONTRACT NUMBER	
MACHINED SKIN - LOWER, MID SPAR STA 1558.716 TO WBL 1243.750					DATE 11-19-2009		
THE PARTS LIST IN THIS REPORT SUPERSEDES THE DRAWING SHEET PARTS LIST FOR THIS PART							
OWNER WING, MATT WILSON, 425-266-3786				PIN/ITEM 11-240300			
QPI####, Char. No. ## Attachments							

. . . REVISIONS . . .							
REV	REVISION DESCRIPTION	APPROVED DATE	CHANGE NUMBER	PHASE	CLASS		
A	PANEL 112U4930-40 REPLACES 112U4930-2 SPACER 112U4930-41 REPLACES 112U4930-3 FLAT PATTERN 112U4930-103 REPLACES 112U4930-101 NBMT SIMILAR TO 112U4930-1 REV A REASON: A REVISED RECESS DEPTH OF .175 IS ADDED TO ACCESS DOORS A1, C, D & E. (C1640005452 - NCR 61033EP & 61036EP) DOOR PROFILE REVISED FOR DOORS A& B. (C1660014923 - NCR 88107ET) PROD INFO: AIRPLANE/PARTS MUST COMPLY AIRPLANES/PARTS COMPLETE PER NCR 61033EP, 61036EP & 88107ET. INITIATED AGAINST LINE NO.1420 ARE SATISFACTORY. MFG INFO:4235, PRR95000T, LCCTEP05452 & LCCT ET14923: NOSAR, IN-SEQ KAL PER CIR#WRC-E-4235-34460. INCORP AT LN 1433	11-19-2009	LCCT EP05452 NCR1640061033	PRODUCTION			
NA							

. . . PART SPECIFIC DATA . . .							
NOTE TITLE		NOTE DESCRIPTION					
DATASET FILENAME		112U4930-39 "See Char. No. ##"라고 기입하고, PL처럼 별도 첨부 후 검사/확인					
DRAWING		112U4930 SHEET DL (8페이지 PDSL 내용 참고)					
FINISH - SEQUENCE 1		F-17.37 BORIC ACID-SULFURIC ACID ANODIZE IN ACCORDANCE WITH BAC 5632, CLASS 5 OR CHROMIC ACID ANODIZE AT 22 VOLTS IN ACCORDANCE WITH BAC 5019, CLASS 5.					
FINISH - SEQUENCE 2		F-19.22 APPLY ONE COAT OF BMS 10-20, TYPE II COATING IN ACCORDANCE WITH BAC 5793.					
GENERAL TOLERANCE REQUIREMENT		UNLESS OTHERWISE NOTED WITHIN THE 3D MBD CATIA DATA SET, THE LOCATION OF ALL PART FEATURES					
(CONTINUED ON NEXT PAGE)							
BOEING PROPRIETARY - SEE STANDARD NOTES FOR RESTRICTIONS ON DATA USE OR DISCLOSURE							

PARTS LIST	BOEING	CORPORATE OFFICES SEATTLE, WA 98124	EXPORT CONTROL COM	CAGE 81205	NUMBER 112U4930-40	REV A	SHEET 2 of 4
LIST TITLE MACHINED SKIN - LOWER, MID SPAR STA 1558.716 TO WBL 1243.750					MODEL	CONTRACT NUMBER	DATE 11-19-2009
(CONTINUED FROM PRECEDING PAGE)							
NOTE TITLE	NOTE DESCRIPTION						
	☐ ARE SUBJECT TO A SURFACE PROFILE TOLERANCE ZONE OF 0.1000 WITH RESPECT TO THE PRIMARY DATUM A, SECONDARY DATUM B, AND THE TERTIARY DATUM C						
MACHINE FINISH REQUIREMENTS	☐ MISMATCH BETWEEN CUTTER PASSES NOT TO EXCEED .003. IN ADDITION BLEND ALL EXTERNAL (OML) CUTTER MISMATCHES ON A 100/1 TAPER. MINIMUM CHORDWISE RADIUS (RADII RUNNING FORE AND AFT ON SKIN) IS .50.						
MACHINED SURFACE MISMATCH	☐ ALL CONNECTING CURVED SURFACES OR CURVED AND PLANE SURFACES SHOWN AS TANGENT MUST BE BLENDED SMOOTHLY AND MISMATCH MUST NOT EXCEED .005 EXCEPT AS NOTED.						
MATERIAL IDENTIFIER AND TEST REQUIREMENTS CODE	C9200-002-N0						
NONCONVENTIONAL MACHINING	☐ NONCONVENTIONAL MACHINING TECHNIQUES NOT SPECIFICALLY ALLOWED ARE PROHIBITED.						
OPPOSITE PART	112U4930-39 IS OPPOSITE TO 112U4930-40						
PROCESS SPECIFICATION	☐ AFTER COMPRESSION PEENING, LOCAL PEENING IS ALLOWED TO MEET CONTOUR REQUIREMENTS. SHOT PEEN USING 230 - 460 SHOT. ALL SURFACES PEENED AT THIS TIME TO AN INTENSITY OF .015A OR GREATER SHALL BE SANDED LOCALLY TO 125 MICROINCH FINISH USING A .300 CUTOFF PER BACD2097 AND LOCALLY COMPRESSION PEENED PER BAC 5730 AT .004A - .007A INTENSITY. COVERAGE: 1.0 AUTOMATED; 2.0 MANUAL, MANUAL EQUIPMENT OPTIONAL FOR THIS PROCESS ONLY.						
PROCESS SPECIFICATION	☐ AFTER FORMING, CHECK CONTOUR PER BAC 5300 . THE INBOARD HEADER SHALL BE LOCATED 0.5/1.5 OUTBOARD FROM THE INBOARD EDGE. THE OUTBOARD HEADER SHALL BE LOCATED 0.5/1.5 INBOARD FROM THE OUTBOARD EDGE. ADDITIONAL HEADERS ARE ALLOWED BETWEEN THE INBOARD AND OUTBOARD HEADER. ALLOW 5 LBS PER LINEAR INCH PRELOAD AT INBD HEADER TO A MAX OF 100 LBS. AT ALL OTHER HEADERS, ALLOW 3 LBS PER LINEAR INCH PRELOAD TO A MAX OF 50 LBS. TOTAL PRELOAD ON HEADERS IS NOT TO EXCEED 500 LBS. THE OUTSIDE SURFACE OF THE SKIN SHALL MEET A PROFILE OF A SURFACE OF .060 AT CONTOUR CHECK HEADERS FOR ACCEPTANCE.						
PROCESS SPECIFICATION	☐	MANUFACTURING OPTION - ABRASIVE WATER JET CUTTING PER BAC 5656 IS OPTIONAL TO CONVENTIONAL CUTTING TECHNIQUES.					
PROCESS SPECIFICATION	☐	MANUFACTURING OPTION - ELECTRICAL DISCHARGE MACHINING PER BAC 5969 IS OPTIONAL TO CONVENTIONAL MACHINING TECHNIQUES.					
PROCESS SPECIFICATION	☐	MANUFACTURING OPTION - LASER CUTTING PER BAC 5982 IS OPTIONAL TO CONVENTIONAL CUTTING TECHNIQUES.					
(CONTINUED ON NEXT PAGE)		공정을 적용한 경우에만 기록 해당					
BOEING PROPRIETARY - SEE STANDARD NOTES FOR RESTRICTIONS ON DATA USE OR DISCLOSURE							

PARTS LIST	BOEING		CORPORATE OFFICES SEATTLE, WA 98124	EXPORT CONTROL COM	CAGE 81205	NUMBER 112U4930-40	REV A	SHEET 3 of 4
LIST TITLE MACHINED SKIN - LOWER, MID SPAR STA 1558.716 TO WBL 1243.750						MODEL	CONTRACT NUMBER	DATE 11-19-2009
(CONTINUED FROM PRECEDING PAGE)								
NOTE TITLE		NOTE DESCRIPTION						
PROCESS SPECIFICATION		MANUFACTURING OPTION - THERMAL CUTTING PER BAC 5928 CLASS 1 IS OPTIONAL TO CONVENTIONAL CUTTING TECHNIQUES.						
PROCESS SPECIFICATION		○ RADIUS ALL EDGES PER BAC 5730 PRIOR TO SHOT PEENING.						
PROCESS SPECIFICATION		○ SHOT PEEN ALL SURFACES PER BAC 5730. INTENSITY 0.004A-0.007A.						
PROCESS SPECIFICATION		○ SHOT PEEN FORM PER BAC 5730-1 MAXIMUM SHOT SIZE 0.157 INCH DIAMETER. PRIOR TO COMPRESSION PEENING, SAND INTERIOR AND EXTERIOR SURFACES TO PRODUCE A 125 MICROINCH RA SURFACE ROUGHNESS PER BACD2097. IF FORMING AND COMPRESSION PEENING OPERATIONS ARE ACCOMPLISHED SIMULTANEOUSLY, NO FURTHER SURFACE ROUGHNESS IMPROVEMENTS ARE REQUIRED UNLESS OTHERWISE SPECIFIED.						
PROCESS SPECIFICATION		○ SURFACE ROUGHNESS 125 MICROINCHES RA ALL MACHINED SURFACES PER BACD2097.						
TAB REMOVAL		○ AFTER REMOVAL OF HANDLING TABS OR OTHER SUBSEQUENT TRIMMING, MAINTAIN 125 MICROINCHES RA SURFACE ROUGHNESS PER BACD2097. BREAK SHARP EDGES .020/.060R PER BAC5300. (OPTIONAL-CHAMFER .020/.040 X 45 DEG.) VISUAL INSPECTION SATISFACTORY. SHOT PEEN TRIMMED AREA. BARE AREA TO BE FINISHED WITH BRUSH ALODINE 600 PER BAC5719 TYPE II, CLASS A FOLLOWED BY TWO COATS OF BMS10-20 TYPE II PRIMER PER BAC5793 (BAKE NOT REQUIRED WITHIN 3 INCHES OF EDGE ON INTERIOR OR EXTERIOR SURFACES COMMON TO TAB REMOVAL).						
THICKNESS TOLERANCE		○ THICKNESS TOLERANCE FOR MACHINING IS + OR - .0100.						
* * * * *								
. . . COMPONENTS . . .								
QTY REQD	PART OR IDENTIFYING NUMBER	DESCRIPTION	NOTE TITLE	NOTE DESCRIPTION				
1	112U4930-104	○ MACHINED SKIN FLAT - LOWER, MID SPAR STA 1558.716 TO WBL 1243.750	Flat Pattern MBD 또는 2D DWG을 적용해야 하는 경우; - 해당 MBD에 대해 추가 Form 3 및 IP를 작성하거나, - "See Char. No. ##"라고 기입하여 첨부 후 요건을 검사/확인 함.					
PARENTHESIS () INDICATES SUBSTITUTE PART								
BOEING PROPRIETARY - SEE STANDARD NOTES FOR RESTRICTIONS ON DATA USE OR DISCLOSURE								

PARTS LIST	BOEING	CORPORATE OFFICES SEATTLE, WA 98124	EXPORT CONTROL COM	CAGE 81205	NUMBER 112U4930-40	REV A	SHEET 4 of 4
LIST TITLE MACHINED SKIN - LOWER, MID SPAR STA 1558.716 TO WBL 1243.750					MODEL	CONTRACT NUMBER	DATE 11-19-2009

. . . STANDARD NOTES . . .

NOTICE - THE INFORMATION CONTAINED HEREIN IS PROPRIETARY TO THE BOEING COMPANY AND SHALL NOT BE REPRODUCED OR DISCLOSED IN WHOLE OR IN PART OR USED FOR ANY PURPOSE EXCEPT WHEN SUCH USER POSSESSES DIRECT, WRITTEN AUTHORIZATION FROM THE BOEING COMPANY.

MATERIALS, PART & PROCESS SUBSTITUTION AND EQUIVALENTS PER 65B88700 (747), 012T2100 (767), 012W6100 (777), 012W6101 (LIAISON) AND 65-88700 (ALL OTHERS).

FASTENER SYMBOL CODES PER BACD2074. INSTALL PER BAC5004 AND BAC5047 (FLUID TIGHT). ☐

SURFACE ROUGHNESS INTERPRETATION PER BACD2097. ☐

UNLESS OTHERWISE SPECIFIED, DIMENSIONS ARE IN INCHES.

FOR DRAWING SHEETS DATED PRIOR TO 08/27/1984: DIMENSIONING AND TOLERANCING PER ANSI Y14.5-1973. FOR DRAWING SHEETS DATED ON OR AFTER 08/27/1984: DIMENSIONING AND TOLERANCING PER ANSI Y14.5M-1982. FOR DRAWING SHEETS DATED ON OR AFTER 06/23/1997: DIMENSIONING AND TOLERANCING PER ASME Y14.5M-1994, UNLESS OTHERWISE NOTED ON DRAWING SHEET.

UNLESS OTHERWISE SPECIFIED, RIVET & BOLT EDGE MARGINS PLUS OR MINUS .05. ☐

UNLESS OTHERWISE SPECIFIED, BEND RADII SHALL BE PLUS OR MINUS .01 INCH ON MATERIAL THICKNESS BELOW .06 INCH AND PLUS OR MINUS .03 ON MATERIAL THICKNESS GREATER THAN .06 INCH. ☐

UNLESS OTHERWISE SPECIFIED, SHEET METAL CORNER RADII SHALL BE .16 INCH TO .19 INCH ON INTERNAL RADII AND .00 INCH TO .25 INCH ON EXTERNAL RADII. ☐

DIMENSIONS AND SURFACE TEXTURE DESIGNATIONS APPLY BEFORE PLATING OR FINISH COATING UNLESS OTHERWISE NOTED. ☐

UNLESS OTHERWISE SPECIFIED, FABRICATION, ASSEMBLY, AND INSTALLATION SHALL CONFORM TO THE FOLLOWING:

BAC5009 FOR INSTALLATION OF BOLTS AND NUTS. ☐

BAC5300 TO FORM, PUNCH, STRAIGHTEN, BREAK SHARP EDGES AND FIT METAL PARTS. ☐

BAC5307 FOR PART MARKING. ☐

BAC5602 FOR HEAT TREAT OF ALUMINUM ALLOYS. ☐

☐ : Required to record on Form 3

☐ : Not required to record on Form 3, but recorded on Form 1 or Form 2