

## Title:

# 4L-DS500T(B) PAINT SPECIFICATION

## Version control:

| Revision # | Date       | Updates                               | Prepared by    |
|------------|------------|---------------------------------------|----------------|
| A          | 05/25/2023 | First version                         | Zhongliang Zhu |
| B          | 06/03/2026 | Primer change, stack thickness change | Zhongliang Zhu |
| C          |            | -                                     |                |

## External Distribution :

☒ YES

☐ NO

## 1. Materials:

| Part #          | Product Description                    |
|-----------------|----------------------------------------|
| Cashew JP part# |                                        |
|                 | Strone Ace No. 2000 Clear              |
|                 | Hardner for No. 2000                   |
| T702-10-2635    | Strone Ace No. 2635 Thinner            |
| Y119-15550      | Strone Ace HG-650 White-4              |
| T195-00-1073    | Strone Hardener TXL No.73              |
| T119-23-1405    | DS500T_Rev.B_Ver.04 (B22)              |
| T182-00-7002    | CR-900TXL Clear w/ AFP                 |
| T182-00-7004    | Strone Ace CR-900TXL Flat (B22) w/ AFP |
| T195-00-7502    | Strone Hardener UH-80                  |
| T702-10-2185    | Strone No.2185 Thinner                 |

## 2. Paint layer construction:

Layers from bottom (on substrate) to top (facing environment):

- Primer:
  - Material: Strone Ace No. 2000
  - Dry film thickness: 16±2um
- Basecoat (2 Pass):
  - Material: Strone Ace HG-650 White-4
  - Dry film thickness: 42±4um
- Color layer:
  - Material: Strone Ace HG-650 DS500T(B)
  - Dry film thickness: 21±2um
- Clear coat:
  - Material: Strone Ace CR-900TXL(B)
  - Dry film thickness: 21±2um

Schematic:

|                             |
|-----------------------------|
| CR-900TXL(B), 21±2um        |
| TAN499T(B), 21±2um          |
| White-4, 42±4um             |
| Strone Ace No. 2000, 16±2um |
| Al Substrate                |

### 3. Process document:

- Primer: 70°C for 30 min.
- Basecoat: 80°C for 30 min.
- Color layer: 80°C for 30 min.
- Clear coat: 80°C for 30 min.
- Post Bake: 120°C for 30 min.

### 4. Acceptance criteria:

- Overall thickness: 100±10um
- Adhesion: >4B using ASTM D3359 method, 2mm gap
- Gloss: 3.0 to 6.0
- Color measurement value:  $\Delta E < 1$  from the following results

| Light Condition | D65   |
|-----------------|-------|
| SCI/SCE         | SCI   |
| L*              | 70.76 |
| a*              | 1.39  |
| b*              | 9.89  |
| C*              | 9.99  |
| H               | 82.01 |