

Title:

4L-TAN499T(B) PAINT SPECIFICATION

Version control:

Revision #	Date	Updates	Prepared by
A	05/25/2023	First version	Zhongliang Zhu
B	06/03/2026	Primer change, stack thickness change	Zhongliang Zhu
C		-	

External Distribution :

☒ YES

☐ NO

1. Materials:

Part #	Product Description
Cashew JP part#	
	Strone Ace No. 2000 Clear
	Hardener for No. 2000
T702-10-2635	Strone Ace No. 2635 Thinner
Y119-15550	Strone Ace HG-650 White-4
T195-00-1073	Strone Hardener TXL No.73
T702-10-2475	Strone No.2475 Thinner
Y119-15547	TAN499(B) SC Ver.1
T182-00-7002	CR-900TXL Clear w/ AFP
T182-00-7004	Strone Ace CR-900TXL Flat (B22) w/ AFP
T195-00-7502	Strone Hardener UH-80
T702-10-2185	Strone No.2185 Thinner

2. Paint layer construction:

Layers from bottom (on substrate) to top (facing environment):

- Primer:
 - Material: Strone Ace No. 2000
 - Dry film thickness: 16±2um
- Basecoat (2 Pass):
 - Material: Strone Ace HG-650 White-4
 - Dry film thickness: 42±4um
- Color layer:
 - Material: Strone Ace HG-650 TAN499T(B)
 - Dry film thickness: 21±2um
- Clear coat:
 - Material: Strone Ace CR-900TXL(B)
 - Dry film thickness: 21±2um

Schematic:

CR-900TXL(B), 21±2um
TAN499T(B), 21±2um
White-4, 42±4um
Strone Ace No. 2000, 16±2um
Al Substrate

3. Process document:

- Primer: 70°C for 30 min.
- Basecoat: 80°C for 30 min.
- Color layer: 80°C for 30 min.
- Clear coat: 80°C for 30 min.
- Post Bake: 120°C for 30 min.

4. Acceptance criteria:

- Overall thickness: 100±10um
- Adhesion: >4B using ASTM D3359 method, 2mm gap
- Gloss: 4.0 to 5.5
- Color measurement value: $\Delta E < 1$ from the following results

Light Condition	D65
SCI/SCE	SCI
L*	48.12
a*	2.43
b*	11.93
C*	16
H	73