

Multicores Copper & Aluminum Conductors

XLPE Insulated and PVC Sheathed

Voltage Grade

3.6 / 6 (7.2) KV

Description

Soft annealed Stranded circular compacted Copper or Stranded circular compacted Aluminum conductor, semiconducting layer as conductor screen, XLPE insulated, semiconducting layer as non metallic insulation screen, Copper tape or wire as metallic insulation screen, three cores assembled together with non hygroscopic Polypropylene fillers, banded with suitable tape and PVC sheathed.

Application

These cables are generally suitable for direct burial or for installation on trays or in ducts.

Technical Data

Relevant Standard	IEC 60502
Conductor	Plain copper conductor class 2 or Aluminum conductor class 2
Conductor Screen	Extruded Semiconductive Compound
Insulation	Extruded XLPE Compound Rated 90° C
Insulation Screen	Non Metallic part: Extruded Semiconductive Compound (Bonded or Strippable) to the insulation Metallic part: (by one of the following) • Copper tape is applied helically with a suitable overlap. • Copper Wires helically applied and binded with a Copper tape to achieve electrical contact Conductor screen, XLPE insulation and non metallic insulation screen are applied at the same time using triple head extruder.
Assembly	The insulated Cores are assembled together using nonhygroscopic polyprobylene filler (if needed), then banded with suitable tape
Outer Sheath	Extruded PVC Compound
Cores Indentification	by inserting Red, Yellow, Blue narrow plastic tapes between the non metallic & the metallic insulation screen, or any other color according to customer request
Outer Sheath Color	Black (default color), or any other color according to customer request
Maximum Operating Temp.	90° C
Minimum bending Radius	12 x outer diameter
Packing Condition	Our standard length on Wooden Drum / or according to customer request



MEDIUM VOLTAGE CABLES

Product Code	Nominal Cross Sectional Area	Max. Conductor Resistance		Operating Capacitance	Inductance	Current Rating			Approx. Overall Diameter	Approx. Weight
		DC at 20 °C	AC at 90° C			Laid in Ground	Laid in Duct	Laid in Free Air		
	mm²	Ω/km	Ω/km	µF/km	mH/km	A	A	A	mm	kg/km
A - Copper Conductors										
PM-CT14-X5-03-UP	50	0.3870	0.4956	0.3425	0.3287	207	166	215	38.0	2370
PM-CT15-X5-03-UP	70	0.2680	0.3435	0.3975	0.3110	254	205	269	42.1	3145
PM-CT16-X5-03-UP	95	0.1930	0.2479	0.4432	0.2980	304	247	324	45.3	3950
PM-CT17-X5-03-UP	120	0.1530	0.1970	0.4858	0.2843	344	281	370	48.1	4730
PM-CT18-X5-03-UP	150	0.1240	0.1602	0.5314	0.2782	385	320	420	52.0	5720
PM-CT19-X5-03-UP	185	0.0991	0.1289	0.5860	0.2702	434	365	480	56.1	6890
PM-CT20-X5-03-UP	240	0.0754	0.0992	0.6311	0.2620	500	428	561	61.7	8700
PM-CT21-X5-03-UP	300	0.0601	0.0803	0.6466	0.2583	559	484	639	67.7	10755
PM-CT22-X5-03-UP	400	0.0470	0.0646	0.6722	0.2541	633	558	731	74.8	13555
PM-CT23-X5-03-UP	500	0.0366	0.0524	0.7084	0.2495	708	637	834	83.2	17105
B - Aluminum Conductors										
PM-AT14-X5-03-UP	50	0.6410	0.8248	0.3548	0.3240	162	130	167	38.9	1555
PM-AT15-X5-03-UP	70	0.4430	0.5704	0.4006	0.3091	197	162	208	42.3	1915
PM-AT16-X5-03-UP	95	0.3200	0.4123	0.4493	0.2945	236	194	252	45.3	2260
PM-AT17-X5-03-UP	120	0.2530	0.3263	0.4889	0.2837	268	222	289	48.3	2605
PM-AT18-X5-03-UP	150	0.2060	0.2660	0.5405	0.2767	301	252	328	52.6	3075
PM-AT19-X5-03-UP	185	0.1640	0.2123	0.5951	0.2690	340	288	376	56.7	3585
PM-AT20-X5-03-UP	240	0.1250	0.1625	0.6311	0.2620	393	334	441	61.7	4330
PM-AT21-X5-03-UP	300	0.1000	0.1308	0.6466	0.2583	443	380	505	67.7	5205
PM-AT22-X5-03-UP	400	0.0778	0.1028	0.6722	0.2541	508	444	586	74.8	6440
PM-AT23-X5-03-UP	500	0.0605	0.2495	0.7084	0.2495	578	520	680	83.2	7920

The above data is approximate and subject to manufacturing tolerances

Note:-

Flame retardant PVC sheathed or Polyethylene Sheathed are available according to customer request
Longitudinal or radial Water tightness layers are also available according to customer request
the below data are applicable for cables with rated voltage 3.8 / 6.6 (7.2) KV