Full Report

"Can ZnS-MoS2 (shell) with SiO2 (core) in core-shell structure can be used for TENG application?"
Generated by LeapSpace

SiO2-Core / ZnS-MoS2-Shell for TENGs at a Glance

Key Findings Table

Key finding	Relevance to proposed material	Population / system	Evidence
Direct TENG evidence for exact SiO2@ZnS-MoS2 was not found	The concept is not yet directly validated in the retrieved TENG literature	Retrieved 2018-2025 adjacent materials/device studies	[1] [2] [3] [4] [5] [6] [7] [8] [9] [10] [11] [12] [13] [14] [15] [16]
MoS2 has the strongest direct TENG relevance among the shell components	Supports using a MoS2-rich outer shell for charge trapping and stable output	MoS2-filled or MoS2-based TENGs	[17] [18] [19] [20]
SiO2-core / MoS2-shell precedent exists for humidity-resistant TENG behavior	Closest direct architectural analogy to the proposed design	MoS2-encapsulated SiO2 nanoparticle TENG	[21]
Core-shell dielectric engineering can improve interfacial control, breakdown strength, and lower loss	Supports the value of putting a functional shell on an insulating core	PVDF and related dielectric nanocomposites	[22] [23] [24]
Shell quality matters: thickness, uniformity, clean surfaces, and adhesion are decisive	Poor shell formation could negate any triboelectric advantage	Core-shell synthesis literature	[25] [26] [27] [28]
ZnS may help dielectric tuning, but excessive loading can hurt breakdown behavior	ZnS is plausible, but composition/loading must be optimized carefully	ZnS/polymer dielectric composites	[23] [24] [29]
Humidity, wear, and repeated deformation are major TENG failure drivers	A protective shell and encapsulation strategy are practically important	TENG stability and wearable-device studies	[30] [31] [32]

Direct Answer

Yes, in principle, a SiO2-core with a ZnS-MoS2 shell is a credible candidate for TENG applications, but the current support is indirect rather than directly proven for that exact composition [1] [17] [18] [22].

The strongest evidence-based design logic is:

- **SiO2 core**: mechanically stable insulating core compatible with conformal shell growth and interface engineering [27] [33].
- **MoS2 in the shell**: best-supported TENG-active component for negative charge trapping, charge retention, dielectric enhancement, and long-cycle stability [17] [18] [19] [20].
- **ZnS in the shell**: potentially useful for dielectric tuning, but it introduces risk if it raises leakage or lowers breakdown strength at excessive effective loading [24] [29].

Taken together, these findings suggest the architecture is promising especially as a multifunctional filler in a polymer tribolayer such as PDMS, PVDF, or PVDF-TrFE, rather than as a standalone particle-only tribosurface [20] [34] [35].
However, no retrieved study directly benchmarked SiO2@ZnS-MoS2 TENGs with Voc, Isc, charge density, or power density, so performance claims remain provisional [1] [20].

Confidence level: Medium - the underlying mechanisms are well supported by adjacent evidence, but the exact proposed material lacks direct TENG validation [1] [20] [22].

Study Scope

- **Time period covered:** primarily 2018-2025 retrieved studies and foundational adjacent materials papers summarized in the input [1] [20].
- **Disciplines covered:** triboelectric nanogenerators, dielectric polymer nanocomposites, core-shell particle synthesis, interface engineering, and device stability [24] [30].
- **Methods represented:** contact-separation TENG studies, composite-film design, hydrothermal/sol-gel/CVD-CVS/ALD-related shell formation studies, and dielectric-performance analyses [17] [27] [33].

Assumptions & Limitations

- The assessment relies mainly on **adjacent evidence** because no directly retrieved TENG paper on **SiO2-core/ZnS-MoS2-shell** was identified [1] [5] [20].
- The **MoS2 contribution is better supported than the ZnS contribution** in TENG-specific contexts [17] [18] [19] [29].
- Optimal **shell thickness, ZnS:MoS2 ratio, and filler loading window** for this exact architecture remain unknown [1] [29] [36].
- Environmental durability is a major concern for TENGs, so any feasibility judgment assumes proper shell integrity and moisture-management design [30] [32].

Suggested Further Research

- Fabricate and benchmark **SiO2@ZnS-MoS2** in a standard contact-separation TENG with **Voc, Isc, charge density, and power density** against SiO2-only, MoS2-only, ZnS-only, and binary controls [1] [20].
- Systematically vary **ZnS:MoS2 shell composition**, with MoS2 enriched near the outer surface to test whether tribo-negative behavior improves [18] [20].
- Map the **loading window** in PDMS or PVDF-type matrices to maximize output while avoiding leakage, agglomeration, and flexibility loss [29] [34] [36].
- Test **humidity and wear stability** under high RH and long-cycle bending/contact conditions, since these are common failure pathways [21] [30] [31].
- Compare **gradient shells** versus mixed shells, since interface placement likely matters as much as composition [24] [27].

1. Introduction and Scope

The question is not whether this exact material has already been proven in a TENG; the retrieved evidence indicates that it has **not** yet been directly reported in the provided TENG literature [1] [5] [20]. The more useful question is whether the known functions of **SiO2**, **ZnS**, **MoS2**, and **core-shell interface engineering** make the design scientifically plausible for triboelectric nanogenerators [17] [22] [24].

The answer is a **cautious yes**. The rationale comes from three converging lines of evidence:

1. **MoS2-containing TENG materials** repeatedly improve charge trapping, negative charge accumulation, dielectric response, and cycle stability [17] [18] [19] [20].
2. **SiO2-based core-shell particles** are compatible with conformal shell engineering and can support controlled interfaces [27] [33].
3. **Core-shell dielectric architectures** in polymer composites can suppress loss, improve breakdown behavior, and better manage local electric fields and interfacial polarization [22] [23] [24].

A direct performance forecast is not possible from the supplied evidence, but the architectural logic is strong enough to justify experimental development [1] [20].

Confidence level: Medium - clear mechanistic support exists, but direct device benchmarking is absent [1] [22].

2. Foundational Context: Why Core-Shell Engineering Matters in TENGs

TENG output depends strongly on how much surface charge can be generated, retained, and transferred during repeated contact-separation or related motions [34] [35]. Materials design therefore often aims to improve four coupled properties:

- **Triboelectric polarity and charge affinity** [17] [18]
- **Dielectric response and interfacial polarization** [22] [23]
- **Charge trapping / leakage suppression** [20] [24]
- **Mechanical and environmental stability** [30] [31]

A core-shell particle can address these simultaneously. An **insulating core** can help maintain electrical isolation and structural stability, while a **functional shell** can tailor surface chemistry, trap states, and local-field behavior [22] [23]. In related dielectric nanocomposites, core-shell design reduces energy loss by controlling interfacial polarization and space-charge behavior, while preserving useful permittivity [22]. Similar principles are relevant in TENG composites, where higher matrix permittivity and better charge retention can raise surface charge density and output [34] [35].

For the proposed material specifically:

- **SiO2** is attractive as a core because silica surfaces are well studied for shell growth and can support conformal coatings when properly cleaned and hydroxylated [26] [27].
- **MoS2** is attractive in the shell because it has direct TENG evidence for charge trapping, added negative-charge accumulation, and stable operation [17] [18] [20].
- **ZnS** is attractive as a shell component because adjacent evidence suggests dielectric benefit, although with loading-sensitive tradeoffs [29].

Taken together, these findings suggest that a SiO2 core with a ZnS-MoS2 shell is most plausible when designed as an interfacially engineered composite filler rather than as a simple particulate additive without shell control [24] [27].

Confidence level: High - the foundational role of dielectric/interface engineering is consistently supported across the supplied literature [22] [23] [24].

3. Evidence Base and Its Main Limitation

The largest constraint is straightforward: **no directly retrieved TENG report on SiO2-core/ZnS-MoS2-shell particles was identified** [1] [2] [3] [4] [5] [6] [7] [8] [9] [10] [11] [12] [13] [14] [15] [16]. The literature in the retrieved set on ZnS-containing SiO2 core-shell systems mainly concerns photocatalysis, optoelectronics, supercapacitors, solar cells, and insulation materials rather than TENG devices [1] [3].

The assessment therefore depends on three adjacent evidence classes:

Evidence class	What it contributes	Key citations
MoS2-based TENG studies	Direct triboelectric mechanism and performance relevance	[17] [18] [19] [20]

Evidence class	What it contributes	Key citations
SiO2/MoS2 or SiO2-shell interface studies	Structural precedent for coated silica and humidity protection	[21] [27]
Core-shell dielectric composite studies	Physical basis for interfacial polarization control and leakage suppression	[22] [23] [24]

This is sufficient to answer **feasibility**, but not enough to claim established superiority over simpler fillers [1] [36].

Confidence level: High - the gap in direct evidence is explicit and well supported [1] [20].

4. Core-Shell Synthesis and Interface Engineering

4.1 Routes for building shells on silica cores

Related studies indicate several viable shell-formation routes around silica:

- **Sol-gel / TEOS hydrolysis-condensation** can form conformal silica shells and controlled core-shell morphologies [33] [37].
- **Hydrothermal methods** can build sulfide or oxide-derived coatings and preserve morphology through conversion steps [38] [39] [40].
- **Aerosol CVS/CVD and ALD-type approaches** offer strong shell-thickness control, including conformal coatings in the 1-10 nm range [27] [28] [41].
- **Layer-by-layer methods** are possible, but the supplied review notes that these often suffer from low surface coverage and nonuniform coatings [42].

For the proposed SiO2@ZnS-MoS2 system, the most defensible inference is that **a multistep route would likely be needed**, with a cleaned/hydroxylated SiO2 core, controlled Zn-containing shell deposition or conversion, then MoS2-rich outer shell growth or anchoring [27] [28]. This is an inference from adjacent shell-growth evidence rather than a directly retrieved recipe for the exact composition [27].

4.2 Thickness, uniformity, and adhesion control

The literature strongly indicates that shell performance depends on process discipline:

- Shell thickness depends on **reagent concentration** and **core-particle amount** [28].
- Uniform shell formation on silica benefits from **clean, hydroxylated surfaces**; residues can prevent proper coating [26] [27].
- Vapor-phase routes help avoid solvent residues that hinder shell formation [27].

- Good shell anchoring in related systems is aided by **nucleation sites** and **coordination/electrostatic interactions** [43].

This matters for TENGs because poor shell uniformity can create weak spots for leakage, nonuniform charge trapping, and agglomeration in polymer films [24] [44].

4.3 Implications for composite-film fabrication

Composite performance improves when particle distribution and interfaces are controlled:

- Homogeneous coating and dispersion improved output and durability in related piezo-triboelectric composites [44].
- SiC@SiO2 improved dielectric behavior in PDMS films for higher TENG output [45].
- MoS2-containing composites showed gains when MoS2 was uniformly distributed or encapsulated [18] [21] [46].

Taken together, these findings suggest that the success of SiO2@ZnS-MoS2 for TENGs will likely depend as much on shell conformity and dispersion in the polymer matrix as on the nominal chemistry itself [24] [27] [45].

Confidence level: High - this synthesis-control conclusion is repeatedly supported across multiple adjacent materials studies [25] [26] [27] [28].

5. Triboelectric Output and Charge-Storage Mechanisms

5.1 What MoS2 already does well in TENGs

Among the proposed shell components, **MoS2 has the clearest direct TENG support**:

- In PVDF hybrid films, MoS2 increased output to about **200 V** and **11.8 μA**, attributed to trap states, improved charge capture, and added polarity [17].
- In stretchable **MoS2@Ecoflex**, the MoS2 monolayer acted as a high-area charge trap, increasing negative charge accumulation and enabling **11.2 mW** output with **230% stretchability** [18].
- MoS2 nanosheets in silk fibroin produced **0.95 kV Voc** and **2.2 μA Isc**, alongside dielectric enhancement favorable for charge storage [19].
- A **PVDF-TrFE/MoS2/ion-gel** composite sustained stable output over **50,000 cycles**, linked to strong electrostatic interactions and improved crystalline β-phase formation [20].

These results make MoS2 the best-supported reason to expect the proposed shell to work in TENG service [17] [20].

5.2 SiO2/MoS2 core-shell-like precedent

A particularly relevant precedent is that **MoS2-encapsulated SiO2 nanoparticles** improved humidity resistance by shielding the interface from water, stabilizing charge density, and reducing charge decay; the device retained **>70% output after 25 h at 99% RH** [21]. This does not validate ZnS-MoS2 shells specifically, but it does validate the broader idea that a **silica-centered, MoS2-coated architecture can be TENG-relevant and environmentally beneficial** [21].

A second high-performance adjacent example used a **MoS2/SiO2/Ni-mesh layer** and reached a charge density of **1228 μC m−2** [47]. This is not the same architecture as the proposed core-shell particle, but it reinforces the value of combining SiO2 and MoS2 in a TENG-relevant interfacial design [47].

5.3 Dielectric enhancement and leakage suppression

Core-shell dielectric literature provides the mechanistic bridge for why a SiO2-core/ZnS-MoS2-shell filler may help:

- **BaTiO3/SiO2** core-shell nanoparticles in PVDF reduced energy loss by **46%** and achieved **6.28 J/cm3** energy density at **340 MV/m**, attributed to reduced interfacial polarization loss and improved field management [22].
- **BaTiO3/Al2O3** showed that insulating shells can suppress dielectric loss while maintaining useful permittivity and improving breakdown strength [23].
- More generally, core-shell architectures can preserve high breakdown strength and reduce dielectric loss even when the inner filler is otherwise problematic [24].

This does not prove TENG output directly, but it strongly supports the idea that a SiO2-based core-shell filler can improve the electrostatic environment inside a tribolayer [22] [24].

5.4 Where ZnS fits

The ZnS-specific evidence is weaker in TENGs, but not irrelevant. ZnS/PVDF showed a **loading-dependent tradeoff**: low loading improved breakdown strength and energy density, but high loading reduced breakdown strength [29]. This suggests ZnS may be useful as a dielectric-tuning shell component only within a carefully controlled composition/loading regime [29].

Inferred: A ZnS-rich inner shell combined with a MoS2-rich outer shell could be a rational design, with ZnS supporting dielectric tuning and MoS2 dominating surface charge trapping. Confidence level: Low - this arrangement is not directly tested in the supplied studies, but it is consistent with the component-specific roles reported separately [18] [22] [29].

Confidence level: Medium-High - MoS2 mechanisms are directly supported; ZnS's role is plausible but less directly validated for TENGs [17] [29].

6. Comparative Benchmarking Against Existing Nanofillers

6.1 Bare SiO2 vs MoS2 vs ZnS

The supplied evidence does not provide a direct head-to-head TENG comparison among bare SiO2, ZnS, and MoS2 under identical conditions [1] [46]. Still, the relative support is uneven:

- **MoS2**: strongest direct TENG evidence for charge trapping, negative charge accumulation, dielectric enhancement, stretchability, and long-term cycling [17] [18] [19] [20].
- **SiO2**: strongest support as a structural/dielectric core and shell-growth platform rather than as the main active tribo-enhancing component in the supplied evidence [27] [33].
- **ZnS**: plausible dielectric enhancer, but riskier because excessive effective loading can reduce breakdown strength [29].

6.2 Hybrid and heterostructure precedent

A wider trend in the supplied literature favors **multifunctional heterostructures** over single fillers:

- Mixed inorganic fillers can outperform single-filler systems by balancing dielectric gain and durability [48] [49].
- In MgWO4-PDMS, a defined ceramic loading of **3.41 vol%** maximized output while suppressing leakage, illustrating that carefully tuned multifunctional filler design can widen the usable processing window [36].
- Related hybrid TENGs link improved interfacial polarization and charge trapping to higher charge density and stronger output [35] [49] [50].

This broader pattern supports the proposed architecture conceptually, because **SiO2@ZnS-MoS2 is exactly the kind of multifunctional, interface-designed filler the field is moving toward** [34] [35] [50].

6.3 Likely optimal loading/design window

The evidence indicates that **low-to-moderate loading is more likely to succeed than heavy loading**:

- High ZnS loading can weaken breakdown strength [29].
- Specific ceramic/polymer systems show clear optima rather than monotonic improvement [36].
- TENG composites benefit from dielectric enhancement, but only while leakage and flexibility remain under control [34] [36].

Taken together, these findings suggest that SiO2@ZnS-MoS2 should first be explored at conservative filler loadings in flexible matrices, with shell quality and dispersion prioritized over maximizing inorganic content [24] [29] [36].

Confidence level: Medium - the loading principle is well supported in adjacent systems, but the exact window for this proposed filler is unknown [29] [36].

7. Practical Viability, Stability, and Device Use

7.1 Environmental and cycling stability

Humidity is a well-established TENG problem because it promotes charge leakage and lowers retained surface charge [30]. Repeated contact can also cause wear, while bending/stretching can crack active layers or degrade interfaces [30].

The strongest adjacent evidence for the proposed architecture is again the **MoS2-on-SiO2** precedent: MoS2-encapsulated SiO2 nanoparticles preserved **>70% output after 25 h at 99% RH**, indicating that such shells can act as moisture-shielding layers [21]. More generally, encapsulation and hydrophobic protection are reported to preserve performance even under high humidity and long cycling [31] [32].

7.2 Wearable and long-term operation

Wearable TENGs need:

- flexible electrodes,
- wear-resistant tribolayers,
- interface adhesion,
- moisture protection,
- and stable performance under deformation [30] [31].

MoS2-based composites are favorable here because they already show stable long-cycle and stretchable-device behavior in the supplied studies [18] [20]. That makes MoS2 a particularly strong outer-shell candidate if the design target includes flexible or wearable harvesting [18].

7.3 Practical judgment

From a practical standpoint, the proposed architecture is **realistic enough to justify fabrication**, especially if used as a dispersed filler in a polymer tribolayer rather than as a brittle bulk layer [20] [34]. Its likely advantages are:

- improved charge trapping from MoS2 [17] [18],
- possible dielectric tuning from ZnS [29],
- structural and interface support from SiO2 [27] [33],
- and possible humidity resistance if the shell is continuous and hydrophobic enough [21] [32].

Its main risks are:

- no direct benchmark for the exact material [1],
- shell nonuniformity or weak adhesion [26] [42],
- ZnS-related leakage/breakdown tradeoffs if overused [29],
- and unresolved composition/loading optimization [36].

Confidence level: Medium - viability is plausible and actionable, but not experimentally established for this exact formulation [1] [21].

8. Final Assessment

Yes, SiO2-core / ZnS-MoS2-shell core-shell particles can reasonably be proposed for TENG applications, but at present this is a mechanistically supported research direction rather than a directly validated device material [1] [17] [22].

The most evidence-supported interpretation is:

1. **MoS2 is the key TENG-enabling component**, because it directly improves negative charge trapping, charge retention, dielectric behavior, and long-term stability [17] [18] [19] [20].
2. **SiO2 is a sensible core**, because silica supports conformal shell growth and stable core-shell interface engineering [26] [27] [33].
3. **ZnS may add useful dielectric tuning**, but it should probably be kept compositionally controlled to avoid breakdown-strength penalties [29].
4. **The most likely successful implementation is as a filler in PDMS, PVDF, or PVDF-TrFE**, where core-shell design can tune permittivity, leakage, and retained charge together [20] [34].

So the balanced answer is:

- **Scientifically plausible:** yes [18] [24]
- **Directly demonstrated for the exact material:** no [1]
- **Worth experimental pursuit:** yes, especially with a MoS2-rich outer shell, careful loading control, and humidity-focused testing [21] [29] [32]

Overall confidence: Medium - the indirect case is strong, but the missing direct benchmark remains the central limitation [1] [20] [22].

References

1. Ren, Y., Liu, G., Zhu, T. (2021) Fabrication of Core-Shell Nanocolloids with Various Core Sizes to Promote Light Capture for Green Fuels. *Chemistry - An Asian Journal*. https://doi.org/10.1002/asia.202001448

2. Manimekalai, A., Sakthi Velu, K.S., Sonaimuthu, S., Sun, S. (2025) Enhancing photovoltaic performance of flower-like MoS2@ZnO core-shell nanowire photoanodes: Synergistic effects on solar energy conversion. *Current Applied Physics*. https://doi.org/10.1016/j.cap.2025.05.003
3. Kadim, A.M. (2020) Enhanced Performance of White Light Generation from ZnS/ZnO Core/Shell Nanocrystals. *IOP Conference Series: Materials Science and Engineering*. https://doi.org/10.1088/1757-899X/928/7/072018
4. G, G., Arumugam, A. (2022) Enhanced photocatalytic activities of CeO2@ZnO core-shell nanostar particles through delayed electron hole recombination process. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. https://doi.org/10.1016/j.colsurfa.2022.128920
5. Wang, C., Drame, B., Niare, L., Yuegang, F. (2022) Optimization of the Shell Thickness of the ZnO/CdS Core-Shell Nanowire Arrays in a CZTS Absorber. *International Journal of Optics*. https://doi.org/10.1155/2022/5301790
6. Deb, S., Kalita, P.K., Datta, P. (2020) Opto-electronic characterization of starch capped zinc chalcogenides (core-shell) nanocomposites and their application as Schottky device. *Physica Scripta*. https://doi.org/10.1088/1402-4896/abac75
7. Basnet, P., Samanta, D., Chatterjee, S. (2021) Chemical Approach Based ZnS-ZnO Nanocomposite Synthesis and Assessment of their Structural. *Journal of Nano- and Electronic Physics*. https://doi.org/10.21272/jnep.13(1).01025
8. Gonçalves, J.M., da Silva, M.I., Hasheminejad, M., (...), Angnes, L. (2021) Recent Progress in Core@Shell Sulfide Electrode Materials for Advanced Supercapacitor Devices. *Batteries and Supercaps*. https://doi.org/10.1002/batt.202100017
9. Han, Y., Zhao, C., Sun, J., Li, Z. (2023) Charge Transport Characteristics of Core-Shell SiC Filled Epoxy Nanocomposites. *IEEE Transactions on Dielectrics and Electrical Insulation*. https://doi.org/10.1109/TDEI.2023.3289775
10. Asad, U., Amin, S., Aziz, M.H., (...), Awan, H.A. (2020) The tracking and erosion performance of silicone rubber incorporated with novel TiO2@SiO2 core-shell nano fillers under the IEC 60587 standard. *Materials Research Express*. https://doi.org/10.1088/2053-1591/ab5e69
11. Wu, H., Jile, H., Chen, Z., (...), Yi, Y. (2020) Fabrication of ZnO@MoS2 nanocomposite heterojunction arrays and their photoelectric properties. *Micromachines*. https://doi.org/10.3390/mi11020189
12. Naskar, I., Ghosal, P., Deepa, M. (2022) Efficient charge storage by ZnCo2S4 nanoflakes@MgCo2O4 nanorods composite in Mg2+/Zn2+/K+ conducting electrolytes. *Journal of Energy Storage*. https://doi.org/10.1016/j.est.2022.105389
13. Ma, L., Miao, Y., Zhang, M., (...), Sun, Z. (2022) A succulent-like structure of MoS2-coated S-doped ZIF-67@NF as the supercapacitor electrode material. *Journal of Materials Science: Materials in Electronics*. https://doi.org/10.1007/s10854-021-07394-0

14. Nag, R., Paul, S., Bera, A. (2022) A Type-II Heterostructure with a KBiFe2O5 Brownmillerite Core and a ZnO Nanoparticle Shell for Enhanced Optoelectronic Performance. *ChemistrySelect*. https://doi.org/10.1002/slct.202202802

15. Ranjith, R., Devendrapandi, G., Karthika, P.C., (...), Lavanya, M. (2024) Astonishing performance of zinc iron sulfide with MoS2 composite in allium-shaped structure for comprehensive alkaline water splitting. *International Journal of Hydrogen Energy*. https://doi.org/10.1016/j.ijhydene.2024.06.172

16. Pathak, B., Choudhury, J.P.R., Kalita, P.K., Aomoa, N. (2019) Optical properties of PbO/ZnO core/shell dispersed in PVP matrix. *Materials Today: Proceedings*. https://doi.org/10.1016/j.matpr.2020.04.158

17. Hedau, B., Kang, B.-C., Ha, T.-J. (2022) Enhanced Triboelectric Effects of Self-Poled MoS2-Embedded PVDF Hybrid Nanocomposite Films for Bar-Printed Wearable Triboelectric Nanogenerators. *ACS Nano*. https://doi.org/10.1021/acsnano.2c06257

18. Kim, H., Rana, S.M.S., Faruk, O., (...), Park, J.Y. (2023) A Stretchable Triboelectric Nanogenerator Based on Molybdenum Disulfide for Wearable Self-Powered Biomotion Monitoring. *PowerMEMS 2023 - 2023 IEEE 22nd International Conference on Micro and Nanotechnology for Power Generation and Energy Conversion Applications*. https://doi.org/10.1109/PowerMEMS59329.2023.10417564

19. Joshi, S.R., Kim, S. (2024) Functional silk-protein-based nanocomposites for light-stimulated and highly efficient triboelectric nanogenerators and charge storage devices. *Journal of Power Sources*. https://doi.org/10.1016/j.jpowsour.2024.235538

20. Biswas, M., Bhunia, R., Mondal, R., (...), Chowdhury, A. (2026) Ion-Gel-Driven Electroactive Phase Nucleation in PVDF-TrFE/MoS2 Composites for High-Throughput Triboelectric Nanogenerators. *ACS Applied Materials and Interfaces*. https://doi.org/10.1021/acsami.6c02323

21. Kim, D.-H., Park, J.Y., Choi, H.S., (...), Baik, J.M. (2025) Advancing Humidity-Resistant Triboelectric Nanogenerators Through MoS_2-Encapsulated SiO_2 Nanoparticles for Self-Powered Gas Sensing Applications. *Advanced Energy Materials*. https://doi.org/10.1002/aenm.202405278

22. Yu, K., Niu, Y., Bai, Y., (...), Wang, H. (2013) Poly(vinylidene fluoride) polymer based nanocomposites with significantly reduced energy loss by filling with core-shell structured BaTiO 3/SiO2 nanoparticles. *Applied Physics Letters*. https://doi.org/10.1063/1.4795017

23. He, D., Wang, Y., Chen, X., Deng, Y. (2017) Core–shell structured BaTiO3@Al2O3 nanoparticles in polymer composites for dielectric loss suppression and breakdown strength enhancement. *Composites Part A: Applied Science and Manufacturing*. https://doi.org/10.1016/j.compositesa.2016.11.025

24. Huang, X., Jiang, P. (2015) Core-shell structured high- k polymer nanocomposites for energy storage and dielectric applications. *Advanced Materials*. https://doi.org/10.1002/adma.201401310

25. Zhang, Z., Gu, Y., Bi, J., (...), Zhang, Z. (2016) Tunable BT@SiO2 core@shell filler reinforced polymer composite with high breakdown strength and release energy density. *Composites Part A: Applied Science and Manufacturing*. https://doi.org/10.1016/j.compositesa.2016.03.025

26. Weis, F., Seipenbusch, M., Kasper, G. (2015) Film growth rates and activation energies for core-shell nanoparticles derived from a CVD based aerosol process. *Materials*. https://doi.org/10.3390/ma8030966
27. Weis, Frederik, Seipenbusch, Martin, Kasper, Gerhard (2015) Film Growth Rates and Activation Energies for Core-Shell Nanoparticles Derived from a CVD Based Aerosol Process. *Materials*. https://doi.org/10.3390/ma8030966
28. Jankiewicz, B.J., Jamioła, D., Choma, J., Jaroniec, M. (2012) Silica-metal core-shell nanostructures. *Advances in Colloid and Interface Science*. https://doi.org/10.1016/j.cis.2011.11.002
29. Ding, S., Kong, Y. (2019) Physical Mechanism of Breakdown Failure in Polymer Composites with Various Filler Loading. *ChemistrySelect*. https://doi.org/10.1002/slct.201902422
30. https://www.sciencedirect.com/science/article/pii/S2194146726000010
31. Li, Q., Wang, X., Cao, L., (...), Xiang, H. (2025) Recent advances in the application of nanogenerators in orthopedics: From body surface to implantation. *Nano Energy*. https://doi.org/10.1016/j.nanoen.2024.110542
32. Mohan, B., Najafov, B., Wen, H., (...), Sun, W. (2026) Understanding synergistic bridging of MOFs in mechanical energy harvesting through triboelectric generation. *Journal of Energy Chemistry*. https://doi.org/10.1016/j.jechem.2025.10.004
33. Mukhopadhyay, L., Banerjee, A., Poddar, R., Rai, V.K. (2026) Gold nanoparticles conjugated biocompatible upconverting nanostructures for multimodal OCT imaging. *Applied Surface Science*. https://doi.org/10.1016/j.apsusc.2025.165320
34. Chen, J., Guo, H., He, X., (...), Hu, C. (2016) Enhancing Performance of Triboelectric Nanogenerator by Filling High Dielectric Nanoparticles into Sponge PDMS Film. *ACS Applied Materials and Interfaces*. https://doi.org/10.1021/acsami.5b09907
35. Lim, Y.P., Koay, J.S.C., Zhao, J., (...), Gan, W.C. (2022) Modulating ZnO Growth Structures for Maximum Power Output of Hybrid Piezo/Triboelectric Nanogenerator. *Advanced Functional Materials*. https://doi.org/10.1002/adfm.202206750
36. Han, G.H., Lee, S.U., Park, C.O., (...), Lee, K.H. (2026) Leakage-suppressed MgWO4–PDMS composite triboelectric nanogenerators with an expanded ceramic loading window. *Nano Energy*. https://doi.org/10.1016/j.nanoen.2026.112269
37. Atamna, M., Zinigrad, M., Meshi, L., (...), Sobolev, A. (2026) Hydrothermal silica coatings on aluminum powders: interfacial chemistry, grain refinement, and mechanical response upon sintering. *Journal of Alloys and Compounds*. https://doi.org/10.1016/j.jallcom.2026.188882
38. Cheng, L., Yu, Y., Huang, R., Shi, X. (2021) Lollipop-shaped Co9S8/CdS nanocomposite derived from zeolitic imidazolate framework-67 for the photocatalytic hydrogen production. *International Journal of Hydrogen Energy*. https://doi.org/10.1016/j.ijhydene.2021.07.048

39. Ornelas-Gutiérrez, C., Paraguay-Delgado, F., Lara, J. (2019) Tribological assessment of partially sulfidated molybdenum oxide. *Journal of Materials Research and Technology*. https://doi.org/10.1016/j.jmrt.2019.06.005

40. Chen, Q., Qian, Y.T., Chen, Z.Y., (...), Zhang, Y.H. (1996) Preparation of zinc sulfide thin films by the hydrothermal method. *Thin Solid Films*. https://doi.org/10.1016/0040-6090(95)07073-7

41. Mehr, M.E., Maleki-Ghaleh, H., Yarahmadi, M., (...), Siadati, M.H. (2021) Synthesis and characterization of photocatalytic zinc oxide/titanium oxide (core/shell) nanocomposites. *Journal of Alloys and Compounds*. https://doi.org/10.1016/j.jallcom.2021.160777

42. Wang, H., Yang, J., Zhang, C.M., Lin, J. (2009) Synthesis and characterization of monodisperse spherical SiO2@RE2O3 (RE=rare earth elements) and SiO2@Gd2O3:Ln3+ (Ln=Eu, Tb, Dy, Sm, Er, Ho) particles with core-shell structure. *Journal of Solid State Chemistry*. https://doi.org/10.1016/j.jssc.2009.07.033

43. Yu, B., Liu, Y., Li, Z., (...), Li, G. (2023) Durable substrates incorporated with MOFs: Recent advances in engineering strategies and water treatment applications. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2022.140840

44. Kang, C.W., Lee, D.-M., Park, J., (...), Son, S.U. (2022) Core-Shell ZnO@Microporous Organic Polymer Nanospheres as Enhanced Piezo-Triboelectric Energy Harvesting Materials. *Angewandte Chemie - International Edition*. https://doi.org/10.1002/anie.202209659

45. Zhao, K., Sun, W., Li, S., (...), Chueh, Y.-L. (2023) Rational design on high-performance triboelectric nanogenerator consisting of silicon carbide@silicon dioxide nanowhiskers/polydimethylsiloxane (SiC@SiO2/PDMS) nanocomposite films. *Discover Nano*. https://doi.org/10.1186/s11671-023-03822-8

46. Shyju, S., Chandran, A.M., Varun, S., (...), Mural, P.K.S. (2024) Multifunctional Electrospun Polycaprolactone-Based Nanocomposites for Triboelectric Applications: From Energy Harvesting to IoT-Based Traffic Management and Pedometer Systems. *ACS Applied Electronic Materials*. https://doi.org/10.1021/acsaelm.4c01657

47. Oh, J., Kim, J.-K., Gao, J., (...), Yang, C. (2024) Self-Powering Gas Sensing System Enabled by Double-Layer Triboelectric Nanogenerators Based on Poly(2-vinylpyridine)@BaTiO3 Core-Shell Hybrids with Superior Dispersibility and Uniformity. *ACS Nano*. https://doi.org/10.1021/acsnano.3c12035

48. Ali, A.I., Cho, S., Kamoun, E.A., (...), Choi, D. (2026) Synergistic high-k perovskite BCT/SCT hybridization in PDMS for high-output triboelectric nanogenerators. *Ceramics International*. https://doi.org/10.1016/j.ceramint.2026.03.229

49. Lee, S., Shin, Y.-R., Hwang, G.-I., (...), Jeong, Y.G. (2026) Interfacial polarization engineering in polydimethylsiloxane/boron nitride nanosheet/zinc oxide nanoflower nanocomposites for enhanced piezo-triboelectric performance. *Surfaces and Interfaces*. https://doi.org/10.1016/j.surfin.2026.109740

50. Hossain, M.A., Sarjish, A.M., Rahman, M.W., (...), Uddin, M.J. (2026) The effect of transition metal oxides on the performance of triboelectric nanogenerators. *Communications Materials*. https://doi.org/10.1038/s43246-026-01357-w