Synthesis of SiO2@ZnS-MoS2 core-shell particles

"How can SiO2@ZnS-MoS2 core-shell particles be synthesized?" *Generated by LeapSpace*

SiO2@ZnS-MoS2 particles can be synthesized most plausibly by a two-step core-shell build: first form SiO2 cores, then grow a ZnS shell, and finally add MoS2 as an outer layer or secondary shell using hydrothermal, thermal decomposition, or templated shell-growth routes. The retrieved evidence directly supports SiO2@ZnS synthesis, MoS2 shell growth on other cores, and generic core-shell shelling strategies; it does not show a single paper that exactly reports SiO2@ZnS-MoS2 in one step [80] [81] [82] [83].

Practical synthesis routes

Route	How it would work for SiO2@ZnS-MoS2	What the evidence supports
Stöber + shell growth	Make **monodisperse SiO2 spheres** by Stöber hydrolysis/condensation, then grow a **ZnS shell** by precursor deposition, and add **MoS2** by a final hydrothermal sulfidation or layered growth step [84] [85] [86]	SiO2 cores are commonly made by Stöber-style methods, and silica-core shelling is widely used [84] [85] [86] [87]
Thermal decomposition / shell conversion	Coat SiO2 with a ZnS shell by thermal decomposition or analogous precursor conversion, then deposit or grow MoS2 on top [80]	**SiO2@ZnS** was made by **thermal decomposition**; XRD showed **cubic ZnS** and **amorphous SiO2** [80]
Hydrothermal MoS2 overlayer	Use SiO2@ZnS as the starting particle and grow MoS2 hydrothermally from molybdate + sulfur precursors to form a layered outer shell [81] [82] [88]	MoS2 shells/nanoflowers are readily formed by **hydrothermal reactions** on preformed cores [81] [82] [88] [89]
Template-assisted / sacrificial route	Build a core-shell intermediate, then selectively remove or transform an inner or intermediate layer if a **yolk-shell** or hollow variant is desired [83] [90]	Silica-templated ZnS and ZnS@MoS2-to-hollow-MoS2 conversions are documented [83] [90]

Most supportable stepwise design

1. **Prepare amorphous SiO2 cores** by a Stöber-type hydrolysis/condensation route or a closely related silica-template method [84] [85] [86] [87].

2. **Deposit ZnS onto SiO2** using a shell-growth route such as thermal decomposition, precursor conversion, or a solution-based deposition method; SiO2@ZnS was explicitly obtained with **mesoporous SiO2 core + ZnS shell** and **cubic ZnS** [80].
3. **Grow MoS2 as the outer shell** by hydrothermal treatment from molybdate and sulfur precursors; hydrothermal growth is the clearest route in the retrieved evidence for forming layered MoS2 architectures on pre-existing particles [81] [82] [88].
4. **Control shell thickness and morphology** by precursor concentration, reaction time, and surface chemistry; the evidence shows shell thickness is tunable in silica-based shell systems and MoS2 interfacial growth depends strongly on hydrothermal conditions [86] [91] [92].

What phase choices are usable

- **SiO2 core: amorphous SiO2** is the practical and directly supported form for core-shell synthesis [80] [84].
- **ZnS shell: cubic ZnS** is directly demonstrated in SiO2@ZnS particles, and ZnS shells are also synthesizable by shell-growth methods [80] [93].
- **MoS2 shell: layered crystalline MoS2**, often formed as nanosheets or flower-like assemblies, is the usable shell phase [81] [82] [89].

Bottom line

The **most defensible synthesis strategy** is **SiO2 core fabrication → ZnS shell growth → outer MoS2 hydrothermal shelling**, because each step is individually supported by retrieved core-shell precedents, even though the exact three-component sequence is not directly reported in one study [53] [80] [81] [83].

Confidence level: Medium — the individual synthesis steps are well supported by directly relevant core-shell examples, but the exact SiO2@ZnS-MoS2 combination itself is inferred from adjacent systems rather than directly demonstrated.

References

53. Mahajan, J., Jeevanandam, P. (2021) A facile thermal decomposition approach for the synthesis of SiO2@ZnS core-shell nanoparticles and their application as effective adsorbent for the removal of congo red. *Materials Today Communications*. https://doi.org/10.1016/j.mtcomm.2021.102085

80. Mahajan, J., Jeevanandam, P. (2021) A facile thermal decomposition approach for the synthesis of SiO2@ZnS core-shell nanoparticles and their application as effective adsorbent for the removal of congo red. *Materials Today Communications*. https://doi.org/10.1016/j.mtcomm.2021.102085

81. Guo, K., Shao, X., Chen, M., (...), Wang, L. (2026) Temperature-dependent tribological mechanisms of MoS2@SiO2 core-shell lubricants from 200 to 800 ℃: Experiments and molecular dynamics. *Results in Engineering*. https://doi.org/10.1016/j.rineng.2026.112693

82. Guo, S., Zhang, Y., Tang, S., (...), Li, X. (2021) Tuning interlayer spacing of MoS2 for enhanced hydrogen evolution reaction. *Journal of Alloys and Compounds*. https://doi.org/10.1016/j.jallcom.2020.158581

83. Li, C., Li, J., Wang, Z., (...), An, C. (2017) The synthesis of hollow MoS2 nanospheres assembled by ultrathin nanosheets for an enhanced energy storage performance. *Inorganic Chemistry Frontiers*. https://doi.org/10.1039/c6qi00502k

84. Kong, D.Y., Yu, M., Lin, C.K., (...), Fang, J. (2005) Sol-gel synthesis and characterization of Zn2SiO 4:Mn@SiO2 spherical core-shell particles. *Journal of the Electrochemical Society*. https://doi.org/10.1149/1.1990612

85. Yang, Pingan, Ye, Wenxian, Ruan, Haibo, (...), Luo, Jiufei (2023) Core–Shell Structured Silica-Coated Iron Nanowires Composites for Enhanced Electromagnetic Wave Absorption Properties. *International Journal of Molecular Sciences*. https://doi.org/10.3390/ijms24108620

86. Ferreira, V.R.A., Azenha, M.A., Pereira, C.M., Silva, A.F. (2021) Preparation of molecularly imprinted hollow TiO2 microspheres for selective photocatalysis. *Chemical Engineering Journal Advances*. https://doi.org/10.1016/j.ceja.2020.100071

87. Daware, K., Kasture, M., Kalubarme, R., (...), Fujishima, A. (2019) Detection of toxic metal ions Pb2+ in water using SiO2@Au core-shell nanostructures: A simple technique for water quality monitoring. *Chemical Physics Letters*. https://doi.org/10.1016/j.cplett.2019.136635

88. Manimekalai, A., Sakthi Velu, K.S., Sonaimuthu, S., Sun, S. (2025) Enhancing photovoltaic performance of flower-like MoS2@ZnO core-shell nanowire photoanodes: Synergistic effects on solar energy conversion. *Current Applied Physics*. https://doi.org/10.1016/j.cap.2025.05.003

89. Qin, Z., Wang, C., Ma, Y., (...), Zhang, P. (2021) MoS2Nanoflowers Decorated with Fe3O4/Graphite Nanosheets for Controllable Electromagnetic Wave Absorption. *ACS Applied Nano Materials*. https://doi.org/10.1021/acsanm.0c03328

90. Zhao, Y., Shi, W., Gong, M., (...), Chen, T. (2005) A γ-ray irradiation route to fabricate monodisperse zinc sulfide hollow spheres using silica as templates. *Materials Chemistry and Physics*. https://doi.org/10.1016/j.matchemphys.2005.04.052

91. Li, J., Zhang, H.-F., Shi, Y.-P. (2011) In-situ synthesis and normal chromatographic properties of nonporous SiO 2 /ZrO 2 core-shell composite microspheres. *Analytical Sciences*. https://doi.org/10.2116/analsci.27.447

92. Kaja, S., Mukherjee, A., Chakravarty, M., Nag, A. (2022) Identifying high performance photosensitizer with simultaneous enhancement in fluorescence and singlet oxygen generation, from '(Ag/Au)-aggregation-induced emission-active fluorogen' theranostic nanoparticles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. https://doi.org/10.1016/j.colsurfa.2022.129448

93. Vaidya, S., Patra, A., Ganguli, A.K. (2010) CdS@TiO2 and ZnS@TiO2 core-shell nanocomposites: Synthesis and optical properties. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. https://doi.org/10.1016/j.colsurfa.2010.04.030