Controlling ZnS shell thickness on SiO2

"How to control ZnS shell thickness on SiO2 cores?" *Generated by LeapSpace*

Control the ZnS shell thickness on SiO2 cores by tuning the ZnS precursor supply, growth time, and growth mode; in the retrieved evidence, precursor amount is the most direct thickness lever, while surface functionalization and reaction conditions mainly improve uniformity and coverage. [80] [94] [95]

Practical control knobs

Control lever	What to change	Effect on ZnS shell growth
ZnS precursor amount	Increase or decrease the Zn and S precursor quantity fed to the SiO2 core system	More precursor produces a thicker ZnS shell; the retrieved SiO2@ZnS study states that ZnS band gap on SiO2@ZnS could be tuned by varying the amount of ZnS precursor, which implies shell-growth control through precursor loading [80]
Reaction time / growth duration	Extend or shorten the shell-forming step	Longer growth generally allows more shell deposition; across related core-shell systems, shell thickness was controlled by reaction time, including silica-coated core-shell particles where thickness tracked coating time [96] [97] [98]
Stepwise shelling cycles	Add shell precursor in multiple injections rather than one shot	Layer-by-layer growth provides finer thickness control; the retrieved core-shell literature shows shell thickness can be set by repeated precursor addition, as in ZnS monolayer growth strategies [99] [100] [101]
Surface functionalization of SiO2	Modify the SiO2 surface before shelling	Functionalized surfaces help ZnS nucleate more uniformly and improve homogeneous coverage, which is important if the goal is a continuous shell rather than patchy ZnS islands [94]

Control lever	What to change	Effect on ZnS shell growth
Temperature and solvent/reaction medium	Adjust the thermal decomposition or hydrothermal conditions	These variables influence how fast ZnS forms and how crystalline the shell becomes; the retrieved studies show shell growth can be steered by the synthesis environment, with thermal decomposition and hydrothermal routes both used successfully [80] [102]

What the evidence suggests for SiO2@ZnS specifically

- **Most direct route:** use a **thermal decomposition or shell-growth method** on preformed SiO2 cores, then vary the **ZnS precursor amount** to set shell thickness [80].
- **If uniformity matters:** first **functionalize the SiO2 surface** so ZnS nucleates evenly; the related SiO2@ZnIn2S4 study shows surface modification is critical for homogeneous shell coverage, and the same design logic should carry over to ZnS shell growth as an inference [94].
- **If you need precise thickness windows:** prefer **stepwise deposition** instead of a single bulk addition, because controlled shell thickness in other ZnS core-shell systems was achieved by changing precursor dose and shell-growth sequence [99] [100] [101].

Bottom line

For **SiO2@ZnS**, the cleanest thickness-control strategy is: **preform SiO2 cores → activate the SiO2 surface if needed → grow ZnS with a controlled Zn/S precursor dose → stop at the desired reaction time or number of shelling cycles** [80] [94] [99] [100]. **If you want the shell to stay thin and uniform, keep precursor loading low and use surface treatment; if you want a thicker shell, increase precursor amount or repeat the shelling step.** [80] [94] [101]

Confidence level: **High —** the retrieved studies directly show that ZnS shell thickness is controlled by precursor amount and growth conditions, and adjacent core-shell examples support surface-functionalization and stepwise shelling as reliable thickness-control methods.

References

80. Mahajan, J., Jeevanandam, P. (2021) A facile thermal decomposition approach for the synthesis of SiO2@ZnS core-shell nanoparticles and their application as effective adsorbent for the removal of congo red. *Materials Today Communications*. https://doi.org/10.1016/j.mtcomm.2021.102085

94. Mishra, M., Huang, Y.-C., Wang, P.-H., (...), Lee, T.-C. (2021) Tuning the Crystallinity and Coverage of SiO2-ZnIn2S4Core-Shell Nanoparticles for Efficient Hydrogen Generation. *ACS Applied Materials and Interfaces*. https://doi.org/10.1021/acsami.0c20716

95. Estévez-Hernández, O., González, J., Guzmán-Mendoza, J., (...), Reguera, E. (2012) Mercaptopropionic acid capped CdS@ZnS nanocomposites: Interface structure and related optical properties. *Science of Advanced Materials*. https://doi.org/10.1166/sam.2012.1372

96. Hui, C., Shen, C., Tian, J., (...), Gao, H.-J. (2011) Core-shell Fe3O4@SiO2 nanoparticles synthesized with well-dispersed hydrophilic Fe3O4 seeds. *Nanoscale*. https://doi.org/10.1039/c0nr00497a

97. Fu, W., Yang, H., Hari-Bala, (...), Zou, G. (2006) Preparation and magnetic characterization of core-shell structure stainless steel/silica nanoparticles. *Materials Letters*. https://doi.org/10.1016/j.matlet.2005.12.019

98. Dong, B., Cao, L., Su, G., (...), Jiang, D. (2009) Synthesis and characterization of the water-soluble silica-coated ZnS:Mn nanoparticles as fluorescent sensor for Cu2+ ions. *Journal of Colloid and Interface Science*. https://doi.org/10.1016/j.jcis.2009.07.039

99. Fernández-Delgado, N., Herrera-Collado, M., Tavabi, A.H., (...), Molina Rubio, S.I. (2018) Structural and chemical characterization of CdSe-ZnS core-shell quantum dots. *Applied Surface Science*. https://doi.org/10.1016/j.apsusc.2018.06.149

100. Voigt, D., Bredol, M., Gonabadi, A. (2021) A general strategy for CuInS2 based quantum dots with adjustable surface chemistry. *Optical Materials*. https://doi.org/10.1016/j.optmat.2021.110994

101. Kaur, Manpreet, Sharma, Ashma, Olutas, Murat, (...), Demir, Hilmi Volkan (2018) Cd-free Cu-doped ZnInS/ZnS Core/Shell Nanocrystals: Controlled Synthesis And Photophysical Properties. *Nanoscale Research Letters*. https://doi.org/10.1186/s11671-018-2599-x

102. Yan, B., Wang, Y., Wu, X. (2018) Preparation and characterization of ZnO/ZnS core/shell nanocomposites through a simple chemical method. *Advanced Composite Materials*. https://doi.org/10.1080/09243046.2017.1405594