Synthesis of MoS2 on SiO2@ZnS particles

"How to grow MoS2 on ZnS-coated silica particles?" *Generated by LeapSpace*

Grow MoS_2 on ZnS-coated silica particles by using the ZnS shell as the nucleation surface and then depositing MoS_2 as a second shell, with the most supportable route being a two-step solution/hydrothermal process rather than direct high-temperature CVD on the powder. The retrieved evidence supports three practical ways to do this: **(1) hydrothermal shell growth**, **(2) solvothermal conversion/deposition of Mo–S species onto ZnS**, and **(3) a ZnS-first, MoS_2-second template route that can later be converted into hollow or open MoS_2 if desired** [83] [103] [104] [105].

Most practical route

Step	What to do	Why it works
1. Start with SiO_2@ZnS particles	Use preformed **ZnS-coated silica** as the core template	SiO_2@ZnS is already a demonstrated core-shell platform, with **amorphous SiO_2** and **cubic ZnS** reported in one synthesis route [80] [106]
2. Add Mo source + sulfur source in solution	Expose the ZnS-coated particles to **molybdate/Mo precursor + sulfur** under **hydrothermal or solvothermal** conditions	ZnS/MoS_2 heterostructures and **ZnS@MoS_2** core-shell nanospheres are formed this way; MoS_2 can wrap the outer surface through solution growth [83] [107]
3. Use the ZnS surface as a nucleation scaffold	Keep the particles dispersed so MoS_2 grows on the outside rather than aggregating	The evidence shows MoS_2 morphology and coverage depend strongly on the **substrate/surface**, and hydrothermal time controls how much MoS_2 forms [105] [108]
4. Tune reaction time and precursor ratio	Short time / lower Mo loading for a thin shell; longer time / higher loading for thicker coverage	MoS_2 layer number, defect density, and coverage are all sensitive to growth conditions, and ZnS@MoS_2 → hollow MoS_2 transformations show the shell can be controlled by chemistry and post-treatment [83] [103] [105]

Best-supported synthesis options

1) Hydrothermal overgrowth on ZnS-coated silica

This is the closest match to your target. A related study made **ZnS@MoS_2 core-shell nanospheres by a nanotemplate-assisted hydrothermal method**, then removed ZnS to obtain hollow MoS_2 [83]. Another report formed **ZnS/MoS_2 heterostructures** by one-pot solvothermal synthesis, showing the two phases can coexist and couple productively [107].
Inference: if your goal is to keep the SiO_2@ZnS particle intact, stop after the MoS_2 overgrowth step instead of etching the ZnS away [83] [107].

2) Stepwise shelling: ZnS shell first, MoS_2 shell second

The retrieved core-shell literature supports stepwise shelling as a general strategy for controlled outer-layer formation [109] [110]. For MoS_2, a two-step route is especially plausible because MoS_2 can be grown as an outer layer on pre-existing structures, including **Sb_2S_3@MoS_2** via hydrothermal processing and **ZnO/ZnS/MoS_2** via sequential reaction steps [104] [111].
Inference: for SiO_2@ZnS, this translates to **preform ZnS on SiO_2, then introduce Mo precursor + sulfur to grow MoS_2 onto the ZnS surface** [104] [111].

3) Convert a Mo-rich layer into crystalline MoS_2

A ZnS-seeded solution route produced **amorphous MoSx/ZnS**, which converted on heating into **crystalline MoS_2** [103]. That suggests a possible pathway if you first form a Mo–S-rich outer layer on ZnS-coated silica and then crystallize it by annealing.
Inference: this route may help if you want a **denser or more crystalline MoS_2 shell**, but it is less gentle than direct hydrothermal growth and may disturb the silica/ZnS interface [103].

What conditions matter most

- **Surface chemistry matters:** MoS_2 growth depends strongly on the starting surface, and substrate treatment changes morphology and coverage in CVD-grown MoS_2 [112] [113].
- **Time and temperature matter:** hydrothermal MoS_2 growth is time-dependent, and longer growth generally increases coverage or layer density [105] [108].
- **Precursor ratio matters:** in ZnS/MoS_2-derived systems, changing the Mo/Zn ratio changes shell thickness and the final MoS_2 wall structure [103].
- **If you need particle integrity, avoid full ZnS removal:** one cited route intentionally etched ZnS to make hollow MoS_2, so that should be avoided if the SiO_2@ZnS architecture is the goal [83].

Bottom line

The **most defensible method** is: **prepare SiO_2@ZnS particles, disperse them in a hydrothermal/solvothermal Mo precursor + sulfur system, and grow MoS_2 as the outer shell while tuning Mo loading, temperature, and reaction time** [83] [107] [108]. This is supported by adjacent ZnS@MoS_2 and ZnS/MoS_2 core-shell systems, even though the exact **SiO_2@ZnS@MoS_2** sequence is not directly reported in the retrieved evidence [103] [104] [111].

Confidence level: **Medium —** the growth logic is strongly supported by closely related ZnS/MoS_2 and core-shell precedents, but the exact three-component particle has not been directly demonstrated in the retrieved sources [83] [103] [111].

References

80. Mahajan, J., Jeevanandam, P. (2021) A facile thermal decomposition approach for the synthesis of SiO2@ZnS core-shell nanoparticles and their application as effective adsorbent for the removal of congo red. *Materials Today Communications*. https://doi.org/10.1016/j.mtcomm.2021.102085

83. Li, C., Li, J., Wang, Z., (...), An, C. (2017) The synthesis of hollow MoS2 nanospheres assembled by ultrathin nanosheets for an enhanced energy storage performance. *Inorganic Chemistry Frontiers*. https://doi.org/10.1039/c6qi00502k

103. Blanco, E., Uzio, D., Berhault, G., Afanasiev, P. (2014) From core-shell MoSx/ZnS to open fullerene-like MoS2 nanoparticles. *Journal of Materials Chemistry A*. https://doi.org/10.1039/c3ta14888b

104. Xu, M., Zhao, J. (2018) Facile Synthesis of 1D/2D Core–Shell Structured Sb2S3@MoS2 Nanorods with Enhanced Photocatalytic Performance. *Electronic Materials Letters*. https://doi.org/10.1007/s13391-018-0050-1

105. Sahatiya, Parikshit, Jones, S Solomon, Badhulika, Sushmee (2018) *Flexible and Printed Electronics*. https://doi.org/10.1088/2058-8585/aaa4a5

106. Sana, P., Verma, S., Malik, M.M. (2015) Optical and structural investigations of manganese doped ZnS/SiO2 core-shell nanostructure. *International Journal of Nanoscience*. https://doi.org/10.1142/S0219581X15500064

107. Shah, Sayyar Ali, Khan, Iltaf, Yuan, Aihua (2022) *Molecules*. https://doi.org/10.3390/molecules27103289

108. Liu, X., Ding, W., Wang, G., (...), Wei, C. (2026) Nitrogen-regulated d-p orbital interaction in MoS2@Porous carbon nanofiber interlayers for accelerated sulfur redox kinetics in lithium-sulfur batteries. *Carbon*. https://doi.org/10.1016/j.carbon.2026.122012

109. Zhu, C.-Q., Wang, P., Wang, X., Li, Y. (2008) Facile phosphine-free synthesis of CdSe/ZnS core/shell nanocrystals without precursor injection. *Nanoscale Research Letters*. https://doi.org/10.1007/s11671-008-9139-z

110. Karimipour, M., Bagheri, M., Johansson, E.M.J., Molaei, M. (2018) Excellent growth of ZnS shell on Ag2S QDs using a photochemical-microwave irradiation approach and fabrication of their indoor QD thin film solar cells. *Materials Technology*. https://doi.org/10.1080/10667857.2018.1503781

111. Butanovs, E., Kuzmin, A., Butikova, J., (...), Polyakov, B. (2017) Synthesis and characterization of ZnO/ZnS/MoS2 core-shell nanowires. *Journal of Crystal Growth*. https://doi.org/10.1016/j.jcrysgro.2016.11.106

112. https://www.sciencedirect.com/science/article/pii/S1573480319001657

113. Rosman, Nurul Nabila, Mohamad Yunus, Rozan, Jeffery Minggu, Lorna, (...), Mohamed, Mohd Ambri (2020) *Nanotechnology*. https://doi.org/10.1088/1361-6528/abbea9