Core-shell structure optimization for SiO2/MoS2/ZnS

"SiO2/MoS2-ZnS does have an optimum situation for core shell structure?" *Generated by LeapSpace*

Yes — **an optimum SiO_2/MoS_2-ZnS core-shell arrangement is plausible, but it is not universal; it depends on which phase is the core, which is the outer shell, and what property you want to maximize** [80] [81] [130] [131] [132]. The evidence supports an **intermediate shell-thickness regime** rather than "as thin as possible" or "as thick as possible," because both extremes can hurt performance in core-shell systems [80] [134] [135] [136] [137] [138] [139] [140] [141] [142] [143] [144] [145].

What "optimum" looks like

Design variable	What the evidence suggests	Practical implication
Shell thickness	An **intermediate thickness** is often best; too thin can leave the shell incomplete, while too thick can add strain, defects, recombination, or quenching [134] [136] [138] [140] [141] [142] [145]	Optimize thickness rather than maximizing it
Core/shell order	**SiO_2@ZnS** is directly demonstrated, **MoS_2@SiO_2** is directly demonstrated, and **MoS_2 shell growth on other cores** is established [80] [81] [129] [131] [132]	The most defensible SiO_2-based designs are the direct pairings, or a sequential shell architecture
MoS_2 layer character	MoS_2 is most useful as a **thin, conformal, crystalline layered shell** rather than a thick, aggregated deposit [104] [131] [146] [147]	Favor continuous shell coverage and good interfacial contact
ZnS layer character	ZnS works well as a **moderate-thickness crystalline shell**; thicker shells can improve passivation, but overgrowth can introduce strain or reduced efficiency [80] [136] [140] [141] [145] [148]	Keep ZnS continuous but avoid excessive thickness

For your specific architecture

- If you mean **SiO_2 core with ZnS shell and MoS_2 outer layer**, the retrieved evidence most strongly supports a **stepwise architecture** with a **continuous ZnS interlayer/shell** and a **thin MoS_2 outer shell** rather than a very thick MoS_2 coating [80] [131] [132].

- If you mean **SiO_2/MoS_2 with ZnS as the outer shell**, the same optimization logic applies: a **MoS_2 layer that is conformal and not overly thick** plus a **ZnS outer layer thick enough for passivation but not so thick that strain/defects dominate** [81] [140] [142] [144].
- The clearest general rule from the evidence is that **optimum performance comes from balancing interface quality, charge/transport or barrier effects, and structural stress** [131] [135] [136] [139] [143] [144].

Bottom line

Yes, there can be an optimum configuration for SiO_2/MoS_2-ZnS core-shell systems, but it is usually an intermediate-thickness, well-adhered, conformal shell architecture rather than a maximally thick one [80] [131] [132] [134] [135] [136] [140] [142]. For a practical design, the safest target is **continuous SiO_2-based cores with controlled ZnS and MoS_2 shell thicknesses tuned to avoid strain, trap states, and incomplete coverage** [80] [131] [138] [141].

Confidence level: Medium — the evidence strongly supports thickness-dependent optimization in closely related core-shell systems, but the exact SiO_2/MoS_2-ZnS pairing has not been directly benchmarked as a single optimized platform.

References

80. Mahajan, J., Jeevanandam, P. (2021) A facile thermal decomposition approach for the synthesis of SiO2@ZnS core-shell nanoparticles and their application as effective adsorbent for the removal of congo red. *Materials Today Communications*. https://doi.org/10.1016/j.mtcomm.2021.102085

81. Guo, K., Shao, X., Chen, M., (...), Wang, L. (2026) Temperature-dependent tribological mechanisms of MoS2@SiO2 core-shell lubricants from 200 to 800 ℃: Experiments and molecular dynamics. *Results in Engineering*. https://doi.org/10.1016/j.rineng.2026.112693

104. Xu, M., Zhao, J. (2018) Facile Synthesis of 1D/2D Core–Shell Structured Sb2S3@MoS2 Nanorods with Enhanced Photocatalytic Performance. *Electronic Materials Letters*. https://doi.org/10.1007/s13391-018-0050-1

129. Sun, W., Xi, Z., Zheng, H., (...), Hao, C. (2021) Synthesis and electrorheological properties of silica-coated MoS2 nanocomposites with hierarchical and core-shell structure. *Journal of the Taiwan Institute of Chemical Engineers*. https://doi.org/10.1016/j.jtice.2021.01.009

130. Liu, S., Li, S., Sekar, K., (...), Fujishima, A. (2019) Hierarchical ZnS@C@MoS2 core-shell nanostructures as efficient hydrogen evolution electrocatalyst for alkaline water electrolysis. *International Journal of Hydrogen Energy*. https://doi.org/10.1016/j.ijhydene.2019.08.048

131. Butanovs, E., Kuzmin, A., Zolotarjovs, A., (...), Polyakov, B. (2022) The role of Al2O3 interlayer in the synthesis of ZnS/Al2O3/MoS2 core-shell nanowires. *Journal of Alloys and Compounds*. https://doi.org/10.1016/j.jallcom.2022.165648

132. Joy, M., Mohamed, A.P., Warrier, K.G.K., Hareesh, U.S. (2017) Visible-light-driven photocatalytic properties of binary MoS2/ZnS heterostructured nanojunctions synthesized via one-step hydrothermal route. *New Journal of Chemistry*. https://doi.org/10.1039/c6nj03727e

134. Luo, Y., Gao, J., Fan, Z., (...), Zhu, X. (2025) Synthesis and luminescent properties of multi-mode core-shell-shell LaPO4:RE (RE^{3+} = Er^{3+}, Eu^{3+}) microspheres for anti-counterfeiting ink applications. *Ceramics International*. https://doi.org/10.1016/j.ceramint.2024.10.221

135. Liu, X., Tang, Z., Zhao, S., (...), Deng, H. (2026) Hierarchically porous microstructure composite coatings with core–shell scattering units for high–performance radiative cooling. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.176524

136. https://www.sciencedirect.com/science/article/pii/S1520512626004735

137. Du, L., Li, R., Chen, W. (2023) Colored textiles based on noniridescent structural color of ZnS@SiO2 colloidal crystals for daytime passive radiative cooling. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2023.146431

138. Han, J., Liu, Z., Yadian, B., (...), Cui, T. (2014) Synthesis of metal sulfide sensitized zinc oxide-based core/shell/shell nanorods and their photoelectrochemical properties. *Journal of Power Sources*. https://doi.org/10.1016/j.jpowsour.2014.06.060

139. Sun, Y.-H., Yang, Z.-M., Xie, C.-N., Jiang, Z.-H. (2012) Preparation and characteristics of core-shell structure Y 3Al 5O 12:Yb 3+@SiO 2 nanoparticles. *Journal of Alloys and Compounds*. https://doi.org/10.1016/j.jallcom.2012.02.105

140. Chen, Yuhang, Xue, Qi, Luo, Weiguo, (...), Hang, Tao (2023) ZnO/ZnS core–shell quantum dots with enhanced ultraviolet fluorescence and low cytotoxicity for cell imaging. *Nanotechnology*. https://doi.org/10.1088/1361-6528/acfa06

141. https://www.sciencedirect.com/science/article/pii/S1573482X19001899

142. Lee, S.-H., Song, S.-W., Yoon, S.-Y., (...), Yang, H. (2022) Heterostructural tailoring of blue ZnSeTe quantum dots toward high-color purity and high-efficiency electroluminescence. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2021.132464

143. Taha, M., Al Kiey, S.A., Khalid, A., (...), Abdallah, S. (2026) Engineering the ZnO/SiO2 Interface for tunable optoelectronic and charge transport properties in Core–Shell nanostructures. *Materials Science and Engineering: B*. https://doi.org/10.1016/j.mseb.2026.119671

144. Chen, Z., Cummins, D., Reinecke, B.N., (...), Jaramillo, T.F. (2011) Core-shell MoO3-MoS2 nanowires for hydrogen evolution: A functional design for electrocatalytic materials. *Nano Letters*. https://doi.org/10.1021/nl2020476

145. Li, X., Shi, Z., Liu, J., Wang, J. (2019) Shell thickness dependent photocatalytic activity of TiO2/ZnS core-shell nanorod arrays. *Materials Research Express*. https://doi.org/10.1088/2053-1591/ab62fe

146. DiStefano, J.G., Li, Y., Jung, H.J., (...), Dravid, V.P. (2018) Nanoparticle@MoS2 Core-Shell Architecture: Role of the Core Material. *Chemistry of Materials*. https://doi.org/10.1021/acs.chemmater.8b01333

147. Pan, J., Liu, Y., Ou, W., (...), Li, C. (2020) The photocatalytic hydrogen evolution enhancement of the MoS2 lamellas modified g-C3N4/SrTiO3 core-shell heterojunction. *Renewable Energy*. https://doi.org/10.1016/j.renene.2020.07.097

148. Tsai, Y.-S., Chou, T.-W., Xu, C.Y., (...), Chen, H. (2019) ZnO/ZnS core-shell nanostructures for hydrogen gas sensing performances. *Ceramics International*. https://doi.org/10.1016/j.ceramint.2019.05.345