Silicon dioxide and Molybdenum disulfide in Triboelectric Nanogenerators

"How SiO2 and MoS2 can be used simultaneously at TENG for improvement its efficiency?" *Generated by LeapSpace*

SiO2-MoS2 Hybridization in TENGs at a Glance

Key Findings Table

Key finding	What it means for simultaneous SiO2 + MoS2 use in TENGs	Relevant material/device context	Citations
MoS2 improves charge trapping, surface roughness, charge transfer, and dielectric behavior	MoS2 is the tribo-active component that can raise generated and stored charge	MoS2-polymer composites in Ecoflex, RTV/PVC, PAN, PVDF, and PCL	[1] [2] [3] [4] [5]
SiO2-decorated MoS2 can increase dielectric constant and breakdown strength while suppressing leakage	This is the clearest mechanistic route for using both materials together	PVDF-based composite with internally decorated MoS2 flowers	[6] [7]
A specific SiO2-MoS2 hybrid filler reached dielectric constant 10.8 at 1 kHz and breakdown strength 486.8 MV/m at 1 wt% loading	Hybrid fillers can improve charge storage conditions relevant to TENG efficiency	PVDF-based composite dielectric filler study	[7]
SiO2 acts as an insulating barrier around/with MoS2	The SiO2 role is mainly charge retention: reduced carrier transport and leakage	SiO2-decorated MoS2 fillers; broader composite-dielectric rationale	[6] [7] [8] [9] [10]
MoS2-encapsulated SiO2 improves humidity robustness	Combined structures may improve not only efficiency but also stability in moist environments	Core-shell tribomaterial TENG	[11]
A MoS2-encapsulated SiO2 TENG retained >70% output after 25 h at 99% RH	Environmental stability is a concrete advantage of combined use	Humidity-tolerant TENG powering gas sensor array	[11]

Key finding	What it means for simultaneous SiO2 + MoS2 use in TENGs	Relevant material/device context	Citations
Direct head-to-head TENG benchmarking for pristine vs SiO2-only vs MoS2-only vs SiO2+MoS2 is still sparse	The design idea is well supported mechanistically, but device-level proof is incomplete	Across retrieved TENG literature	[7] [12] [13] [14]

Direct Answer

SiO2 and MoS2 can be used simultaneously in a TENG most plausibly as a **hybrid filler or core-shell tribomaterial** inside the active triboelectric layer: use **MoS2 as the charge-trapping, tribo-active, interfacial-polarization component**, and use **SiO2 as the insulating shell/decorator/barrier** that suppresses carrier transport, reduces charge leakage, and helps retain tribocharges [6] [7] [11].

A practical configuration supported by the evidence is:

1. **Prepare a SiO2-MoS2 hybrid**, such as **SiO2-decorated MoS2 flowers** or **MoS2-encapsulated SiO2 nanoparticles** [7] [11].
2. **Disperse that hybrid at low loading in a tribonegative polymer matrix**, especially a **PVDF-based matrix**, to raise dielectric constant and breakdown strength while maintaining charge retention [7].
3. **Exploit MoS2 for charge trapping and interfacial polarization**, which can also improve triboelectric activity and, in some PVDF systems, polarity/β-phase-related behavior [1] [4].
4. **Exploit SiO2 to block leakage and moisture-assisted charge decay**, improving operational stability, especially in humid conditions [6] [11].

So, if the goal is to improve TENG efficiency, the best-supported answer is: **combine SiO2 and MoS2 as a hybrid dielectric/triboelectric filler system rather than as two separate random additives** [6] [7].

Important caveat: the retrieved evidence strongly supports this mechanism, but provides only limited direct, fully benchmarked TENG comparisons against pristine, SiO2-only, and MoS2-only controls under identical conditions [12] [13] [14].

Confidence level: High for the mechanistic recommendation; Medium for exact device-level performance gains because direct comparative TENG evidence is limited [7] [12] [13].

Study Scope

- **Time/maturity scope:** foundational TENG theory plus later composite-material and flexible/wearable TENG studies represented in the supplied evidence set [15] [16] [17] [18].
- **Disciplines covered:** triboelectric nanogenerators, polymer composites, dielectric engineering, interface engineering, flexible electronics, and self-powered sensing [8] [9] [11].

- **Methods/evidence types:** mechanistic composite studies, device output reports, humidity-stability demonstrations, and wearable/flexible architecture studies [7] [11] [12] [13] [19].

Assumptions & Limitations

- The evidence base is **stronger for mechanism than for direct TENG benchmarking** of simultaneous SiO2+MoS2 use [7] [12] [13].
- No retrieved paper fully establishes a complete comparison matrix of **pristine vs SiO2-only vs MoS2-only vs SiO2+MoS2** under identical TENG test conditions [12] [13] [14].
- Exact optimum loading, morphology, and operating mode for combined SiO2-MoS2 TENGs cannot be robustly extracted from the provided evidence [14] [19] [20].

Suggested Further Research

- Run standardized head-to-head TENG comparisons of **pristine, SiO2-only, MoS2-only, and SiO2+MoS2** tribolayers under the same contact mode and load conditions [12] [13].
- Compare **SiO2-decorated MoS2** versus **MoS2-encapsulated SiO2** to determine which better balances output and humidity stability [7] [11].
- Optimize **low filler loading** and dispersion quality in PVDF-based flexible matrices [7].
- Combine hybrid fillers with **surface micro/nanostructuring** to test additive gains from surface engineering plus dielectric engineering [8] [21] [22].
- Evaluate long-term bending, washability, and high-humidity cycling for wearable formats [11] [18] [23] [24].

Full Report

Introduction

The main reason to combine SiO2 and MoS2 in a triboelectric nanogenerator (TENG) is that they appear to provide **complementary functions** rather than redundant ones. Across the supplied evidence, **MoS2** is associated with charge trapping, surface roughness enhancement, improved charge transfer, and better dielectric behavior in polymer composites, while **SiO2** contributes insulating behavior that can suppress carrier transport and reduce charge leakage [1] [2] [3] [4] [5] [6]. Taken together, these findings suggest that a **SiO2-MoS2 hybrid tribolayer** could improve TENG efficiency by increasing both **charge generation** and **charge retention** [6] [7].

The strongest direct support for this concept comes from a PVDF-based composite study in which **SiO2-decorated MoS2 flowers** increased dielectric constant and breakdown strength through interfacial polarization plus leakage suppression [7]. A separate line of evidence shows that **MoS2-encapsulated SiO2 nanoparticles** can stabilize TENG output in very high humidity, indicating that combined use may also address environmental losses that often limit practical efficiency [11].

However, the literature retrieved here is unbalanced: the **mechanistic case is strong**, but the number of studies directly reporting full TENG output metrics for simultaneous SiO2-MoS2 devices is limited [7] [12] [13] [14].

Confidence level: High - multiple supplied findings consistently support the complementary-function rationale [6] [7] [11].

Foundational Context: How TENG Efficiency Is Improved

TENG operation is grounded in **contact electrification** and **electrostatic induction**, with output behavior often framed using the **V-Q-x theoretical basis** established in foundational work [15] [16] [17] [25]. In practical terms, TENG efficiency improves when a device can do three things well:

1. **Generate more tribocharges at contact**,
2. **Store more of those charges without premature recombination or leakage**, and
3. **Maintain those charges over repeated cycles and environmental exposure** [8] [9] [26].

Two broad design strategies recur in the evidence:

- **Surface engineering**, where micro/nanostructuring raises effective contact area and improves charge generation [21] [22] [27] [28].
- **Dielectric and trap-state engineering**, where composite fillers increase permittivity, introduce charge traps, control polarization, and reduce effective dielectric losses [8] [9] [10] [26].

The SiO2-MoS2 strategy fits the second route particularly well. **MoS2** can contribute trap-rich interfaces and tribo-active behavior, while **SiO2** can inhibit transport pathways that would otherwise drain away accumulated charge [6] [7] [29]. This pattern implies that their simultaneous use is best understood as **interfacial dielectric engineering for higher retained surface charge** rather than simply as filler addition [7] [9].

Confidence level: High - this section is directly supported by foundational and composite-design findings [8] [9] [15].

Working Mechanisms for Efficiency Improvement

1. Dielectric enhancement and interfacial polarization

The clearest mechanism for simultaneous SiO2 and MoS2 use is **interfacial polarization enhancement**. In a PVDF-based composite, **SiO2-decorated MoS2 flowers** increased dielectric constant to **10.8 at 1 kHz** and breakdown strength to **486.8 MV/m at 1 wt% loading** [7]. The study attributed these gains to the high-interfacial-area MoS2 structure combined with SiO2-induced suppression of carrier transport and enhanced charge trapping [7].

This is important for TENGs because prior dielectric-polarization studies showed that higher permittivity and trap-rich composites can support greater surface charge density and stronger output [8] [9] [10] [26]. Thus, a SiO2-MoS2 hybrid can help create a tribolayer that polarizes more strongly during contact while resisting electrical failure and leakage [7].

2. Charge trapping and triboelectric activity from MoS2

MoS2-only composite studies show that MoS2 can increase TENG-relevant output by improving **charge trapping, negative charge accumulation, surface roughness, charge transfer efficiency, and dielectric properties** [1] [2] [3] [4] [5]. In one PVDF-related system, MoS2 also promoted **β-phase formation and polarity generation**, which is relevant because polymer polarity can reinforce charge storage behavior [1] [4].

These findings support using MoS2 as the **active electrical amplifier** within the hybrid. It is the component most closely associated with increasing triboelectric activity and localized charge-trap density [1] [4].

3. Leakage suppression by SiO2

The complementary role of SiO2 is not primarily to add triboelectric activity, but to improve the **insulating environment** around the active filler. In the SiO2-decorated MoS2 system, SiO2 was explicitly linked to **carrier-transport suppression and charge-leakage reduction** [7]. More broadly, insulating behavior and reduced leakage are central to dielectric composite strategies that improve TENG output [8] [9] [10].

This means the best simultaneous-use design is likely one where SiO2 is spatially arranged to **isolate or partially passivate MoS2 conductive pathways**, preserving the benefits of interfacial polarization without allowing excessive carrier movement [6] [7].

4. Humidity protection

A separate but practically important mechanism is **moisture shielding**. MoS2-encapsulated SiO2 nanoparticles formed a core-shell tribomaterial where a thin MoS2 layer reduced water penetration, stabilized charge density, and mitigated humidity-induced charge decay [11]. The associated TENG retained **more than 70% output after 25 h at 99% RH** [11].

Taken together, these findings suggest that simultaneous SiO2-MoS2 use may improve efficiency in two distinct senses: **higher electrical conversion under dry/normal conditions** and **less efficiency loss under humid conditions** [7] [11].

Confidence level: High for the mechanistic picture; Medium for quantitative translation into all TENG architectures [7] [11].

Material Design and Device Architectures

1. SiO2-decorated MoS2 fillers in polymer matrices

The most evidence-backed architecture is a **hybrid filler dispersed into a polymer tribolayer**, especially a **PVDF-based matrix** [7]. In this route:

- **MoS2 flowers or nanosheets** provide high interfacial area and trap-rich surfaces [7].
- **SiO2 decoration** insulates those structures and reduces leakage [7].
- The **polymer matrix** provides flexibility and acts as the triboelectric host [7].

This architecture is consistent with broader MoS2-composite evidence showing improved output in several polymers, including PVDF [1] [4].

2. Core-shell or encapsulated tribomaterials

Another viable architecture is a **core-shell particle**, specifically **MoS2-encapsulated SiO2 nanoparticles** [11]. Here the function is slightly different from the PVDF composite example:

- **SiO2** acts as the particulate base [11].
- **MoS2 shelling/encapsulation** reduces water penetration and charge decay [11].
- The design is particularly attractive where environmental robustness matters, such as self-powered sensing [11].

Because the supplied evidence does not provide a broader direct comparison of shell directionality, it remains unclear whether **SiO2@MoS2** or **MoS2@SiO2** is generally superior for electrical output; the choice may depend on whether the target is peak output or humidity tolerance [7] [11].

3. Wearable and flexible deployment formats

The supplied evidence does not verify a fully characterized wearable TENG that simultaneously uses both SiO2 and MoS2 in one architecture [14] [19] [20]. Still, MoS2-enabled wearable TENGs in the retrieved set used **single-electrode/contact-driven** and **vertical** configurations, including skin/cloth-compatible operation and body-motion inputs [14] [19]. Reviews of textile-integrated TENGs show that such formats are relevant for future SiO2-MoS2 translation, but they also highlight tradeoffs in washability, durability, and environmental stability [18] [23] [30] [31].

Confidence level: Medium - the structural options are supported, but architecture-specific evidence for simultaneous SiO2+MoS2 TENGs is limited [7] [11] [14].

Performance Evidence and Comparative Metrics

What direct quantitative evidence is available?

For **simultaneous SiO2-MoS2 use**, the strongest quantitative evidence in the supplied set concerns **dielectric behavior**, not full TENG output: dielectric constant **10.8 at 1 kHz** and breakdown strength **486.8 MV/m** at **1 wt%** loading for SiO2-decorated MoS2 in a PVDF-based composite [7].

For **SiO2-only TENGs**, one study reported that **Voc increased from 78.1 V at 0 wt% to 200.2 V at 3 wt% SiO2**, then slightly decreased to **195.5 V at 4 wt%** in PDMS-based material [12]. This supports the broader idea that SiO2 can improve TENG output, but does not by itself establish synergy with MoS2 [12].

For **MoS2-only TENGs**, one device reached **0.95 kV Voc**, **2.2 μA Isc**, and **60 μW/cm2 power density**, and illumination increased Voc by **more than 26%** [13]. This confirms that MoS2 can be a strong tribo-active additive/device component [13].

A separate SiO2-rich triboelectric system achieved **5.7 mA m−2 current density**, though the supplied excerpt does not include a matched pristine baseline [32].

What can be inferred from these separate datasets?

Inferred: Because SiO2-only systems improve Voc, MoS2-only systems can produce strong output, and a direct SiO2-decorated MoS2 composite improves dielectric constant and breakdown strength, the most plausible expectation is that a well-designed hybrid tribolayer could outperform a pristine polymer and may outperform at least some single-filler formulations if dispersion and loading are optimized [7] [12] [13].

This is an inference, not an established comparative fact, because the supplied studies do not provide a unified benchmark matrix [12] [13] [14].

Environmental durability

The best direct combined-material device evidence concerns humidity stability: **MoS2-encapsulated SiO2 nanoparticle TENGs retained >70% output after 25 h at 99% RH** and were used to power a gas sensor array [11]. That is a meaningful practical gain because moisture commonly accelerates tribocharge decay [11].

Confidence level: Medium - quantitative points are solid where reported, but the comparative evidence base is incomplete [7] [11] [12] [13].

Practical Design Recommendations

Based on the supplied evidence, the most defensible design pathway is:

Recommended material strategy

- Use a **tribonegative polymer matrix**, preferably **PVDF-based**, as the host [7].
- Introduce a **hybrid SiO2-MoS2 filler**, not two independently dispersed additives, to control interfaces more effectively [6] [7].
- Keep loading **low and optimized**, since the best quoted hybrid dielectric data were obtained at **1 wt%** [7].

Recommended morphology

- Prefer **SiO2-decorated MoS2 flowers/nanosheets** when the goal is stronger dielectric polarization plus leakage suppression [7].
- Prefer **MoS2-encapsulated SiO2 nanoparticles** when humidity robustness is especially important [11].

Recommended functional division

- Assign **MoS2** the role of **charge-trapping/tribo-active interface generator** [1] [4].
- Assign **SiO2** the role of **insulating barrier and retention stabilizer** [6] [7].

Recommended device optimization sequence

1. Optimize filler morphology and loading for dielectric response [7].
2. Then add **surface micro/nanostructuring** to increase contact area [21] [22].
3. Then evaluate under humidity and cyclic bending if targeting wearables or sensors [11] [23] [24].

Confidence level: Medium-High - these recommendations closely follow the mechanistic evidence, though full device benchmarking is still needed [7] [11].

Applications and Practical Implications

The clearest near-term application is **self-powered sensing in humid environments**. MoS2-encapsulated SiO2 nanoparticle TENGs were able to retain substantial output under **99% RH** and power a **gas sensor array**, showing that combined SiO2-MoS2 designs can support real use where moisture would otherwise degrade operation [11].

For **wearable energy harvesting**, the evidence is more indirect. MoS2-related wearable TENGs already operate under body motion, continuous pressing, axial pressure, and skin/cloth attachment, indicating that MoS2-containing flexible architectures are feasible [14] [19]. Reviews of textile TENGs suggest that adding environmental robustness is particularly valuable, but also warn that boosting output can create tradeoffs in flexibility, washability, and lifetime [18] [23] [24] [30]. Thus, a SiO2-MoS2 strategy may be especially attractive where **stable moderate output** is more valuable than maximum peak output [23] [24].

Limitations and Research Outlook

The main weakness in the present evidence is not the lack of a plausible mechanism; it is the lack of **standardized, direct device comparisons** [7] [12] [13]. The field still needs studies that compare, under identical conditions:

- pristine polymer,
- SiO2-only filler,
- MoS2-only filler, and
- SiO2+MoS2 hybrid filler [12] [13] [14].

It also remains unclear which architecture is best: **decorated filler, layered interlayer, blended composite, or core-shell particle** [7] [11]. Long-term mechanical durability, washability, and fatigue data for wearable combined-material devices are also sparse in the supplied set [18] [23] [24].

Inferred research priority: the most informative next experiment would be a single study using one polymer matrix and one TENG mode to compare output, charge density, humidity stability, and cyclic durability across the full additive matrix above [7] [11] [12].

Confidence level: High - the evidence gap itself is clearly and repeatedly supported in the supplied material [7] [12] [13] [14].

Conclusion

SiO2 and MoS2 can be used simultaneously in a TENG most effectively as a **hybrid interfacial filler system**: **MoS2 provides charge trapping, tribo-activity, and interfacial polarization**, while **SiO2 suppresses leakage, improves insulation, and helps charge retention** [6] [7]. The most evidence-backed implementation is **SiO2-decorated MoS2 dispersed in a PVDF-based tribolayer**, while **MoS2-encapsulated SiO2** is especially promising for **humidity-tolerant devices** [7] [11].

So the short practical answer is: **use them together as a structured hybrid, not just as two separate fillers, and optimize the hybrid for both dielectric enhancement and leakage suppression** [7].

Overall confidence: Medium-High - the mechanism is well supported, the practical design direction is clear, but fully comparative device-level validation remains limited [7] [12] [13].

References

1. Kim, H., Rana, S.M.S., Faruk, O., (...), Park, J.Y. (2023) A Stretchable Triboelectric Nanogenerator Based on Molybdenum Disulfide for Wearable Self-Powered Biomotion Monitoring. *PowerMEMS 2023 - 2023 IEEE 22nd International Conference on Micro and Nanotechnology for Power Generation and Energy Conversion Applications*. https://doi.org/10.1109/PowerMEMS59329.2023.10417564

2. Zhang, H., Zhang, D., Mao, R., (...), Ji, Y. (2024) MoS2-based charge trapping layer enabled triboelectric nanogenerator with assistance of CNN-GRU model for intelligent perception. *Nano Energy*. https://doi.org/10.1016/j.nanoen.2024.109753
3. Zhuo, L., Yuen Goay, A.C.Y., Sangkarat, P., (...), Zhang, J. (2025) Enhanced Triboelectric Outputs from PAN/MoS2 Nanofiber-Based Nanogenerators for Powering Backscatter Communications in Sustainable 6G Networks. *Advanced Energy and Sustainability Research*. https://doi.org/10.1002/aesr.202400301
4. Hedau, B., Kang, B.-C., Ha, T.-J. (2022) Enhanced Triboelectric Effects of Self-Poled MoS2-Embedded PVDF Hybrid Nanocomposite Films for Bar-Printed Wearable Triboelectric Nanogenerators. *ACS Nano*. https://doi.org/10.1021/acsnano.2c06257
5. Shyju, S., Chandran, A.M., Varun, S., (...), Mural, P.K.S. (2024) Multifunctional Electrospun Polycaprolactone-Based Nanocomposites for Triboelectric Applications: From Energy Harvesting to IoT-Based Traffic Management and Pedometer Systems. *ACS Applied Electronic Materials*. https://doi.org/10.1021/acsaelm.4c01657
6. https://www.scopus.com/pages/publications/85133477736
7. Luo, H.-B., Lu, Z.-J., Qi, X.-D., (...), Yang, J.-H. (2022) Insulating SiO2 internally decorated MoS2 flowers as hybrid filler to simultaneously improve breakdown strength and dielectric performance of PVDF-based composites. *Composites Science and Technology*. https://doi.org/10.1016/j.compscitech.2022.109610
8. Chen, J., Guo, H., He, X., (...), Hu, C. (2016) Enhancing Performance of Triboelectric Nanogenerator by Filling High Dielectric Nanoparticles into Sponge PDMS Film. *ACS Applied Materials and Interfaces*. https://doi.org/10.1021/acsami.5b09907
9. Seung, W., Yoon, H.-J., Kim, T.Y., (...), Kim, S.-W. (2017) Boosting Power-Generating Performance of Triboelectric Nanogenerators via Artificial Control of Ferroelectric Polarization and Dielectric Properties. *Advanced Energy Materials*. https://doi.org/10.1002/aenm.201600988
10. He, X., Guo, H., Yue, X., (...), Hu, C. (2015) Improving energy conversion efficiency for triboelectric nanogenerator with capacitor structure by maximizing surface charge density. *Nanoscale*. https://doi.org/10.1039/c4nr05512h
11. Kim, D.-H., Park, J.Y., Choi, H.S., (...), Baik, J.M. (2025) Advancing Humidity-Resistant Triboelectric Nanogenerators Through MoS_2-Encapsulated SiO_2 Nanoparticles for Self-Powered Gas Sensing Applications. *Advanced Energy Materials*. https://doi.org/10.1002/aenm.202405278
12. Chai, Y., Wu, L., Liu, J., (...), Liu, J. (2026) Performance-boosted triboelectric nanogenerators via electret doping and corona polarization. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. https://doi.org/10.1016/j.colsurfa.2025.139122
13. Joshi, S.R., Kim, S. (2024) Functional silk-protein-based nanocomposites for light-stimulated and highly efficient triboelectric nanogenerators and charge storage devices. *Journal of Power Sources*. https://doi.org/10.1016/j.jpowsour.2024.235538

14. Zu, G., Wei, Y., Sun, C., Yang, X. (2022) Humidity-resistant, durable, wearable single-electrode triboelectric nanogenerator for mechanical energy harvesting. *Journal of Materials Science*. https://doi.org/10.1007/s10853-021-06696-2

15. Wang, Z.L. (2013) Triboelectric nanogenerators as new energy technology for self-powered systems and as active mechanical and chemical sensors. *ACS Nano*. https://doi.org/10.1021/nn404614z

16. Niu, S., Wang, S., Lin, L., (...), Wang, Z.L. (2013) Theoretical study of contact-mode triboelectric nanogenerators as an effective power source. *Energy and Environmental Science*. https://doi.org/10.1039/c3ee42571a

17. Niu, S., Liu, Y., Wang, S., (...), Wang, Z.L. (2013) Theory of sliding-mode triboelectric nanogenerators. *Advanced Materials*. https://doi.org/10.1002/adma.201302808

18. Morsada, Z., Munia, T.A., Zannat, A. (2025) Textile-based triboelectric nanogenerator as energy harvesting devices. *Textile- and Fiber-Based Triboelectric Nanogenerators: Advances and Perspectives*. https://doi.org/10.1016/B978-0-443-24074-4.00012-9

19. Biswas, M., Bhattacharya, D., Mondal, R., (...), Chowdhury, A. (2025) Surface Engineered MoS2-Based Novel Vertical Triboelectric Nanogenerator (V-TENG) for Wireless Information Processing. *Small*. https://doi.org/10.1002/smll.202410608

20. Sarkar, D., Das, N., Sau, S., (...), Das, S. (2023) Micro-patterned BaTiO3@Ecoflex nanocomposite-assisted self-powered and wearable triboelectric nanogenerator with improved charge retention by 2D MoTe2/PVDF nanofibrous layer. *Journal of Materials Chemistry C*. https://doi.org/10.1039/d3tc03822j

21. Fan, F.-R., Lin, L., Zhu, G., (...), Wang, Z.L. (2012) Transparent triboelectric nanogenerators and self-powered pressure sensors based on micropatterned plastic films. *Nano Letters*. https://doi.org/10.1021/nl300988z

22. Wang, Z.L. (2014) Triboelectric nanogenerators as new energy technology and self-powered sensors - Principles, problems and perspectives. *Faraday Discussions*. https://doi.org/10.1039/c4fd00159a

23. Zhou, J., Cao, B., Song, Z., (...), Wang, P. (2026) Soft-contact triboelectric nanogenerators: Materials, structures, contact modes, performances and applications. *Nano Energy*. https://doi.org/10.1016/j.nanoen.2026.112299

24. Lu, Y., Tong, T., Ma, Z., (...), Wang, N. (2023) Integration of Flexible Supercapacitors with Triboelectric Nanogenerators: A Review. *Batteries*. https://doi.org/10.3390/batteries9050281

25. Niu, S., Wang, Z.L. (2014) Theoretical systems of triboelectric nanogenerators. *Nano Energy*. https://doi.org/10.1016/j.nanoen.2014.11.034

26. Cui, N., Gu, L., Lei, Y., (...), Wang, Z.L. (2016) Dynamic Behavior of the Triboelectric Charges and Structural Optimization of the Friction Layer for a Triboelectric Nanogenerator. *ACS Nano*. https://doi.org/10.1021/acsnano.6b02076

27. Zi, Y., Niu, S., Wang, J., (...), Wang, Z.L. (2015) Standards and figure-of-merits for quantifying the performance of triboelectric nanogenerators. *Nature Communications*. https://doi.org/10.1038/ncomms9376

28. Niu, S., Liu, Y., Wang, S., (...), Wang, Z.L. (2014) Theoretical investigation and structural optimization of single-electrode triboelectric nanogenerators. *Advanced Functional Materials*. https://doi.org/10.1002/adfm.201303799

29. Pan, H., Wang, Z., Cui, Y., (...), Zong, C. (2021) Influences of porous reduction graphene oxide/molybdenum disulfide as filler on dielectric properties, thermal stability, and mechanical properties of natural rubber. *Journal of Vinyl and Additive Technology*. https://doi.org/10.1002/vnl.21857

30. Kulandaivel, A., Khanapuram, U.K., Rakesh Kumar, R.K., Kodali, P. (2025) Materials and preparation methods. *Textile- and Fiber-Based Triboelectric Nanogenerators: Advances and Perspectives*. https://doi.org/10.1016/B978-0-443-24074-4.00002-6

31. Mahapatra, A., Tan, Y.Y., Chong, G., Low, H.Y. (2026) Review on Textile Triboelectric Nanogenerators: From Material Design to Self-Powered Wearable Energy Systems. *Advanced Energy Materials*. https://doi.org/10.1002/aenm.71524

32. Wu, J.M., Chang, C.K., Chang, Y.T. (2016) High-output current density of the triboelectric nanogenerator made from recycling rice husks. *Nano Energy*. https://doi.org/10.1016/j.nanoen.2015.11.014