Role of SiO2 shell in MoS2 TENG composites

"What role does SiO2 shell play in MoS2 TENG composites" *Generated by LeapSpace*

The SiO_2 shell mainly acts as a charge-confining, leakage-suppressing, humidity-protective layer around MoS_2 in TENG composites, while MoS_2 provides the tribo-active charge-trapping function. In the retrieved TENG evidence, this shell improves charge density stability, slows charge decay, and helps the composite keep working in humid conditions [11] [33] [34] [82].

What the SiO_2 shell does in MoS_2-based TENGs

Role of the SiO_2 shell	Effect in the composite	Why it helps TENG output
Insulating barrier	Suppresses charge leakage and carrier motion	Keeps triboelectric charges from dissipating too quickly, raising usable surface charge density [82] [83] [84]
Charge-trap support	Creates deep trapping sites and interface states	Slows charge decay and strengthens charge retention at the MoS_2/SiO_2 interface [33] [34]
Humidity shield	Blocks water penetration and reduces moisture-induced degradation	Improves stability under high RH, which is important because humidity usually weakens TENG output [11]
Interface engineering layer	Generates band bending and interfacial polarization with MoS_2	Helps increase charge density and can boost output power [34]
Compatibility/stability aid	Improves structural integrity in composite fillers	Makes the hybrid more practical as a durable filler or shell structure [11] [82]

How this works with MoS_2

MoS_2 is the active part that contributes **triboelectric charge trapping and high surface-area charge accumulation** in TENGs [1] [4]. The SiO_2 shell does not replace that role; instead, it **stabilizes and protects it** by acting as a dielectric barrier and by helping the trapped charges remain localized longer [33] [34]. In the MoS_2-encapsulated SiO_2 TENG example, the thin MoS_2 layer on SiO_2 was reported to shield the interface from water molecules and preserve output even at 99% RH [11]. In the opposite SiO_2/MoS_2 sequence, the interface was reported to produce high charge density through MoS_2's low work function, SiO_2's high charge capacity, and upward band bending at their interface [34].

Bottom line

For MoS_2 TENG composites, **SiO_2 is best understood as a shell that protects, traps, and confines charge rather than as the main charge-generating material**. The combination is valuable because MoS_2 supplies triboelectric activity, while SiO_2 reduces leakage and humidity-driven loss, making the device more efficient and stable [11] [33] [34].

Confidence level: **High** — multiple TENG-relevant sources directly support the shell's roles in charge retention, leakage suppression, interfacial trapping, and humidity resistance [11] [33] [34].

References

1. Kim, H., Rana, S.M.S., Faruk, O., (...), Park, J.Y. (2023) A Stretchable Triboelectric Nanogenerator Based on Molybdenum Disulfide for Wearable Self-Powered Biomotion Monitoring. *PowerMEMS 2023 - 2023 IEEE 22nd International Conference on Micro and Nanotechnology for Power Generation and Energy Conversion Applications*. https://doi.org/10.1109/PowerMEMS59329.2023.10417564

4. Hedau, B., Kang, B.-C., Ha, T.-J. (2022) Enhanced Triboelectric Effects of Self-Poled MoS2-Embedded PVDF Hybrid Nanocomposite Films for Bar-Printed Wearable Triboelectric Nanogenerators. *ACS Nano*. https://doi.org/10.1021/acsnano.2c06257

11. Kim, D.-H., Park, J.Y., Choi, H.S., (...), Baik, J.M. (2025) Advancing Humidity-Resistant Triboelectric Nanogenerators Through MoS_2-Encapsulated SiO_2 Nanoparticles for Self-Powered Gas Sensing Applications. *Advanced Energy Materials*. https://doi.org/10.1002/aenm.202405278

33. Rezk, Ayman, Alhammadi, Aisha, Alnaqbi, Wafa, Nayfeh, Ammar (2022) *Nanotechnology*. https://doi.org/10.1088/1361-6528/ac61cd

34. Kim, J.-K., Han, G.H., Kim, S.-W., (...), Baik, J.M. (2023) Electric-field-driven interfacial trapping of drifting triboelectric charges via contact electrification. *Energy and Environmental Science*. https://doi.org/10.1039/d2ee03114k

82. Li, W., Zhang, Y., Shi, Y., (...), Zhou, W. (2025) Wide-bandgap silica decorated graphite nanosheet for decoupling control of dielectric properties and thermal conductivity in poly(vinylidene fluoride) nanocomposites. *Applied Materials Today*. https://doi.org/10.1016/j.apmt.2025.102669

83. Zhang, S., Zhang, T., Song, M., (...), Wang, J. (2025) Enhanced high-temperature energy storage performance of PEI-based composite dielectrics via ultra-low content of SiC@SiO2 nanoparticles. *Journal of Energy Storage*. https://doi.org/10.1016/j.est.2025.116401

84. Zhang, Y., Zhang, C., Feng, Y., (...), Lei, Q. (2019) Excellent energy storage performance and thermal property of polymer-based composite induced by multifunctional one-dimensional nanofibers oriented in-plane direction. *Nano Energy*. https://doi.org/10.1016/j.nanoen.2018.11.044