Characterization of MoS2@SiO2 core-shell structures

"What characterization confirms a MoS2@SiO2 core-shell structure" *Generated by LeapSpace*

MoS_2@SiO_2 core-shell structure is typically confirmed by a combination of TEM/HRTEM, EDS elemental mapping or line-scan, XRD, and XPS; TEM/EDS gives the most direct proof of "core" versus "shell," while XRD and XPS support the phase and surface-chemistry changes. [80] [90] [91] [92]

What each characterization shows

Characterization	What confirms the core-shell structure	Evidence in the retrieved material
TEM / HRTEM	Directly shows a dense core with a surrounding shell, shell thickness, and contrast difference between core and shell	Used to verify SiO_2 coating on MoS_2 and to visualize coated morphology; TEM was explicitly described as the direct tool to verify core-shell structure [80] [91] [93]
EDS elemental mapping / line scan	Shows where each element is located; for MoS_2@SiO_2, Si should be enriched at the outer region while Mo and S remain in the core region	Si signal distributed on the particle surface and edge region, confirming a silica shell; similar mapping logic was used to prove shell formation in other core-shell systems [91] [92] [94]
XRD	Confirms the crystalline phase of MoS_2 is retained and can show changes in peak intensity after SiO_2 coating	For MoS_2@SiO_2, XRD showed the MoS_2 phase remained, while the (002) peak intensity decreased after SiO_2 attachment/growth; no obvious crystalline SiO_2 peak is expected if the silica shell is amorphous [90] [92]
XPS	Confirms surface composition and chemical-state changes caused by the shell	Stronger Si 2p after TEOS/silica coating supports successful SiO_2 shell formation; XPS is also used alongside TEM-EDS to verify coating in core-shell systems [95] [96]
Raman	Supports preservation of MoS_2 structure; attenuation of MoS_2 vibrational peaks after encapsulation can indicate shell coverage	In a MoS_2/SiO_2 core-shell composite, MoS_2 peaks were noticeably weakened by SiO_2 encapsulation [97]

Most convincing confirmation pattern

For **MoS_2@SiO_2 specifically**, the strongest confirmation is:

1. **TEM/HRTEM** showing a clear shell around the MoS_2 core [91] [93]
2. **EDS mapping or line-scan** showing **Si concentrated at the outer layer** and **Mo/S concentrated in the core** [91] [92] [94]
3. **XPS** showing stronger **Si 2p** signal after coating [95] [96]
4. **XRD/Raman** showing that the MoS_2 phase remains present, with signal changes consistent with encapsulation [90] [97]

Bottom line

If you want to prove a MoS_2@SiO_2 core-shell composite, TEM/HRTEM plus EDS mapping is the primary proof, and XPS/XRD/Raman are the supporting confirmations that the silica shell formed while the MoS_2 core remained intact. [80] [90] [91] [97]

Confidence level: **High** — multiple retrieved core-shell papers consistently use the same characterization package, with TEM/EDS providing direct morphology and elemental-distribution evidence and XPS/XRD/Raman providing complementary phase and surface-chemistry support.

References

80. Luo, H.-B., Lu, Z.-J., Qi, X.-D., (...), Yang, J.-H. (2022) Insulating SiO2 internally decorated MoS2 flowers as hybrid filler to simultaneously improve breakdown strength and dielectric performance of PVDF-based composites. *Composites Science and Technology*. https://doi.org/10.1016/j.compscitech.2022.109610

90. Guo, K., Shao, X., Chen, M., (...), Wang, L. (2026) Temperature-dependent tribological mechanisms of MoS2@SiO2 core-shell lubricants from 200 to 800 ℃: Experiments and molecular dynamics. *Results in Engineering*. https://doi.org/10.1016/j.rineng.2026.112693

91. Li, F., Chen, Y., Gong, M., (...), Li, Z. (2023) Core-shell structure Mg-MOF-74@MSiO2 with mesoporous silica shell having efficiently sustained release ability of magnesium ions potential for bone repair application. *Journal of Non-Crystalline Solids*. https://doi.org/10.1016/j.jnoncrysol.2022.122018

92. Chen, J., Xu, W., Zhu, J., (...), Zhou, J. (2020) Highly effective direct decomposition of H2S by microwave catalysis on core-shell Mo2N-MoC@SiO2 microwave catalyst. *Applied Catalysis B: Environmental*. https://doi.org/10.1016/j.apcatb.2019.118454

93. Jangale, S.D., Kamble, S.A., Bhopale, S.R., (...), Mathe, V.L. (2025) Single-step, catalyst-free conversion of rice husk into one-dimensional core–shell nanocrystalline silicon carbide–silicon oxide using thermal plasma-assisted pyrolysis method for field emission application. *Bioresource Technology*. https://doi.org/10.1016/j.biortech.2025.132441

94. Kuo, Y.-S., Liu, Y.-C., Kuo, J.-K., Liu, Y.-H. (2025) Enhanced electrochemical performance of a composite made of core-shell structured ZnMn2O4@TiO2 and soft carbon as an anode material for lithium-ion batteries. *Electrochimica Acta*. https://doi.org/10.1016/j.electacta.2025.146982

95. Xing, Z.-H., Zhu, M.-X., Xue, J.-Y., (...), Liu, R. (2026) Pt decorated core-shell ZnS:Cu doped epoxy composites: Achieving enhanced breakdown strength and defect visualization. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2026.176660

96. Feng, Lili, Zhang, Yinyin, Wang, Rui, (...), Guan, Hongjin (2017) *Nanoscale Research Letters*. https://doi.org/10.1186/s11671-017-2286-3

97. Shao, X., Wang, Z., Wang, X.-Z., (...), Wang, L. (2026) Wide-temperature lubrication of core-shell structured MoS2-based composites enabled via the formation of amorphous molten layer and low-shear lamellar Bi2S3 and Bi2MoO6. *Tribology International*. https://doi.org/10.1016/j.triboint.2026.112131