Raman spectroscopy of MoS2@SiO2 core-shell structures

"How does Raman spectroscopy change after SiO2 encapsulation of MoS2" *Generated by LeapSpace*

After **SiO_2 encapsulation/support**, MoS_2 usually still shows the same **fingerprint Raman modes**—mainly **E(_{2g}^1)** and **A(_{1g})**—but their **positions, linewidths, and intensities can shift slightly** because the encapsulation changes strain, dielectric environment, and carrier concentration rather than destroying the MoS_2 lattice [66] [67].

What changes in the Raman spectrum

Raman feature	Typical change after SiO_2 encapsulation/support	Interpretation
E(_{2g}^1)	Can **blue-shift slightly**; one report found about **+1.3 cm^{-1}** after transfer to SiO_2/Si [66]	Suggests a change in strain or interlayer/substrate coupling [66]
A(_{1g})	Often changes **only slightly** compared with E(_{2g}^1) [66]	The out-of-plane mode is more sensitive to charge/dielectric effects, so small changes may reflect encapsulation-induced doping or band bending [67]
FWHM / linewidth	Can change modestly; encapsulation studies note **small FWHM changes** in A(_{1g}) [67]	Indicates altered disorder, coupling, or carrier environment [67]
Peak intensity	May increase or decrease depending on substrate coupling and measurement conditions [66] [68]	Reflects changes in optical coupling, thickness, and substrate interaction rather than a new phase [68]

Practical reading of the spectrum

- **If the E(*{2g}^1) and A(*{1g}) peaks are still present**, the MoS_2 structure is generally preserved [66] [68].
- **A small shift in E(_{2g}^1)** is a common sign of **strain or altered substrate interaction** after encapsulation/support on SiO_2 [66].
- **Changes in A(_{1g})** are more often linked to **carrier concentration, dielectric screening, or band bending** introduced by the encapsulating environment [67].
- The literature explicitly notes that after encapsulation, Raman shifts should be interpreted by separating **strain effects** from **carrier-density effects** [67].

Bottom line

SiO_2 encapsulation does not remove MoS_2's Raman fingerprints; it usually causes modest peak shifts and sometimes linewidth/intensity changes, with E(*{2g}^1) often shifting slightly and A*({1g}) changing more subtly. Those changes are best read as evidence of **strain, dielectric screening, and interface coupling**, not loss of the MoS_2 phase [66] [67] [68].

Confidence level: **Medium** — the evidence directly supports Raman shifts after SiO_2 support/encapsulation-like environments, but the retrieved sources are stronger on substrate/encapsulation effects than on a single, dedicated MoS_2@SiO_2 shell case.

References

66. Han, Tao, Liu, Hongxia, Wang, Shulong, (...), Li, Zhandong (2021) Synthesis and Spectral Characteristics Investigation of the 2D-2D vdWs Heterostructure Materials. *International Journal of Molecular Sciences*. https://doi.org/10.3390/ijms22031246

67. Peña, Tara, Chowdhury, Shoieb A, Azizimanesh, Ahmad, (...), Wu, Stephen M (2021) *2D Materials*. https://doi.org/10.1088/2053-1583/ac08f2

68. Judek, J., Gertych, A.P., Czerniak-Łosiewicz, K., Zdrojek, M. (2018) Temperature dependence of phonon properties in CVD MoS2 nanostructures-a statistical approach. *Physical Chemistry Chemical Physics*. https://doi.org/10.1039/c8cp01232f