Mesoporous silica shell surface area

"What pore diameter gives maximum surface area in mesoporous silica shells?" *Generated by LeapSpace*

The **highest surface area in mesoporous silica shells is not tied to one universal pore diameter**; instead, the retrieved evidence shows that **surface area tends to be maximized when pores are still mesoporous, relatively narrow, and well ordered**, with many shell systems clustering around **~2.5–4 nm** and high-surface-area materials often reported in that range [82] [83] [84] [85] [86] [87].

What the evidence shows

Pore diameter	Surface area outcome	Interpretation
~2.0–3.0 nm	High surface areas are reported in ordered shells, including **~2.0 nm** pores in a mesoporous silica shell and **2.6 nm** in another core-shell silica shell [84] [88].	This range is strongly compatible with high surface area because the pore network remains dense and accessible.
~3.0–4.0 nm	Multiple mesoporous silica samples show high surface area around **3–4 nm**, including pristine mesoporous silica at **3–4 nm**, **3.3–3.4 nm** in doped silica catalysts, and **3.55 nm** in mesoporous silica nanoparticles [82] [87] [89].	This is the **best-supported practical range** for high surface area in mesoporous silica shells from the retrieved evidence.
~4–5 nm	Still capable of high surface area, e.g. **4.23 nm** and **4.65 nm** materials with large BET values [85] [90].	Surface area can remain high, but the evidence is less consistent than for ~2.5–4 nm.
>5 nm	Some large-pore shells still show high area, but in one comparison the **largest mesopore size (38.64 nm)** corresponded to the **smallest surface area** [91].	Very large pores tend to reduce surface area because pore wall area per unit mass falls.

Bottom line

If you want a single working answer, **the pore diameter most often associated with maximum surface area in mesoporous silica shells is roughly 2.5–4 nm**, with the strongest cluster of evidence around **~3–3.5 nm** [82] [84] [85] [87] [89]. Very large pores can still be mesoporous, but they generally do **not** maximize surface area; they trade area for larger void volume [90] [91].

Confidence level: **Medium** — the evidence consistently links high surface area to small mesopores in the low-nanometer range, but it does not provide a single controlled study proving one exact optimum across all mesoporous silica shell chemistries.

References

82. Sari, I.F., Ariesta, A.S., Handayani, N., (...), Ali Zulfikar, M.A. (2026) Selective removal of ketoprofen from aqueous systems using mesoporous silica-based molecularly imprinted polymers via computationally informed monomer selection. *Journal of Water Process Engineering*. https://doi.org/10.1016/j.jwpe.2026.110501

83. Lin, C., Chu, Y., Liu, F., Wang, P. (2026) Study on antibacterial lubricating coatings for oral implants based on electrostatic self-assembly and Schiff base reaction. *Colloids and Surfaces B: Biointerfaces*. https://doi.org/10.1016/j.colsurfb.2025.115343

84. Ni, J., Zhuo, Y., Zhang, H., (...), Li, Y. (2025) Engineering covalent core-shell architectures for dynamic optical cryptography: Time-resolved dual switching in organometallosilica nanocomposites. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2025.167799

85. Yeganeh, M., Saremi, M. (2015) Corrosion inhibition of magnesium using biocompatible Alkyd coatings incorporated by mesoporous silica nanocontainers. *Progress in Organic Coatings*. https://doi.org/10.1016/j.porgcoat.2014.10.015

86. Chen, J., Zhang, R., Han, L., (...), Zhao, D. (2013) One-pot synthesis of thermally stable gold@mesoporous silica core-shell nanospheres with catalytic activity. *Nano Research*. https://doi.org/10.1007/s12274-013-0363-1

87. Olowookere, I.T., Perera, I.P., Abeyrathne, C., (...), Suib, S.L. (2025) Selective oxidation of styrene over transition metal-doped mesoporous silica catalyst. *Journal of Colloid and Interface Science*. https://doi.org/10.1016/j.jcis.2024.10.157

88. Meng, Y., Chen, D., Jiao, X. (2006) Fabrication and characterization of mesoporous Co3O4 core/mesoporous silica shell nanocomposites. *Journal of Physical Chemistry B*. https://doi.org/10.1021/jp0626465

89. Zhang, W., Zhang, H., He, J., (...), Ni, P. (2025) Dual-drug-loaded complex hydrogel dressing composed of oxidized hyaluronic acid and modified mesoporous silica for diabetes foot wounds. *Journal of Drug Delivery Science and Technology*. https://doi.org/10.1016/j.jddst.2025.107575

90. Li, C.-C., Qiao, X.-C. (2016) A new approach to prepare mesoporous silica using coal fly ash. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2016.05.029

91. Sani, S., Liu, X., Li, M., (...), Sun, C. (2023) Synthesis and characterization of three-dimensional interconnected large-pore mesoporous cellular lignin carbon materials and their potential for CO2 capture. *Microporous and Mesoporous Materials*. https://doi.org/10.1016/j.micromeso.2022.112334