Pore ordering in mesoporous silica

"How does pore ordering affect surface area in mesoporous silica shells?" *Generated by LeapSpace*

Effect of pore ordering on surface area

More pore ordering usually increases the BET surface area in mesoporous silica shells, because ordered mesostructures create a larger, more accessible mesopore network; however, the gain depends on keeping the pores open and accessible rather than merely making them highly regular. In the retrieved evidence, ordered mesoporous silica consistently shows higher surface area than less ordered or disordered counterparts, including an ordered graphene–TiO_2/SiO_2 composite that had larger pore volume and BET area than its disordered analogue, and a core–shell nano-Y@mesoporous SiO_2 material whose surface area rose substantially after adding an ordered mesoporous shell [86] [87]. This aligns with the broader mesoporous-silica literature showing that ordered pore architectures are a major reason these materials achieve high surface area in the first place [88] [89] [90].

What the evidence implies

Pore ordering state	Surface area effect	Why
Well-ordered mesopores	Higher surface area	Regular, connected pores expose more internal wall area to adsorption and reduce structural irregularity [86] [87] [88]
Less ordered / disordered pores	Lower surface area	Irregular pore formation reduces accessible internal surface and can broaden the pore network [86] [91] [92]
Overly packed, blocked, or defect-rich pores	Surface area can drop despite ordering	Pore blocking, intrusion of species into pores, or structural defects reduce accessible area [93] [94] [95]

Practical takeaway

For mesoporous silica shells, the best surface-area outcome comes from **high pore order plus preserved accessibility**. In other words, **order helps**, but only if the shell remains open, well connected, and not overly blocked by template residue, guest loading, or excessive growth that closes off the pore network [93] [94] [95]. A highly ordered but partially blocked shell can underperform a slightly less perfect one if the latter has more accessible internal area [96] [97].

Bottom line: pore ordering tends to **raise surface area** in mesoporous silica shells by creating a more uniform and accessible pore network, but the real target is **ordered and open**, not just ordered; once pores become blocked, overfilled, or structurally damaged, surface area falls even if some order remains [86] [93] [96].

Confidence level: **High** — multiple independent sources agree that ordered mesoporous silica has higher BET area than less ordered/disordered variants, with clear caveats about pore blockage and accessibility [86] [87] [88] [96].

References

86. Li, K., Chen, T., Yan, L., (...), Zeng, Z. (2013) Design of graphene and silica co-doped titania composites with ordered mesostructure and their simulated sunlight photocatalytic performance towards atrazine degradation. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. https://doi.org/10.1016/j.colsurfa.2013.01.039

87. Lv, Y., Qian, X., Tu, B., Zhao, D. (2013) Generalized synthesis of core-shell structured nano-zeolite@ordered mesoporous silica composites. *Catalysis Today*. https://doi.org/10.1016/j.cattod.2012.09.031

88. Oh, S., Kang, T., Kim, H., (...), Yi, J. (2007) Preparation of novel ceramic membranes modified by mesoporous silica with 3-aminopropyltriethoxysilane (APTES) and its application to Cu2+ separation in the aqueous phase. *Journal of Membrane Science*. https://doi.org/10.1016/j.memsci.2007.06.006

89. Beck, J.S., Vartuli, J.C., Roth, W.J., (...), Schlenker, J.L. (1992) A New Family of Mesoporous Molecular Sieves Prepared with Liquid Crystal Templates. *Journal of the American Chemical Society*. https://doi.org/10.1021/ja00053a020

90. Huo, Q., Margolese, D.I., Stucky, G.D. (1996) Surfactant Control of Phases in the Synthesis of Mesoporous Silica-Based Materials. *Chemistry of Materials*. https://doi.org/10.1021/cm960137h

91. Morsi, R.E., Mohamed, R.S. (2018) Nanostructured mesoporous silica: Influence of the preparation conditions on the physical-surface properties for efficient organic dye uptake. *Royal Society Open Science*. https://doi.org/10.1098/rsos.172021

92. Qin, X.-B., Yu, R.-S., Kurihara, T., (...), Wei, L. (2009) Formation of ordered pores determined by positronium time of flight spectroscopy. *Materials Science Forum*. https://www.scopus.com/pages/publications/64349083554

93. Feng, Z., Bai, X. (2022) 3D-mesoporous KIT-6 supported highly dispersed Pd nanocatalyst for dodecahydro-N-ethylcarbazole dehydrogenation. *Microporous and Mesoporous Materials*. https://doi.org/10.1016/j.micromeso.2022.111789

94. Gao, H., Dong, C., Wang, Q., (...), Zhou, Q. (2018) Improving the proton conductivity of proton exchange membranes via incorporation of HPW-functionalized mesoporous silica nanospheres into SPEEK. *International Journal of Hydrogen Energy*. https://doi.org/10.1016/j.ijhydene.2018.08.214

95. Kuppireddy, S., Ramantani, T., Kentri, T., (...), Karanikolos, G.N. (2026) Optimization and in-situ spectroscopic monitoring of aminosilane-grafted KIT-6 mesoporous silica adsorbents for carbon capture and hydrogen purification. *International Journal of Hydrogen Energy*. https://doi.org/10.1016/j.ijhydene.2026.155414

96. Hung, C.-T., Bai, H. (2008) Adsorption behaviors of organic vapors using mesoporous silica particles made by evaporation induced self-assembly method. *Chemical Engineering Science*. https://doi.org/10.1016/j.ces.2008.01.002

97. Dou, B., Hu, Q., Li, J., (...), Hao, Z. (2011) Adsorption performance of VOCs in ordered mesoporous silicas with different pore structures and surface chemistry. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2010.12.051