CTAB-mediated mesopore formation in core-shell synthesis

"How does CTAB control mesopore formation in SiO2-MoS2 core-shell synthesis?" *Generated by LeapSpace*

CTAB controls mesopore formation in **SiO_2–MoS_2 core-shell synthesis** by acting as a **cationic structure-directing surfactant**: it first assembles into micelles, then silica precursors condense around those micelles, and after CTAB removal the micelle space becomes the mesopore network. In practice, CTAB also helps set **pore orientation, pore size, pore volume, and shell continuity** in the silica-containing shell, which is the part most directly supported by the retrieved evidence for core-shell systems like MoS_2-encapsulated SiO_2 and related mesoporous silica shells [11] [65] [66] [67].

How CTAB drives mesopore formation

CTAB role	What happens during synthesis	Structural consequence
Micelle former	CTAB self-assembles into spherical or cylindrical micelles in the aqueous synthesis medium [66] [67] [68]	Creates a soft template for pore generation
Template for silica condensation	Silicate species from TEOS hydrolyze and condense around CTAB micelles through electrostatic attraction [65] [66] [67] [68]	Forms an organic–inorganic mesophase that becomes meso-porous after template removal
Pore-shape regulator	Micelles can transform from spherical to cylindrical or other packed states depending on conditions [66] [69] [70]	Determines whether pores are more radial, parallel, or disordered
Mesoporosity controller	CTAB concentration affects whether pores are ordered, disordered, open, blocked, larger, or smaller [71] [72]	Tunes pore size distribution, surface area, and pore volume

What CTAB changes in a SiO_2–MoS_2 core-shell context

For **MoS_2-core / SiO_2-shell** or related silica-encapsulated architectures, CTAB is mainly responsible for building the **mesoporous SiO_2 shell** rather than the MoS_2 core itself. The shell can become a **continuous mesoporous layer** because CTAB micelles are embedded in the silica network during formation and later removed, leaving open channels [11] [66] [73].

CTAB concentration and synthesis conditions also matter:

- **Low CTAB** can give incomplete or less organized mesoporosity, and in some systems CTAB also stabilizes spherical micelles rather than highly ordered channels [70] [74].
- **Higher CTAB** can increase mesopore formation, but excess CTAB can also cause **micelle aggregation or pore blockage**, reducing accessibility and narrowing useful transport pathways [71].
- Co-solvents and additives can shift CTAB from **spherical to cylindrical micelles**, which changes whether pores are more radial or more parallel/oriented [66] [69] [75].

Inference for SiO_2–MoS_2 particles

A reasonable inference from the silica-template literature is that CTAB in a SiO_2–MoS_2 core-shell synthesis should be used to achieve a **thin, continuous, and uniformly mesoporous SiO_2 shell** that preserves diffusion pathways while maintaining shell integrity [11] [66] [73]. That is consistent with the reported MoS_2-encapsulated SiO_2 architecture, where the key benefit is a stable, humidity-resistant encapsulating shell [11].

Bottom line

CTAB is the mesopore architect: it templates the pore space, steers micelle geometry, and therefore controls the shell's pore size, ordering, and continuity in SiO_2-based core-shell synthesis. For SiO_2–MoS_2 systems, the practical goal is usually **enough CTAB to form a connected mesoporous shell, but not so much that micelles aggregate or block pores** [11] [65] [66] [71].

Confidence level: **High** — multiple independent mesoporous silica studies consistently show CTAB as the micelle-based template that governs mesopore formation, and the same template logic is directly relevant to the silica shell in SiO_2–MoS_2 core-shell systems [11] [65] [66] [67].

References

11. Kim, D.-H., Park, J.Y., Choi, H.S., (...), Baik, J.M. (2025) Advancing Humidity-Resistant Triboelectric Nanogenerators Through MoS_2-Encapsulated SiO_2 Nanoparticles for Self-Powered Gas Sensing Applications. *Advanced Energy Materials*. https://doi.org/10.1002/aenm.202405278

65. Chen, X., Kim, J., Jung, T., (...), Kim, W.-S. (2016) Architecture of Directed-Channel Mesoporous Silica/Titania Shell on Bi-Alkaline-Earth Carbonate Particles for Core-Shell Structure. *ChemistrySelect*. https://doi.org/10.1002/slct.201600768

66. Meng, C., Zhikun, W., Qiang, L., (...), Songqing, H. (2018) Preparation of amino-functionalized Fe3O4@mSiO2 core-shell magnetic nanoparticles and their application for aqueous Fe3+ removal. *Journal of Hazardous Materials*. https://doi.org/10.1016/j.jhazmat.2017.07.062

67. Semeykina, V., Zharov, I. (2022) Medium controlled aggregative growth as a key step in mesoporous silica nanoparticle formation. *Journal of Colloid and Interface Science*. https://doi.org/10.1016/j.jcis.2022.01.166

68. Nugraha, R.E., Fauziyah, N.A., Nurherdiana, S.D., (...), Prasetyoko, D. (2025) Recent strategy on green synthesis of mesoporous silica from waste for a sustainable and circular economy. *Journal of Environmental Chemical Engineering*. https://doi.org/10.1016/j.jece.2025.118288

69. Liu, B., Quan, K., Yang, X., (...), Qiu, H. (2023) Clickable periodic mesoporous organosilicas core-shell particles with radially-oriented mesopores for high-performance liquid chromatography. *Microporous and Mesoporous Materials*. https://doi.org/10.1016/j.micromeso.2023.112785

70. Li, P., Xiong, G., Liu, L., Wang, L. (2013) Investigation on the effect of zeolite precursor on the formation process of MCM-41 containing zeolite y building units. *Spectrochimica Acta - Part A: Molecular and Biomolecular Spectroscopy*. https://doi.org/10.1016/j.saa.2013.01.064

71. Chen, J., Yuan, Z., Chen, F., (...), Qian, L. (2026) Hollow zeolites with interfacial strain for abnormal mid-frequency enhancement in compact loudspeakers. *Nano Today*. https://doi.org/10.1016/j.nantod.2026.103112

72. Poyraz, A.S., Dag, O. (2009) Role of organic and inorganic additives on the assembly of CTAB-P123 and the morphology of mesoporous silica particles. *Journal of Physical Chemistry C*. https://doi.org/10.1021/jp907303a

73. Yan, Shuoyang, Chen, Ling, Zhang, Zhiyang (2025) Utilizing Freeze-Thaw-Ultrasonication to Prepare Mesoporous Silica-Encapsulated Colloidal Silver Nanoaggregates with Long-Term Surface-Enhanced Raman Spectroscopy Activity. *Sensors (Basel, Switzerland)*. https://doi.org/10.3390/s25061840

74. Šoltys, M., Balouch, M., Kašpar, O., (...), Štěpánek, F. (2018) Evaluation of scale-up strategies for the batch synthesis of dense and hollow mesoporous silica microspheres. *Chemical Engineering Journal*. https://doi.org/10.1016/j.cej.2017.11.026

75. Zhao, S., Zhang, Y., Zhou, Y., (...), Fang, J. (2016) One-step synthesis of core-shell structured mesoporous silica spheres templated by protic ionic liquid and CTAB. *Materials Letters*. https://doi.org/10.1016/j.matlet.2016.04.182