Applicant	Shenzhen HonZen Vision Technology Co., Ltd.
Address	4/F Building B, Yili Science Park, Guanhu Street, Longhua District, Shenzhen
Manufacturer	Shenzhen HonZen Vision Technology Co., Ltd.
Address	4/F Building B, Yili Science Park, Guanhu Street, Longhua District, Shenzhen

The following sample(s) was /were submitted and identified on behalf of the clients as ：

Sample Name：	Sports camera
Model Name:	H88, i3, i3s
Trade Name:	N/A
Sample Received Date：	April 2, 2025
Testing Period:	April 2, 2025-April 10, 2025
Report Date:	April 10, 2025

Test Requested and Conclusion(s):

No.	Standard and Requirement	Conclusion(s)
1	RoHS Directive 2011/65 / EU- XRF scanning	PASS
2	RoHS Directive 2011/65/EU and its subsequent amendments (EU) 2015/863- Pb/Cd/Hg/CrVI Content- Polybrominated diphenyl ethers(PBDEs)- Polybrominated biphenyls (PBBs)- Phthalates(Bis(2-ethylhexyl) phthalate (DEHP) , Butyl benzyl phthalate (BBP),Dibutylphthalate (DBP) , and Diisobutyl phthalate (DIBP))	PASS

Test Method	Please refer to next page(s).
Test Result	Please refer to next page(s).
Test conclusion：	Based upon the performed tests by submitted samples, the test results comply with the limits of the RoHS 2.0 Directive (EU) 2015/863 and (EU)2017/2102 amending Annex II to Directive 2011/65/EU.

Signed for and on behalf of



_____

Vivian Jiang

Technical Director

Unless otherwise agreed in writing, this document is issued by the company subject to its general conditions of service printed overleaf, available on request or accessible at http://www.tmc-lab.com. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of TMC, this test report shall not be copied except in full and published as advertisement.

Sample description:

Sample No.	Sample description	Test photo group
1	Cover	
2	Sticker	
3	Double-sided adhesive	
4	Black plastic shell	
5	Magnet	
6	Screw	
7	Tape	
8	Black wire	
9	Red wire	
10	Battery	
11	PCB	
12	White plastic shell	

1. Test results:

XRFScanning-RoHSDirective2011/65/EU

Methods:IEC62321-3-1:2013analysisbyX-rayfluorescencespectrometry(XRF).

Test result(s):

No.	Sample Description	Results of XRF					Chemical confirmation results (mg/kg)	Conclusion
		Pb	Cd	Hg	Cr	Br		
1	Cover	BL	BL	BL	BL	BL	---	PASS
2	Sticker	BL	BL	BL	BL	BL	---	PASS
3	Double-sided adhesive	BL	BL	BL	BL	BL	---	PASS
4	Black plastic shell	BL	BL	BL	BL	BL	---	PASS
5	Magnet	BL	BL	BL	BL	---	---	PASS
6	Screw	BL	BL	BL	BL	---	---	PASS
7	Tape	BL	BL	BL	BL	BL	---	PASS
8	Black wire	BL	BL	BL	BL	BL	---	PASS
9	Red wire	BL	BL	BL	BL	BL	---	PASS
10	Battery	BL	BL	BL	BL	BL	---	PASS
11	PCB	BL	BL	BL	BL	BL	---	PASS
12	White plastic shell	BL	BL	BL	BL	BL	---	PASS

Remark:

a. It is the result on total Br while test item on restricted substances is PBBs/PBDEs. It is the result on total Cr while test item on restricted substances is Cr(VI).

b. The XRF screening test for RoHS elements-The reading may be different to the actual content in the sample be of non-uniformity composition.

c. Results are obtained by EDXRF for primary screening, and further chemical testing by ICP-OES (for Pb, Cd, Hg), UV-VIS for Cr(VI) and GC/MSD (for PBBs/PBDEs) is recommended to be performed if the concentration exceeds the below warming value according to IEC 62321-3-1:2013.

Attached table 1, XRF screening limits in mg/kg in different matrices :

XRF detection limits in mg/kg for regulated elements in various material

Materials	Concentration (mg/kg)				
	Cd	Cr	Pb	Hg	Br
Polymeric	BL≤60<X<140≤OL	BL≤640<X	BL≤670<X<1330≤OL	BL≤660<X<1340≤OL	BL≤290<X
Metallic	BL≤60<X<140≤OL	BL≤640<X	BL≤670<X<1330≤OL	BL≤660<X<1340≤OL	---
Composite materials	BL≤40<X<160≤OL	BL≤440<X	BL≤470<X<1530≤OL	BL≤460<X<1540≤OL	BL≤240<X

Note：

-BL= Below Limit

-OL=Over Limit

-X = inconclusive, the region where need further chemical testing by ICP-OES (for Pb, Cd, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs).

---- = Not Applicable

- mg/kg=0.0001%

- N.D.=Not Detected(<MDL)

- MDL= Method Detection Limit

-Negative = Absence of Cr(VI), the detected Cr(VI) concentration in the boiling water extraction solution is less than 0.02 mg/kg with 50cm2 sample surface area used.

-*=According to 2011/65/EU Annex,point *Lead as an alloying element is steel containing up to 0.35% lead by weight, aluminum containing up to 0.4% lead by weight and as a copper alloy, containing up to 4% lead by weight can be exempted.

2. Pb, Cd, Cr(VI), Hg, PBBs&PBDEs

Test Method:

A. Disassembly, disjointment and mechanical sample preparation

—Ref. to IEC 62321-2:2014, Disassembly, disjointment and mechanical sample preparation.

B. With reference to IEC 62321-1:2013, tests were performed for the samples indicated by the photos in this report.

(1) Screening – Lead, mercury, cadmium, total chromium and total bromine

—Ref. to IEC 62321-3-1:2013, Screening for Lead, mercury, cadmium, total chromium and total bromine by X-ray fluorescence spectrometry.

(2) Wet chemical test method

Test Item(s)	Test Method	Test Equipment	Unit	MDL	Limit
Pb	IEC62321-5:2013	ICP-OES	mg/kg	2	1000
Cd	IEC62321-5:2013	ICP-OES	mg/kg	2	100
Hg	IEC 62321-4:2013 /AMD1:2017	ICP-OES	mg/kg	2	1000
Cr(VI) (Metal)	IEC62321-7-1:2015	UV-Vis	μg/cm2	0.1	0.13
Cr(VI) (Nonmetal)	IEC62321-7-2:2017	UV-Vis	mg/kg	8	1000
PBBs	IEC62321-6:2015	GC-MS	mg/kg	5	100
PBDEs	IEC62321-6:2015	GC-MS	mg/kg	5	1000

PBBs		PBDEs	
Monobromobiphenyl	Hexabromobiphenyl	Monobromodiphenyl ether	Hexabromodiphenyl ether
Dibromobiphenyl	Heptabromobiphenyl	Dibromodiphenyl ether	Heptabromodiphenyl ether
Tribromobiphenyl	Octabromobiphenyl	Tribromodiphenyl ether	Octabromodiphenyl ether
Tetrabromobiphenyl	Nonabromobiphenyl	Tetrabromodiphenyl ether	Nonabromodiphenyl ether
Pentabromobiphenyl	Decabromobiphenyl	Pentabromodiphenyl ether	Decabromodiphenyl ether

3. Phthalates—DBP, BBP, DEHP & DIBP

Test Item(s)	Test Method	Test Equipment	Unit	MDL	Limit
Dibutyl Phthalate(DBP)	IEC62321-8:2017	GC-MS	mg/kg	30	1000
Benzylbutyl Phthalate (BBP)	IEC62321-8:2017	GC-MS	mg/kg	30	1000
Di-(2-ethylhexyl)Phthalate(DEHP)	IEC62321-8:2017	GC-MS	mg/kg	30	1000
Diisobutyl phthalate (DIBP)	IEC62321-8:2017	GC-MS	mg/kg	30	1000

Test result(s):

No.	Test item (mg/kg)				Conclusion
	DBP	BBP	DEHP	DIBP	
1	N.D.	N.D.	N.D.	N.D.	PASS
2	N.D.	N.D.	N.D.	N.D.	PASS
3	N.D.	N.D.	N.D.	N.D.	PASS
4	N.D.	N.D.	N.D.	N.D.	PASS
7	N.D.	N.D.	N.D.	N.D.	PASS
8	N.D.	N.D.	N.D.	N.D.	PASS
9	N.D.	N.D.	N.D.	N.D.	PASS
10	N.D.	N.D.	N.D.	N.D.	PASS
11	N.D.	N.D.	N.D.	N.D.	PASS
12	N.D.	N.D.	N.D.	N.D.	PASS


Note：

- mg/kg=0.0001%


-ND=Not Detected(<MDL)

1.Chemical Test Process:

Test for Cd/Pb Content




2.Test for Hg Content




3. Test for Chromium (VI) Content


Nonmetal material



Metal material



4. Test for PBBs/PBDES/DIBP/DBP/BBP/DEHP Content




Sample photo:

S









END OF REPORT