


## Fragmentation Report

Pile\_2\_processed




<b>Report generated:</b>	2025/05/11 - 09:42
<b>Project name:</b>	Pile_2_processed
<b>Project data:</b>	D:/Elen_opprettet21.10.24/Master/Ballangen/Bilder/Salve 170/25.03/Pile_2_processed.frag

## Project

Project name: Pile\_2\_processed  
Project captured: 2025/02/20 - 10:42

## Fragmentation

Preset:	Blast	X <sub>20</sub> :	181.3 mm
Number of fragments:	3538	X <sub>50</sub> :	325.6 mm
Point spacing:	5.6 mm	X <sub>80</sub> :	528.0 mm
Ground sample distance:	0.7 mm		
Sample limit:	2.1 mm		
Area total:	49 602 008.0 mm <sup>2</sup>		
Area analyzed:	33 974 521.2 mm <sup>2</sup>		



— PSD (measured)  
— GSD = 0.7 mm/px  
— MPS = 5.6 mm  
#Fragments = 3538  
▼ X<sub>20</sub> = 181.3 mm  
◆ X<sub>50</sub> = 325.6 mm  
▲ X<sub>80</sub> = 528.0 mm

Size	Passing
2.1 mm	0.00 %
3.0 mm	0.01 %
4.0 mm	0.03 %
5.0 mm	0.05 %
6.0 mm	0.08 %
7.0 mm	0.10 %
8.0 mm	0.12 %
9.0 mm	0.16 %
10.0 mm	0.19 %
20.0 mm	0.72 %
30.0 mm	1.20 %
40.0 mm	1.64 %
50.0 mm	2.09 %
60.0 mm	2.54 %
70.0 mm	3.09 %
80.0 mm	3.97 %
90.0 mm	4.93 %
100.0 mm	5.99 %
200.0 mm	24.50 %
300.0 mm	43.66 %
400.0 mm	62.22 %
500.0 mm	74.91 %
600.0 mm	86.37 %
700.0 mm	92.20 %
800.0 mm	94.11 %
900.0 mm	98.06 %
1 000.0 mm	99.53 %
1 961.3 mm	100.00 %

Colour mode:

Predefined colour scheme

