

Technical Data Sheet

Clear / light-blue hot-washed rPET flakes - Provisional technical reference

PC-TDS-001 / Version 0.1 / 07 May 2026

The values below reflect a standard production batch of Poly Cleaner's clear/light-blue rPET flakes, produced without customer-specific adjustments. Improved quality parameters can be achieved through tailored sorting and processing, with final specifications agreed according to customer requirements. Technical information for green and mixed-colour grades is available on request.

MATERIAL AND EVIDENCE BASIS

Material: flakes from post-consumer PET bottles, processed by sorting, size reduction, hot washing, separation and drying. The current line uses an approximately 14 mm screen; a current sieve analysis is required to define the delivered size distribution.

Source: Poly Cleaner one full truck test results.xlsx, sheet FLAKE_01, load PBO-IMP-26-00613-1. The record lists 21 big-bags of 1,000 kg. Equal bag weights mean the arithmetic bag mean also equals the bag-mass-weighted mean. The laboratory and actual test date are not explicitly identified; the form header date is not treated as the test date.

Note: The results presented reflect a standard production batch of Poly Cleaner LLC, manufactured without customer-specific process adjustments; improved quality parameters can be achieved through tailored production adjustments to meet customer requirements, subject to technical agreement and validation.

HISTORICAL SHIPMENT RESULTS

Parameter	Unit	Mean	Bag range	Sheet TDS value*
Moisture	%	0.425	0.15-0.67	1.2
PVC	ppm	45.29	0-117	80
Other plastics	ppm	74.02	0-293	50
Polyolefins	ppm	0 recorded	0 recorded	50
Other contamination	ppm	17.26	0-46.5	30
Metal	ppm	0 recorded	0 recorded	20
Glue	ppm	31.48	26.54-38.00	100
Light-blue PET share	%	19.62	9-30	<15

INTERPRETATION

Shipment averages exceed the listed values for PVC, other plastics and light-blue share. PVC exceeds 20 ppm in 12 bags; other plastics exceed 50 ppm in 9 bags. Six bags are marked A and fifteen C; the grade definitions and final cargo release decision are not established by this workbook.

DATA LIMITATIONS AND LOT ACCEPTANCE

Property	Available evidence / required action
Intrinsic viscosity (IV)	IV measured at 0.783 dL/g Sample preparation: pre-drying for 4 hours at 160°C under vacuum.
Bulk density	295 g/l
Particle-size distribution	<3 mm: 4,8% ; >14 mm: 0%
Colour / optical properties	≈ 25%

SPECIFICATION TO BE AGREED BEFORE SUPPLY

Poly Cleaner supplies hot-washed rPET flakes from standard production and offers tailored sorting and processing adjustments to meet customer-specific quality requirements. The test results presented describe the respective tested samples and provide a reference for technical discussions. Final specifications are agreed with each customer, with samples available for evaluation before supply.