intertek
Total Quality. Assured.

TEST REPORT Number : WUXH00124826

Applicant : SHANGHAI HAPPY CHILDREN FACTORY
XIN JIANFENG 1002, JIN YANG VILLAGE,
LANG XIA TOWN, JIN SHAN DISTRICT, SHANGHAI

Date : Jan 21, 2022

Sample Description:

One (1) Piece Of Submitted Sample Said To Be :

Item Name	:	**Battery Operated Ride-On Car**
Item No.	:	**Vespa PX A003**
Packaging Provided	:	**Yes**
Labelled Age Group	:	37-95 Months
Country Of Origin	:	China

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(s).

Prepared And Checked By:
For Intertek Testing Services Wuxi Ltd.

Peter Chen
General Manager

INTERTEK TESTING SERVICES WUXI LTD. 无锡天祥质量技术服务有限公司 检验检测专用章

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Conclusion:

Tested Sample	Standard	Result
Submitted Sample	EN71-1: 2014+ A1: 2018 For Mechanical And Physical Properties	Pass
Submitted Sample	EN71-2: 2020 Flammability Test	Pass
Submitted Sample	EN IEC 62115:2020+A11:2020- Safety of Electric Toys Excluding the Clause 15.1.2 ,15.4, 19, Annex C, Annex E ,Annex I	Pass (Subjected to Remark enclosed)
Tested Components Of Submitted Sample	EN 71-3:2019+A1:2021 On Migration Of Certain Elements	Pass
Tested Components Of Submitted Sample	EN 71-3:2019 On Migration Of Certain Elements	Pass
Tested Components Of Submitted Sample	EN 71-3: 2019 on migration of certain elements & EU 2019/1922 amending 2009/48/EC (effective from May, 20,2021) for Aluminium (Al) migration	Pass
Tested Components Of Submitted Sample	Phthalates content requirement in Annex XVII Items 52 of the REACH Regulation (EC) No. 1907/2006 & Amendment No. 552/2009 (formerly known as Directive 2005/84/EC)	Pass
Tested Components Of Submitted Sample	Phthalates content requirement in Annex XVII Item 51of the REACH Regulation (EC) No. 1907/2006 & Amendment No. 552/2009 & Amendment Commission Regulation (EU) 2018/2005 (formerly known as Directive 2005/84/EC)	Pass

Prepared And Checked By:
For Intertek Testing Services Wuxi Ltd.

Peter Chen
General Manager

INTERTEK TESTING SERVICES WUXI LTD. 无锡天祥质量技术服务有限公司 检验检测专用章

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

1 Mechanical and Physical Test

As Per European Standard on Safety of Toys EN71-1: 2014+ A1: 2018.

Applicant's Specified Age Group for Testing: For 37 - 95 Months.

The submitted samples were undergone the following abuse tests:		
Test	Clause	Parameter
Torque Test	8.3	0.34 Nm
Tension Test	8.4.2.1	90 N
Protective Components	8.4.2.3	60 N
Tip over test	8.6	Three times
Impact Test	8.7	1 kg
Compression Test	8.8	110 N
Flexibility of Metallic Wires	8.13	70 N

Clause	Testing Items	Assessment
4	General Requirements	
4.1	Material	P
4.2	Assembly	P
4.3	Flexible plastic sheeting	NA
4.4	Toy bags	NA
4.5	Glass	NA
4.6	Expanding materials	NA
4.7	Edges	P
4.8	Points and metallic wires	P
4.9	Protruding parts	P
4.10	Parts moving against each other	NA
4.11	Mouth actuated toys and other toys intended to be put in the mouth	NA
4.12	Balloons	NA
4.13	Cords of toy kites and other flying toys	NA
4.14	Enclosures	NA
4.15	Toys intended to bear the mass of a child	P
4.16	Heavy immobile toys	NA
4.17	Projectile toys	NA
4.18	Aquatic toys and inflatable toys	NA
4.19	Percussion caps specifically designed for use in toys and toys using percussion caps	NA
4.20	Acoustics	P

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Clause	Testing Items	Assessment
4.21	Toys containing a non-electrical heat source	NA
4.22	Small balls	NA
4.23	Magnets	NA
4.24	Yo-yo balls	NA
4.25	Toys attached to food	NA
4.26	Toy disguise costumes	NA
4.27	Flying toys	NA
5	Toys intended for Children under 36 Months	
5.1	General requirements	NA
5.2	Soft-filled toys and soft-filled parts of a toy	NA
5.3	Plastic sheeting	NA
5.4	Cords, chains and electrical cables in toys	NA
5.5	Liquid filled toys	NA
5.6	Speed limitation of electrically-driven ride-on toys	NA
5.7	Glass and porcelain	NA
5.8	Shape and size of certain toys	NA
5.9	Toys comprising monofilament fibres	NA
5.10	Small balls	NA
5.11	Play figures	NA
5.12	Hemispheric-shaped toys	NA
5.13	Suction cups	NA
5.14	Straps intended to be worn fully or partially around the neck	NA
5.15	Sledges with cords for pulling	NA
6	Packaging	P
7	Warnings, markings and instructions for use	
7.1	General	P
7.2	Toys not intended for children under 36 months	P
7.3	Latex balloons	NA
7.4	Aquatic toys	NA
7.5	Functional toys	NA
7.6	Hazardous sharp functional edges and points	NA
7.7	Projectile toys	NA
7.8	Imitation protective masks and helmets	NA
7.9	Toy kites	NA
7.10	Roller skates, inline skates and skateboards and certain other ride-on toys	P
7.11	Toys intended to be strung across a cradle, cot, or perambulator	NA

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

Clause	Testing Items	Assessment
7.12	Liquid-filled teethers	NA
7.13	Percussion caps specifically designed for use in toys	NA
7.14	Acoustics	NA
7.15	Toy bicycles	NA
7.16	Toys intended to bear the mass of a child	NA
7.17	Toys comprising monofilament fibres	NA
7.18	Toy scooters	NA
7.19	Rocking horses and similar toys	NA
7.20	Magnetic/electrical experimental sets	NA
7.21	Toys with electrical cables exceeding 300 mm in length	NA
7.22	Toys with cords or chains intended for children of 18 months and over but under 36 months	NA
7.23	Toys intended to be attached to a cradle, cot or perambulator	NA
7.24	Sledges with cords for pulling	NA
7.25	Flying toys	NA
7.26	Improvised projectiles	NA

Remark: P = Pass NA = Not Applicable

Remark: Additional information according to the Toy Safety Directives 2009/48/EC requirement. These information also appears as a note within the EN 71 but are not standard requirements:

1. Marking

The manufacturer's and importer's name, registered trade name or registered trade mark, the address and the CE-marking shall be indicated on the toy or, where that is not possible, on its packaging or in a document accompany the toy. In addition, manufacturers shall ensure that their toys bear a type, batch, serial or model number or other element allowing their identification, or where the size or nature of the toy does not allow it, that the required information is provided on the packaging or in a document accompanying the toy.

After checking, it was found that:

	Toy	Packaging
Manufacturer's name	Absent	Present
Manufacturer's address	Absent	Absent
Importer's name	Absent	Absent
Importer's address	Absent	Absent
Product identification code	Absent	Present
CE-marking	Absent	Absent

Below is additional information checking according to the UK Toy (Safety) Regulations requirement.

Marking

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

The manufacturer's and importer's name, registered trade name or registered trademark, the address and type, batch, serial or model number or other element allowing their identification shall be indicated on the product itself.

After checking, it was found that:

	Toy	Packaging
Name of authorised representative in Great Britain	Absent	Absent
Address of authorised representative in Great Britain	Absent	Absent
Product identification code	Absent	Present

With reference to the guidance of using UKCA marking from 1 January 2021 by the Department for Business, Energy and Industrial Strategy published on 1 September 2020.

After checking UKCA marking, it was found that:

	Toy	Packaging
UKCA marking	Absent	Absent

Date Sample Received: Jan 06, 2022&Jan 21, 2022
Testing Period: Jan 06, 2022 To Jan 21, 2022

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

2 Flammability Test

As per European Standard on Safety of Toys EN71-2: 2020

Clause	Testing Items	Assessment
4.1	General	P
4.2	Toys to be worn on the head	
4.2.2	Beards, moustaches, wigs, etc., made from pile or flowing elements which protrude 50 mm or more from the surface of the toy	NA
4.2.3	Beards, moustaches, wigs, etc., made from pile or flowing elements which protrude less than 50 mm from the surface of the toy	NA
4.2.4	Full or partial moulded head masks	NA
4.2.5	Toys to be worn on the head	NA
4.3	Toy Disguise Costumes and Toys Intended to be Worn by a Child in Play	NA
4.4	Toys Intended to be Entered by a Child	NA
4.5	Soft Filled Toys	NA

Remark : P = Pass NA = Not Applicable

Date Sample Received: Jan 06, 2022
Testing Period: Jan 06, 2022 To Jan 21, 2022

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

3 Safety of Electric Toys

As per European Standard on Safety of Electric Toys EN IEC 62115:2020+A11:2020

Applicant's Specified Age Group for Testing: For 37-95 months.

Power source: Vehicle: 12 V, 4.5 Ah, Lead-acid rechargeable battery x 1 pc (Non- Replaceable)

Charger: type: Input 220-240V A.C. Output 12 V D.C. (Provided)
Model: FLH480608

Electric Operated Function: Battery powered sound, LED light, motion.

Clause	Requirement	Assessment
1	Scope	--
2	Normative reference	--
3	Term and definitions	--
4	General requirement	--
5	General conditions for test	--
6	Criteria for reduced testing	NA
6.1	General	--
6.2	Short-circuit resistance	NA
6.3	Low power electric toys	NA
6.4	Battery circuits	NA
7	Marking and instructions	P
7.1	General	P
7.2	Marking on electric toys	P
7.2.1	Identification	See remark(1)
7.2.2	Electric toys with replaceable batteries	NA
7.2.3	Transformer toys and power supply toys	NA
7.2.4	Electric toys with more than one power supply	NA
7.2.5	Electric toys with detachable lamps	NA
7.2.6	Symbols	NA
7.2.7	Durability	P
7.3	Instructions and markings on packaging	P
7.3.1	General	P
7.3.2	Transformer toys and power supply toys	P
7.3.3	Electric toys that are used with replaceable batteries	P
7.3.3.1	General	P
7.3.3.2	Coin batteries	NA
7.3.3.3	Button batteries	NA
7.4	Instructions for electric toys that can be connected to class I equipment	NA
7.5	Instructions for ride-on electric toys	P
7.6	Temperature warnings	NA
8	Power input	NA
9	Heating and abnormal operation	P
9.1	General	P

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

Clause	Requirement	Assessment
9.2	Test condition	--
9.3	Normal operation	P
9.4	Normal operation with insulation short-circuited	P
9.5	Abnormal operation with temperature controls made inoperable	NA
9.6	With accessible moving parts locked	P
9.7	Additional transformers and power supplies	NA
9.8	Abnormal supply to electric toys via a USB connection.	NA
9.9	Fault condition in electronic circuits	P
9.10	Compliance criteria	P
10	Electric strength	P
10.1	Electric strength at operating temperature	P
10.2	Electric strength under humid conditions	P
11	Electric toys used in water, electric toys used with liquid and electric toys cleaned with liquid	NA
12	Mechanical strength	P
12.1	Enclosures	P
12.2	Attachment strength	P
13	Construction	P
13.1	Nominal supply voltage	P
13.2	Transformers, power supplies and battery chargers	P
13.3	Thermal cut-outs.	NA
13.4	Batteries	P
13.4.1	Small batteries	NA
13.4.2	Other batteries	P
13.4.3	Electrolyte leakage	P
13.4.4	Electric toys placed above a child	NA
13.4.5	Parallel connection of batteries	NA
13.4.6	Battery compartment fasteners	P
13.5	Plug and sockets	P
13.6	Charging batteries	P
13.7	Series motors	NA
13.8	Working voltage	NA
13.9	Electric toys connecting to other equipment.	NA
13.10	Speed limitation of ride-on electric toys	P
14	Protection of cords and wires	P
14.1	Edges and moving parts	P
14.2	Fixed parts	NA
15	Components	See remark(2&3)
15.1.1	General	--
15.1.2	Switches and automatic controls	See remark(3)
15.1.3	Other components	See remark(2)
15.2	Prohibited components	P
15.3	Transformers and power supplies	NA
15.4	Battery chargers	See remark(2)
15.5	Batteries	NA

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

Clause	Requirement	Assessment
16	Screws and connections	P
16.1	Fixings	P
16.2	Connections	P
17	Clearances and creepage distances	P
18	Resistance to heat and fire	P
18.1	Resistance to heat	P
18.2	Resistance to fire	P
18.2.1	General	P
18.2.2	Non-metallic parts	P
18.2.3	Insulating material	NA
19	Radiation and similar hazards	See remark(3)
19.1	General	--
19.2	Optical radiation Toys incorporating lasers and or light emitting diodes (LED) or UV emitting lamps shall comply with Annex E. Electric toys incorporating LEDs shall comply with 19.E.2. Electric toys incorporating lasers shall comply with 19.E.3 Electric toys incorporating UV-emitting lamps shall comply with 19.E.4	See remark(3)
19.3	Other electromagnetic radiation Electric toys with an integrated field source that may produce harmful electromagnetic radiation Measurements methods are given in Annex I.	See remark(3)
Annex A	Experimental sets	NA
Annex B	Needle-flame test	NA
Annex C	Automatic controls and switches	See remark(3)
Annex D	Electric toys with protective electronic circuits	NA
Annex E	Safety of electric toys incorporating optical radiation sources	See remark (3)
Annex F	Flowcharts showing the assessment of optical radiation safety of LEDs in electric toys	--
Annex G	Examples of calculations on LEDs	--
Annex H	Explanation of the principles used for the requirements of Annex E	--
Annex I	Electric toys generationg electromagnetic fields (EMF)	See remark (3)
Annex J	Safety of remote controls for electric ride-on toys	NA
Annex K	Flow charts showing the application of Clause 9	--

Abbreviation: P = Pass NA = Not Applicable

Remark:

(1) Below are additional information according to the requirement in Toy Safety Directive 2009/48/EC relating to marking of toys and do not constitute requirements of this European Standard:
The manufacturer's and importer's name, registered trade name or registered trade mark, the address and type, batch, serial or model number or other element allowing their identification shall be indicated on the toy or, where that is not possible, on its packaging or in a document accompanying the toy.
After checking, it was found that:

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

	Toy	Packaging
Manufacturer's name	Absent	Present
Manufacturer's address	Absent	Absent
Importer's name	Absent	Absent
Importer's address	Absent	Absent
Product identification code	Absent	Present

(2) Applicant needs to ensure that components used in toys shall comply with the safety requirements specified in the relevant standards.

Applicant needs to ensure that battery charger for toys shall comply with IEC 60335-2-29:2016 and Annex AA of that standard.

(3) As requested by the applicant, the Annex E, Annex C, Annex I were not assessed.

Date Sample Received: Jan 06, 2022&Jan 21, 2022
Testing Period: Jan 06, 2022 To Jan 21, 2022

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number： WUXH00124826

Tests Conducted (As Requested By The Applicant)
4 19 Toxic Element Migration Test

(A) Test Result

As per EN 71-3:2019+A1:2021 and followed by Inductively Coupled Plasma Atomic Emission Spectrometry, Inductively Coupled Argon Mass Spectrometry, Ion Chromatography- Inductively Coupled Plasma-Mass Spectrometry, Ion Chromatography with UV-VIS and Gas Chromatographic - Mass Spectrometry.

Category (III)：Scraped-off toy material

Element	Result (mg/kg)					Reporting Limit (mg/kg)	Limit (mg/kg)
	(1)	(2)	(3)	(4)	(5)		
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr III) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin ++	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Reporting Limit (mg/kg)	Limit (mg/kg)
	(6)	(7)	(8)	(9)	(10)		
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr III) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin ++	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Reporting Limit (mg/kg)	Limit (mg/kg)
	(11)	(12)	(13)	(14)	(15)		
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	75	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr III) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin ++	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	137	ND	ND	100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Reporting Limit (mg/kg)	Limit (mg/kg)
	(16)	(17)	(18)	(19)	(20)		
Aluminium (Al)	ND	ND	ND	804	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	31	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr III) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin ++	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	878	100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Reporting Limit (mg/kg)	Limit (mg/kg)
	(21)	(22)	(23)	(24)	(25)		
Aluminium (Al)	ND	ND	ND	ND	325	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	21	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr III) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin ++	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Reporting Limit (mg/kg)	Limit (mg/kg)
	(26)	(27)	(28)	(29)	(30)		
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr III) #	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr VI)	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	2.5	180000
Organic tin ++	ND	ND	ND	ND	ND	5	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000

Remark : mg/kg = milligram per kilogram
++ = Unless the test results were marked with "Δ", Organic tin contents were not directly determined and were derived from migration results of total tin.
- Organic tin test result was expressed as tributyl tin.
ND = Not Detected (less than reporting limit)
# = The reported value of migration of Chromium (III) = migration value of total Chromium – migration value of Chromium(VI).
Δ = Confirmation test was performed on the tested component. The reported value was the sum of the migration values of Dimethyl tin, Methyl tin, Butyl tin, Dibutyl tin, Tributyl tin, Tetrabutyl tin, n-Octyl tin, Di-n-octyl tin, Di-n-propyl tin, Diphenyl tin and Triphenyl tin after converted to Tributyl tin by calculation. Other Organic tin compounds may be also be present in sample as stated in EN 71-3:2019+A1:2021.

Tested Component：See Component List In The Last Section Of This Report.

The pH after the migration of tested components (24),(25) outside the range of 1.1 to 1.3

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

(B) Categories of various toy materials

Category I：Dry, brittle, powder like or pliable

Solid toy material from which powder-like material is released during playing and semi-solid materials that may also leave residues on the hands during play. The material can be ingested. Contamination of the hands with the material may contribute to the oral exposure of the material. (e.g. the cores of colouring pencils, chalk, crayons, modelling clays and plaster).

Category II：Liquid or sticky

Fluid or viscous toy material, which can be ingested or to which dermal exposure may occur during playing. (e.g. liquid paints, finger paints, liquid ink in pens, glue sticks, slimes, bubble solution).

Category III：Scraped-off

Solid toy material with or without a coating, which can be ingested as a result of biting, tooth scraping, sucking or licking. (e.g. coatings, lacquers, plastics, paper, textiles, glass, ceramic, metallic, wooden, bone, leather and other materials).

Date Sample Received: Jan 06, 2022
Testing Period: Jan 06, 2022 To Jan 21, 2022

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number： WUXH00124826

Tests Conducted (As Requested By The Applicant)
5 19 Toxic Elements Migration Test

(A) Test Result

As per EN 71-3:2019 and followed by Inductively Coupled Plasma Atomic Emission Spectrometry, Inductively Coupled Argon Mass Spectrometry, Ion Chromatography- Inductively Coupled Plasma-Mass Spectrometry, and Gas Chromatographic - Mass Spectrometry.

Category (III)：Scraped-off toy material

Element	Result (mg/kg)					Limit (mg/kg)
	(1)	(2)	(3)	(4)	(5)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ++	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ++	< 0.025	< 0.025	< 0.025	< 0.025#	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ++	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Limit (mg/kg)
	(6)	(7)	(8)	(9)	(10)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ++	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ++	< 0.025	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ++	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

Element	Result (mg/kg)					Limit (mg/kg)
	(11)	(12)	(13)	(14)	(15)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	75	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ++	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ++	< 0.025	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ++	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	137	< 100	< 100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Limit (mg/kg)
	(16)	(17)	(18)	(19)	(20)	
Aluminium (Al)	< 300	< 300	< 300	804	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	31	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ++	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ++	< 0.025	< 0.025	< 0.025	< 0.025#	< 0.025#	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ++	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	878	46000

Element	Result (mg/kg)					Limit (mg/kg)
	(21)	(22)	(23)	(24)	(25)	
Aluminium (Al)	< 300	< 300	< 300	< 300	325	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	21	<10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ++	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ++	< 0.025	< 0.025	< 0.025#	< 0.025#	< 0.025#	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ++	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

Element	Result (mg/kg)					Limit (mg/kg)
	(26)	(27)	(28)	(29)	(30)	
Aluminium (Al)	< 300	< 300	< 300	< 300	< 300	70000/28130◎
Antimony (Sb)	< 10	< 10	< 10	< 10	< 10	560
Arsenic (As)	< 10	< 10	< 10	< 10	< 10	47
Barium (Ba)	< 10	< 10	< 10	< 10	< 10	18750
Boron (B)	< 50	< 50	< 50	< 50	< 50	15000
Cadmium (Cd)	< 5	< 5	< 5	< 5	< 5	17
Chromium (III) (Cr III) ++	< 10	< 10	< 10	< 10	< 10	460
Chromium (VI) (Cr VI) ++	< 0.025	< 0.025	< 0.025	< 0.025	< 0.025	0.053
Cobalt (Co)	< 10	< 10	< 10	< 10	< 10	130
Copper (Cu)	< 10	< 10	< 10	< 10	< 10	7700
Lead (Pb)	< 10	< 10	< 10	< 10	< 10	23
Manganese (Mn)	< 10	< 10	< 10	< 10	< 10	15000
Mercury (Hg)	< 10	< 10	< 10	< 10	< 10	94
Nickel (Ni)	< 10	< 10	< 10	< 10	< 10	930
Selenium (Se)	< 10	< 10	< 10	< 10	< 10	460
Strontium (Sr)	< 100	< 100	< 100	< 100	< 100	56000
Tin (Sn)	< 10	< 10	< 10	< 10	< 10	180000
Organic tin ++	< 3.0	< 3.0	< 3.0	< 3.0	< 3.0	12
Zinc (Zn)	< 100	< 100	< 100	< 100	< 100	46000

Remark：mg/kg = Milligram per kilogram
++ = Unless the test results were marked with "#" or "Δ", Chromium (III) & Chromium (VI) and Organic tin contents were not directly determined and were derived from migration results of total chromium and tin respectively.

- Organic tin test result was expressed as tributyl tin.

◎ = The new Aluminium (Al) migration limit [2250mg/kg for Category (I), 560mg/kg for Category (II), 28130mg/kg for Category (III)] was quoted from directive (EU) 2019/1922 amending 2009/48/EC effective from 20 May 2021.

= Confirmation of Chromium (VI) test was performed on the tested component. And the reported value of migration of Chromium (III) = migration value of total Chromium – migration value of Chromium(VI).

Δ = Confirmation test was performed on the tested component. The reported value was calculated by summation of the migration values of Methyl tin, Dimethyl tin, Dibutyl tin, Tributyl tin, Tetrabutyl tin, n-Octyl tin, Di-n-octyl tin, Di-n-propyl tin, Diphenyl tin, Monobutyl tin and Triphenyl tin. Other Organic tin compounds may be also be present in sample as stated in EN 71-3:2019.

The pH after the migration of tested components (24),(25)were outside the range of 1.1 to 1.3.

Tested Component：See Component List In The Last Section Of This Report.

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

(B) Categories of various toy materials

Category I：Dry, brittle, powder like or pliable

Solid toy material from which powder-like material is released during playing and semi-solid materials that may also leave residues on the hands during play. The material can be ingested. Contamination of the hands with the material may contribute to the oral exposure of the material. (e.g. the cores of colouring pencils, chalk, crayons, modelling clays and plaster).

Category II：Liquid or sticky

Fluid or viscous toy material, which can be ingested or to which dermal exposure may occur during playing. (e.g. liquid paints, finger paints, liquid ink in pens, glue sticks, slimes, bubble solution).

Category III：Scraped-off

Solid toy material with or without a coating, which can be ingested as a result of biting, tooth scraping, sucking or licking. (e.g. coatings, lacquers, plastics, paper, textiles, glass, ceramic, metallic, wooden, bone , leather and other materials).

Date Sample Received: Jan 06, 2022
Testing Period: Jan 06, 2022 To Jan 21, 2022

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

6 Phthalate Content

With reference to ISO 8124-6: 2018 method A or C, by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(1+2+3)	(4+5+6)	(Max.)
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	-
Diisononyl phthalate (DINP)	28553-12-0/ 68515-48-0	ND	ND	-
Diisodecyl phthalate (DIDP)	26761-40-0/ 68515-49-1	ND	ND	-
Sum of DINP, DNOP and DIDP	--	ND	ND	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(7+8+9)	(10+11+12)	(Max.)
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	-
Diisononyl phthalate (DINP)	28553-12-0/ 68515-48-0	ND	ND	-
Diisodecyl phthalate (DIDP)	26761-40-0/ 68515-49-1	ND	ND	-
Sum of DINP, DNOP and DIDP	--	ND	ND	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(13)	(14)	(Max.)
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	-
Diisononyl phthalate (DINP)	28553-12-0/ 68515-48-0	ND	ND	-
Diisodecyl phthalate (DIDP)	26761-40-0/ 68515-49-1	ND	ND	-
Sum of DINP, DNOP and DIDP	--	ND	ND	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(15+16+18)	(17)	(Max.)
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	-
Diisononyl phthalate (DINP)	28553-12-0/ 68515-48-0	ND	ND	-
Diisodecyl phthalate (DIDP)	26761-40-0/ 68515-49-1	ND	ND	-
Sum of DINP, DNOP and DIDP	--	ND	ND	0.1

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number： WUXH00124826

Tests Conducted (As Requested By The Applicant)

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(21)	(22)	(Max.)
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	-
Diisononyl phthalate (DINP)	28553-12-0/ 68515-48-0	ND	ND	-
Diisodecyl phthalate (DIDP)	26761-40-0/ 68515-49-1	ND	ND	-
Sum of DINP, DNOP and DIDP	--	ND	ND	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(27+28)	(29+30)	(Max.)
Di-n-octyl phthalate (DnOP)	117-84-0	ND	ND	-
Diisononyl phthalate (DINP)	28553-12-0/ 68515-48-0	ND	ND	-
Diisodecyl phthalate (DIDP)	26761-40-0/ 68515-49-1	ND	ND	-
Sum of DINP, DNOP and DIDP	--	ND	ND	0.1

The above limit was quoted according to Annex XVII Item 52 of the REACH Regulation (EC) No. 1907/2006 & Amendment No. 552/2009 for phthalate content in toys and childcare articles.

Remark：Detection Limit = 0.01%(w/w)
ND = Not Detected

@ = As requested by the applicant, the surface coatings were tested with the substrate for phthalate test. With the consideration of the dilution factor, the testing result may not represent the result of the individual coatings and substrate.

Tested Component：See Component List In The Last Section Of This Report.

Date Sample Received: Jan 06, 2022
Testing Period: Jan 06, 2022 To Jan 21, 2022

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number : WUXH00124826

Tests Conducted (As Requested By The Applicant)

7 Phthalate Content

With reference to ISO 8124-6: 2018 method A or C, by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(1+2+3)	(4+5+6)	(Max.)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	-
Diethyl hexyl phthalate (DEHP)	117-81-7	ND	ND	-
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	-
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	-
Sum of DBP,DEHP,BBP and DIBP	--	ND	ND	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(7+8+9)	(10+11+12)	(Max.)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	-
Diethyl hexyl phthalate (DEHP)	117-81-7	ND	ND	-
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	-
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	-
Sum of DBP,DEHP,BBP and DIBP	--	ND	ND	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(13)	(14)	(Max.)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	-
Diethyl hexyl phthalate (DEHP)	117-81-7	ND	0.02	-
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	-
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	-
Sum of DBP,DEHP,BBP and DIBP	--	ND	0.02	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(15+16+18)	(17)	(Max.)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	-
Diethyl hexyl phthalate (DEHP)	117-81-7	ND	ND	-
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	-
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	-
Sum of DBP,DEHP,BBP and DIBP	--	ND	ND	0.1

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number： WUXH00124826

Tests Conducted (As Requested By The Applicant)

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(21)	(22)	(Max.)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	-
Diethyl hexyl phthalate (DEHP)	117-81-7	ND	ND	-
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	-
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	-
Sum of DBP,DEHP,BBP and DIBP	--	ND	ND	0.1

Tested Compound	CAS No.	Result (%,w/w)		Limit (%,w/w)
		(27+28)	(29+30)	(Max.)
Dibutyl phthalate (DBP)	84-74-2	ND	ND	-
Diethyl hexyl phthalate (DEHP)	117-81-7	ND	ND	-
Benzyl butyl phthalate (BBP)	85-68-7	ND	ND	-
Diisobutyl phthalate (DIBP)	84-69-5	ND	ND	-
Sum of DBP,DEHP,BBP and DIBP	--	ND	ND	0.1

The above limit was quoted according to Annex XVII Item 51of the REACH Regulation (EC) No. 1907/2006 & Amendment No. 552/2009& Amendment Commission Regulation (EU) 2018/2005 for phthalate content in articles.

Remark：Detection Limit = 0.01%(w/w)
ND = Not Detected

@ = As requested by the applicant, the surface coatings were tested with the substrate for phthalate test. With the consideration of the dilution factor, the testing result may not represent the result of the individual coatings and substrate.

Tested Component：See Component List In The Last Section Of This Report.

Date Sample Received: Jan 06, 2022
Testing Period: Jan 06, 2022 To Jan 21, 2022

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)

Photo

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司

No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101

Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

TEST REPORT Number： WUXH00124826

Tests Conducted (As Requested By The Applicant)

The Sample Were Submitted By Client's, Only For Reference.

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司

No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101

Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com

Tests Conducted (As Requested By The Applicant)
Components List:

(1) Pink plastic(body).
(2) Bright black plastic(body/beside button).
(3) Black plastic(tail body/foot rest/training wheel hub/connected part of training wheel).
(4) Black plastic(key/key hole).
(5) Transparent plastic(front light).
(6) Red transparent plastic(tail light).
(7) Transparent plastic(instrument panel).
(8) Black plastic(music player button/button,button base beside handlebar).
(9) Beige synthetic leather(seat).
(10) Dark grey plastic(accelerator pedal).
(11) Black plastic(wheel/training wheel).
(12) Black plastic(charger).
(13) Black plastic with white printing(button).
(14) Black plastic excluding bright silver coating(body,wheel hub).
(15) Black soft plastic(handlebar).
(16) Black soft plastic(wheel antiskid part).
(17) Black,white soft plastic(charger wire).
(18) Black soft plastic(charger wire end).
(19) Bright silver coating on plastic(body,wheel hub).
(20) Black coating on metal(connected part of front wheel).
(21) White adhesive plastic film with black printing(charger).
(22) Transparent adhesive plastic film with black printing(music player).
(23) Silver,black soft plastic with transparent adhesive(body sticker).
(24) White adhesive paper with red,black printing(warning sticker).
(25) White adhesive paper with yellow,black printing(warning sticker).
(26) White adhesive plastic film with green,dark blue printing(front logo).
(27) White Plastic.
(28) Blue Plastic.
(29) Red Plastic.
(30) Black Plastic.

End of Report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band w = U) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.
The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) received and tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Wuxi Ltd.

Intertek Testing Services Wuxi Ltd.
无锡天祥质量技术服务有限公司
No.8 Fubei Road, Xishan Economic Development Zone, Wuxi, Jiangsu, China. 214101
江苏省无锡市锡山经济开发区府北路 8 号 214101
Tel: +86 510 8821 4567
Fax: +86 510 8820 0428
www.intertek.com.cn
www.intertek.com