

RJR INTER-OFFICE MEMORANDUM

Subject: Weekly Highlights

Date: August 24, 1983

To: Mr. J. D. Phillips

From: J. P. Wheeler
Materials Technology

ITEM FOR WEEKLY BRIEF

1. Cigarette Inks

A new cigarette monogram ink has been implemented on CAMEL Filter cigarettes being run on the Protos Makers in Manufacturing. J. M. Fry's #85966 ink, specially made for this brand, was tested on the Protos, and is now approved for all CAMEL gold ink applications.

2. Coresta Porosity Measurements

A study has been completed on a method to standardize the Phobos meters used by RJR to measure porosity of paper materials. The experimental head, which has been modified, will reproduce readings to within $\pm 1\%$ in a range from 1,000 to 33,000 Coresta. This does not mean, however, that the paper test heads will reproduce this closely. All information will be communicated to TRG, an outside company contracted to build Phobos instruments in the future. An additional comparison/correlation study is underway with the Phobos, Filtrona PPM200 and Filtrona PPM100. This study is using cigarette papers, tipping papers, and porous plug wraps. A show and tell is planned to demonstrate the pros and cons of each instrument.

GENERAL ITEMS

1. Mobil Films' Plant Tour

A visit was made by personnel in Materials Technology Division (B. P. Bradford, D. Petticord, M. J. Smith, and G. A. Smith) to Mobil Films in Macedon, N. Y. for the purpose of touring their Production, QA, and R&D facilities. Discussions were held regarding future RJRT needs and Mobil's part in their development.

2. Intermediate Plug Wraps

Two intermediate plug wraps 28 and 45-M1 will be tested on CAMEL Filter as a vehicle for 'tar' reduction. The current configuration uses 626 plug wrap. Currently, the 'tar' level is 1 mg. above target.

3. SALEM Ultra Light 100

SALEM Ultra Light 100 has recently experienced high 'tar' and high ventilation variability. The high ventilation variability seems to have stemmed from flaps on the leading edge of the tipping. We will be testing bobbin laser tipping from Golden Belt on August 24. Archer will be submitting Reverse Grind (trailing edge tipping) on September 6. Currently, the product is using rewound 3200 cp tipping from Archer, however, they have asked that this rewound tipping not be looked at as a long-term solution to the problem.

xc: Applied R&D Managers


J. P. Wheeler

50492 3009