

BEMFORM

Insulation Type

Base Coat : Polyvinylacetal Conductor

Bonding Layer : -

Lubricant : Available

<u>Standard</u> <u>Layer and Size Range</u>

 IEC 60317 - 18 Grade 1 $3 \le m \le 20$ mm²

 DIN EN 60317 - 18 Grade 2 $3 \le m \le 20$ mm²

 NEMA MW 18 C

Application Fields

* Transformers (especially oil immersed type)

Properties

Technical Characteristics

Thermal		
Thermal Index	°C	120
Heat Shock	°C	> 155
Electrical		
Breakdown Voltage	V	2 x IEC Value
Chemical		
Resistance to Solvent	Н	5 H
Resistance to Transformer Oil		Very Good
resistance to Transform	ei Oii	very dood
Mechanical	ei Oii	very dood
	ei Oii	Very Good