

|                                                                                   |                                                             |                                     |
|-----------------------------------------------------------------------------------|-------------------------------------------------------------|-------------------------------------|
|  | <b>DOCUMENT TITLE:</b><br>Suspension Quality Control Report | <b>Revision:</b><br>A               |
|                                                                                   | <b>DOCUMENT #:</b><br>TMP1-QC-C.SLQ001                      | <b>Effective Date:</b><br>23Sep2022 |

#### General Production Information

|                       |                          |                                           |                                                |
|-----------------------|--------------------------|-------------------------------------------|------------------------------------------------|
| <b>Work Order #:</b>  | 2502-01                  | <b>NCMR #:</b>                            | None                                           |
| <b>Part Number:</b>   | C.SLQ001                 | <b>Manufacture &amp; Expiration Date:</b> | Mfg date: 12 Feb 2025<br>Exp date: 12 Feb 2027 |
| <b>Part Revision:</b> | <del>C</del> B <i>BW</i> | <b>Batch / Lot #:</b>                     | 2502-01-2                                      |

03 Apr 2025

#### Supplies Traceability

| Part Number | Description     | Part Revision | Lot / Batch # |
|-------------|-----------------|---------------|---------------|
| S.SLQ005    | pH Strip        | A             | 10BDH4801     |
| S.SLQ006    | Deuterium oxide | A             | M2338         |

#### Equipment Traceability

| Part Number | Description    | Equipment ID | Calibration Due Date |
|-------------|----------------|--------------|----------------------|
| E.SLQ013    | Weighing scale | ST-012       | 02 Aug 2025          |

#### QC Data

| Sample Tube | Weight Empty (g) | Weight with Residue (g) | Residue Net Weight (g) |
|-------------|------------------|-------------------------|------------------------|
| Sample A1   | 13.022           | 13.153                  | 0.131                  |
| Sample A2   | 12.899           | 13.032                  | 0.133                  |
| Sample B1   | 12.935           | 13.066                  | 0.131                  |
| Sample B2   | 12.856           | 12.984                  | 0.128                  |
| Sample C1   | 12.922           | 13.052                  | 0.13                   |
| Sample C2   | 12.894           | 13.029                  | 0.135                  |



**DOCUMENT TITLE:**  
Suspension Quality Control Report

**Revision:**  
A

**DOCUMENT #:**  
TMP1-QC-C.SLQ001

**Effective Date:**  
23Sep2022

| Sample Tube                   | Weight Empty (g) | Weight with Sample suspended (g) | Weight with Residue on Evaporation (g) | Residue on Evaporation (%) |
|-------------------------------|------------------|----------------------------------|----------------------------------------|----------------------------|
| Suspension Test Sample        | 13.054           | 52.250                           |                                        |                            |
| Residue on Evaporation Sample | 13.061           | 23.063                           | 13.164                                 | 1.03%                      |

### Summary of Results

| Attribute              | Result                             | Acceptance criteria                                                                                                   | Meets Criteria?<br>(circle one)                               |
|------------------------|------------------------------------|-----------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------|
| Appearance (color)     | Opaque white                       | Opaque white                                                                                                          | <input checked="" type="radio"/> Yes <input type="radio"/> No |
| Appearance (form)      | Inviscid liquid                    | Inviscid liquid                                                                                                       | <input checked="" type="radio"/> Yes <input type="radio"/> No |
| Residue on Evaporation | 1.03%                              | 0.5% – 1.5%                                                                                                           | <input checked="" type="radio"/> Yes <input type="radio"/> No |
| pH                     | 6.0                                | 5 – 8                                                                                                                 | <input checked="" type="radio"/> Yes <input type="radio"/> No |
| <sup>1</sup> H NMR     | Attach <sup>1</sup> H NMR spectra  | Identify Peaks with Amplitude >5% of Solvent Peak (4.75ppm)                                                           | <input checked="" type="radio"/> Yes <input type="radio"/> No |
| <sup>19</sup> F NMR    | Attach <sup>19</sup> F NMR spectra | Identify Peaks, if there is a peak at -76ppm determine approximate amplitude relative to peaks at -140ppm and -150ppm | <input checked="" type="radio"/> Yes <input type="radio"/> No |

Report completed by:

Ethan Rao  
Print name

*Ethan Rao*

Signature

07-Mar-2025

Date

Report reviewed by:

Brian McVerry  
Print name

*Brian McVerry*

Signature

19 Mar 2025

Date




**DOCUMENT TITLE:**  
Suspension Quality Control Report

**Revision:**  
A

**DOCUMENT #:**  
TMP1-QC-C.SLQ001

**Effective Date:**  
23Sep2022

$^1\text{H}$  NMR:



Broad Peaks are present at approximately 0.99, 2.2, 2.9, 3.1, 3.5, 3.7, 4.4, and 4.75 ppm indicating successful incorporation of the zwitterion moiety into the polymer.

$^{19}\text{F}$  NMR:




**DOCUMENT TITLE:**  
Suspension Quality Control Report

**Revision:**  
A

**DOCUMENT #:**  
TMP1-QC-C.SLQ001

**Effective Date:**  
23Sep2022



Two peaks at approximately -140 and -150 ppm identified. No peak was present at -76ppm indicating there is no TFE remaining in the suspension.