

	DOCUMENT TITLE: Suspension Quality Control Report	Revision: A
	DOCUMENT #: TMP1-QC-C.SLQ001	Effective Date: 23Sep2022

General Production Information

Work Order #:	2302-01	NCMR #:	N/A
Part Number:	C.SLQ001	Manufacture & Expiration Date:	Mfg date: 02/22/2023 Exp date: 02/22/2024
Part Revision:	B	Batch / Lot #:	2302-01-1

Supplies Traceability

Part Number	Description	Part Revision	Lot / Batch #
S.SLQ005	pH Strip	A	10BDH4801
S.SLQ006	Deuterium oxide	A	M2338

Equipment Traceability

Part Number	Description	Equipment ID	Calibration Due Date
E.SLQ013	Weighing scale	ST-012	10/3/2023

QC Data

Sample Tube	Weight Empty (g)	Weight with Residue (g)	Residue Net Weight (g)
Sample A1	12.9753	13.0873	0.1120
Sample A2	12.8213	12.9481	0.1268
Sample B1	13.0168	13.1495	0.1327
Sample B2	12.8607	12.9951	0.1344
Sample C1	12.9001	13.0390	0.1389
Sample C2	12.9341	13.0696	0.1355

	DOCUMENT TITLE: Suspension Quality Control Report	Revision: A
	DOCUMENT #: TMP1-QC-C.SLQ001	Effective Date: 23Sep2022

Sample Tube	Weight Empty (g)	Weight with Sample suspended (g)	Weight with Residue on Evaporation (g)	Residue on Evaporation (%)
Suspension Test Sample	13.002	39.4016		
Residue on Evaporation Sample	13.0347	23.4549	13.1320	0.973%

Summary of Results

Attribute	Result	Acceptance criteria	Meets Criteria? (circle one)
Appearance (color)	Opaque white	Opaque white	☒ Yes No
Appearance (form)	Inviscid liquid	Inviscid liquid	☒ Yes No
Residue on Evaporation	0.973%	0.5% – 1.5%	☒ Yes No
pH	6	5 – 8	☒ Yes No
¹ H NMR	Attach ¹ H NMR spectra	Identify Peaks with Amplitude >5% of Solvent Peak (4.75ppm)	☒ Yes No
¹⁹ F NMR	Attach ¹⁹ F NMR spectra	Identify Peaks, if there is a peak at -76ppm determine approximate amplitude relative to peaks at -140ppm and -150ppm	☒ Yes No

Report completed by:
Ethan Rao

Print name




Signature

27 Mar 2023

Date

Report reviewed by:
Bryan Wong

Print name



Signature

27 Mar 2023

Date



DOCUMENT TITLE:
Suspension Quality Control Report


Revision:
A

DOCUMENT #:
TMP1-QC-C.SLQ001

Effective Date:
23Sep2022

^1H NMR:

test 370 1 "C:\nmrdata\nmr400a (AV400)\data\Ethan\nmr"



Broad Peaks are present at approximately 0.99, 2.2, 2.9, 3.1, 3.5, 3.7, 4.4, and 4.75 ppm indicating successful incorporation of the zwitterion moiety into the polymer.




DOCUMENT TITLE:
Suspension Quality Control Report

Revision:
A

DOCUMENT #:
TMP1-QC-C.SLQ001

Effective Date:
23Sep2022

^{19}F NMR:



Two peaks at -140 and -150 ppm identified. One peak is identified at -75.55 ppm is due to the presence of trifluoroacetic acid which was added to the sample serving as a reference peak for the NMR spectra. No other peak was present at -76ppm indicating there is no TFE remaining in the suspension.