

	DOCUMENT TITLE: Suspension Quality Control Report	Revision: B
	DOCUMENT #: TMP1-QC-C.SLQ001	Effective Date:

General Production Information

Work Order #:	2502-01	NCMR #:	NCMR-001
Part Number:	C.SLQ001	Manufacture & Expiration Date:	Mfg date: 11 Feb 2025 Exp date: 11 Feb 2027
Part Revision:	B	Batch / Lot #:	2502-01-1

Supplies Traceability

Part Number	Description	Part Revision	Lot / Batch #
S.SLQ005	pH Strip	A	10BDH4801
S.SLQ006	Deuterium oxide	A	M2338

Equipment Traceability

Part Number	Description	Equipment ID	Calibration Due Date
E.SLQ013	Weighing scale	ST-012	02 Aug 2025

QC Data

Sample Tube	Weight Empty (g)	Weight with Residue (g)	Residue Net Weight (g)	Suspension Sample Concentration (g/L)
Sample A1	12.859	12.987	0.128	12.8
Sample A2	12.913	13.042	0.129	12.9
Sample B1	12.872	13.003	0.131	13.1
Sample B2	12.862	12.987	0.125	12.5
Sample C1	12.917	13.048	0.131	13.1
Sample C2	12.922	13.051	0.129	12.9

Average Suspension Sample Concentration (g/L): 12.88

	DOCUMENT TITLE: Suspension Quality Control Report	Revision: B
	DOCUMENT #: TMP1-QC-C.SLQ001	Effective Date:

Sample Tube	Weight Empty (g)	Weight with Sample suspended (g)	Weight with Residue on Evaporation (g)	Residue on Evaporation (%)
Suspension Test Sample	12.997	51.792		
Residue on Evaporation Sample	13.008	23.014	13.111	1.029%

Summary of Results

Attribute	Result	Acceptance criteria	Meets Criteria? (circle one)
Appearance (color)	Opaque white	Opaque white	☒ Yes No
Appearance (form)	Inviscid liquid	Inviscid liquid	☒ Yes No
Residue on Evaporation	1.029%	0.5% – 1.5%	☒ Yes No
pH	6.0	5 – 8	☒ Yes No
¹ H NMR	Attach ¹ H NMR spectra	Identify Peaks with Amplitude >5% of Solvent Peak (4.75ppm)	☒ Yes No
¹⁹ F NMR	Attach ¹⁹ F NMR spectra	Identify Peaks, if there is a peak at -76ppm determine approximate amplitude relative to peaks at -140ppm and -150ppm	☒ Yes No

Report completed by:

Ethan Rao
Print name

Ethan Rao
Signature

01-Apr-2025
Date

Report reviewed by:

Brian McVerry
Print name

Brian McVerry
Signature

01-Apr-2025
Date




DOCUMENT TITLE:
Suspension Quality Control Report

Revision:
B

DOCUMENT #:
TMP1-QC-C.SLQ001

Effective Date:

¹H NMR:



Broad Peaks are present at approximately 0.99, 2.2, 2.9, 3.1, 3.5, 3.7, 4.4, and 4.75 ppm indicating successful incorporation of the zwitterion moiety into the polymer.

¹⁹F NMR:



DOCUMENT TITLE:
Suspension Quality Control Report


Revision:
B

DOCUMENT #:
TMP1-QC-C.SLQ001

Effective Date:

test 161 1 "C:\nmrdata\nmr400a (AV400)\data\Ethan\nmr"

Account No. RBK371
2502-01-1



Two peaks at approximately -140 and -150 ppm identified. No peak was present at -76ppm indicating there is no TFE remaining in the suspension.