CIVIL POROUS PAVEMENT FOR PUBLIC AND MUNICIPAL WALKWAYS

CP-Series Cut Sheet

WHAT IT IS

Flexus™ CP-Series is a civil-grade porous pavement system designed for pedestrian infrastructure where durability, permeability, and material familiarity are prioritized. Formulated as a 50:50 (by volume) granite aggregate and recycled tire rubber matrix with a single-component moisture-cure polyurethane binder, the CP-Series provides a continuous, porous walking surface suited for municipal and public works applications. Available in 1.5 in, 2.0 in, and 2.5 in installed lifts.

SYSTEM SUMMARY

Installed thickness: 1.5 in, 2.0 in, 2.5 in

Surface Finish: Textured, exposed granite aggregate

Aggregate to rubber: 50:50 (by volume)

Binder System: Single-component moisture-cure polyurethane

Binder Content: Minimum 11 percent (by weight)

Installation Type: Poured-in-place, continuous

INTENDED USE

Municipal park trails

Public greenways

Recreation paths

LIMITATIONS

Pedestrian use only

Not designed for vehicular, emergency, or maintenance equipment

Final performance dependent on site conditions, substrate preparation, and construction

PERFORMANCE CHARACTERISTICS

Porous surface that can pass water into a prepared permeable base. An infiltration rate is not published; ASTM C1701 testing is in progress.

Stable bonded walking surface, not loose aggregate

Familiar granite aggregate appearance

Compatible with permeable base assemblies

When properly installed over a compliant subbase, the surface may support ADA slope conditions, with a recommended maximum cross slope of 2 percent. Final compliance is the responsibility of the project designer.

COLOR AND FINISH

CP-Series uses natural granite aggregate with black recycled tire rubber granules for a neutral appearance in civil and municipal settings.

WHY CP-SERIES

Exposed granite aggregate with a familiar civil appearance

Integrated permeability within a continuous surface

A bonded aggregate and recycled tire rubber matrix

DATA STATUS

In testing: ASTM C1701, E303, F1551 / D412, G154, C501, D2859. No results published.

All information contained herein is subject to change without notice. Installation conditions: 50°F (10°C) and rising, not more than 104°F (40°C); dry substrate; single-component moisture-cure binder. See the installation guide.

© 2026 Flexus Materials Ltd Co. All rights reserved.