



100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 12.01.2026

General Description :			
Product	: Red Pigment	Chemical Class	: Synthetic Iron Oxide Fe2O3
Delivery Condition	: Powder	Colour Index	: Pigment Red 101
Grade	: 110	Lot No	: R6021A
STD	: 30A	Quantity	: 0.500 TO
Date of Mfg	: 26.12.2025	PO No	:

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Colour difference DL of Mass Tone	-0.950	0.950	0.28	-
2	Colour difference Da of Mass Tone	-0.950	0.950	-0.36	-
3	Colour difference Db of Mass Tone	-0.950	0.950	-0.11	-
4	Colour difference DE of Mass Tone	-	1.300	0.47	-
5	Colour difference DL of Tint Tone	-0.950	0.950	0.22	-
6	Colour difference Da of Tint Tone	-0.950	0.950	-0.30	-
7	Colour difference Db of Tint Tone	-0.950	0.950	0.06	-
8	Colour difference DE of Tint Tone	-	1.300	0.38	-
9	Tinting strength,%	95.000	105.000	97.85	-
10	Volatiles,% at 105 deg C for 1hr	-	1.000	0.40	ISO 787/2
11	Residue on 325 mesh,%	-	0.150	0.11	ISO 787/7
12	Water soluble,%	-	0.300	0.25	ISO 787/3
13	Total iron as Fe2O3, %	95.000	99.500	98.26	IS44:1991 Annex B
14	Oil absorption ,g/100g	15.000	25.000	15.02	ISO 787/5

Remark : M/S Durga enterprises,Vishakhapatnam