



100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 31.12.2025

General Description :
Product : Yellow Pigment **Chemical Class :** Synthetic Iron Oxide à FeOOH
Delivery Condition : Powder **Colour Index :** Pigment Yellow 42
Grade : Berger Y 978 **Lot No :** L4786
STD : 1978 **Quantity :** 6.000 TO
Date of Mfg : 31.10.2025 **PO No :**

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Volatile matter, at 105 deg C	-	1.000	0.90	ISO 787/2
2	Water soluble salts, %	-	0.300	0.21	ISO 787/3
3	Residue on sieve, % by mass, max	-	0.150	0.12	ISO 787/7
4	pH of 10% aq. extract	4.000	8.000	5.60	ISO 787/9
5	Oil absorption ,g/100g	30.000	39.000	30.23	ISO 787/5
6	Total Iron as Fe ₂ O ₃ , %	86.000	89.000	88.48	IS44:1991 Annex B
7	Loss on ignition at 1000 deg C	-	13.000	10.53	IS44:1991 Annex B

Remark : M/S Berger paints, Assam