



**100 % EOU**  
**Sahupuram**  
**Thoothukudi District**  
**Tamilnadu - 628 229.**



**Certificate of Analysis**

COA No : COA/25-26/2697 Date : 25-03-2026 Lot No : 6781A  
Grade : 130 STD(Year) : 325- Product : Red pigment  
Qty(MT) : 8 Delivery Condition : Powder Color Index : Pigment Red 101  
Chemical Class : Synthetic Iron Oxide Fe<sub>2</sub>O<sub>3</sub> Mfg. Date : 02-02-2026 00:00:00 PO No :  
POD: : Customer :

**Characteristics**

| S.No | Characteristics                                              | Lower Limit | Upper Limit | Results    | Test Method        |
|------|--------------------------------------------------------------|-------------|-------------|------------|--------------------|
| 1    | Form & Condition                                             |             |             | Dry powder |                    |
| 2    | Volatile matter, % by mass, max                              | 0           | 0.50        | 0.45       | IS 44:1991 Annex B |
| 3    | Residue on sieve, % by mass, max                             | 0           | 0.50        | 0.10       | IS 44:1991 Annex B |
| 4    | Oil absorption                                               | 15          | 25          | 15.90      | IS 44:1991 Annex B |
| 5    | Matter soluble in water, % by mass, max                      | 0           | 0.50        | 0.18       | IS 44:1991 Annex B |
| 6    | Sum of soluble chloride & sulphur, % by mass, max            | 0           | 0.10        | 0.04       | IS 44:1991 Annex B |
| 7    | Acidity (as H <sub>2</sub> SO <sub>4</sub> ), % by mass, max | 0           | 0.10        | 0.0018     | IS 44:1991 Annex B |
| 8    | pH of aqueous extract                                        | 4           | 8           | 5.36       | IS 44:1991 Annex B |
| 9    | Ferrous iron, % by mass, max                                 | 0           | 1.5         | NIL        | IS 44:1991 Annex B |
| 10   | Calcium compounds, % by mass, max                            | 0           | 2.25        | 1.27       | IS 44:1991 Annex B |
| 11   | Total Iron as Fe <sub>2</sub> O <sub>3</sub> , %             | 95          |             | 98.42      | IS 44:1991 Annex B |

| S.No | Description  | L                    | a | b | DL | Da | Db | DE | Tinting Strength<br>Avg. Sample of<br>all the Bags |
|------|--------------|----------------------|---|---|----|----|----|----|----------------------------------------------------|
| 1    | Mass Tone    | Close match with STD |   |   |    |    |    |    |                                                    |
| 2    | Reduced Tone | Close match with STD |   |   |    |    |    |    |                                                    |

Remarks: M/S Chemical Impex, Indore

Anandharaj.S  
Senior Manager(QA)  
DCW Limited  
Sahupuram-628 229