



100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 23.01.2026

General Description :			
Product	: Red Pigment	Chemical Class	: Synthetic Iron Oxide Fe₂O₃
Delivery Condition	: Powder	Colour Index	: Pigment Red 101
Grade	: 130 E	Lot No	: L 6552B
STD	: 44	Quantity	: 6.000 TO
Date of Mfg	: 21.11.2025	PO No	:

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Colour difference DL of Mass Tone	-0.950	0.950	0.42	-
2	Colour difference Da of Mass Tone	-0.950	0.950	0.69	-
3	Colour difference Db of Mass Tone	-0.950	0.950	0.90	-
4	Colour difference DE of Mass Tone	-	1.300	1.21	-
5	Colour difference DL of Tint Tone	-0.950	0.950	-0.10	-
6	Colour difference Da of Tint Tone	-0.950	0.950	-0.14	-
7	Colour difference Db of Tint Tone	-0.950	0.950	-0.35	-
8	Colour difference DE of Tint Tone	-	1.300	0.39	-
9	Tinting strength,%	95.000	105.000	101.47	-
10	Volatiles,% at 105 deg C for 1hr	-	1.000	0.45	ISO 787/2
11	Residue on 325 mesh,%	-	0.150	0.12	ISO 787/7
12	Water soluble,%	-	0.300	0.08	ISO 787/3
13	Total iron as Fe ₂ O ₃ , %	95.000	99.500	98.39	IS44:1991 Annex B
14	Oil absorption ,g/100g	15.000	25.000	15.09	ISO 787/5

Remark : M/S GOLCHA PIGMENTS KALUNGA