



DCW LIMITED, 100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 09.05.2026

General Description :
Product : Red Pigment **Chemical Class :** Synthetic Iron Oxide Fe₂O₃
Delivery Condition : Powder **Colour Index :** Pigment Red 101
Grade : 130 **Lot No :** 6715N-B
STD : 325 **Quantity :** 0.500 TO
Date of Mfg : 22.01.2026 **PO No :**

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Colour difference DL of Mass Tone	-0.950	0.950	-0.23	-
2	Colour difference Da of Mass Tone	-0.950	0.950	-0.40	-
3	Colour difference Db of Mass Tone	-0.950	0.950	-0.55	-
4	Colour difference DE of Mass Tone	-	1.300	0.72	-
5	Colour difference DL of Tint Tone	-0.950	0.950	-0.23	-
6	Colour difference Da of Tint Tone	-0.950	0.950	-0.50	-
7	Colour difference Db of Tint Tone	-0.950	0.950	-0.69	-
8	Colour difference DE of Tint Tone	-	1.300	0.89	-
9	Tinting strength,%	95.000	105.000	98.15	-
10	Volatiles,% at 105 deg C for 1hr	-	1.000	0.38	ISO 787/2
11	Residue on 325 mesh,%	-	0.150	0.12	ISO 787/7
12	Water soluble,%	-	0.300	0.13	ISO 787/3
13	Total iron as Fe ₂ O ₃ , %	95.000	99.500	98.54	IS44:1991 Annex B
14	Oil absorption ,g/100g	15.000	25.000	15.39	ISO 787/5

Remark1 : M/S HIMAALAYAA PAINTS
Remark2 : CUDDALORE

This is system-generated document, therefore no signature is required.It is accepted to be Digital Signature.

Head of Quality