



100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 29.04.2026

General Description :			
Product	: Red Pigment	Chemical Class	: Synthetic Iron Oxide Fe₂O₃
Delivery Condition	: Powder	Colour Index	: Pigment Red 101
Grade	: 129	Lot No	: 6933 A
STD	: 30A	Quantity	: 3.000 TO
Date of Mfg	: 27.03.2026	PO No	:

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Colour difference DL of Mass Tone	-0.950	0.950	0.56	-
2	Colour difference Da of Mass Tone	-0.950	0.950	-0.54	-
3	Colour difference Db of Mass Tone	-0.950	0.950	0.20	-
4	Colour difference DE of Mass Tone	-	1.300	0.80	-
5	Colour difference DL of Tint Tone	-0.950	0.950	0.53	-
6	Colour difference Da of Tint Tone	-0.950	0.950	0.20	-
7	Colour difference Db of Tint Tone	-0.950	0.950	0.73	-
8	Colour difference DE of Tint Tone	-	1.300	0.92	-
9	Tinting strength,%	95.000	105.000	98.46	-
10	Volatiles,% at 105 deg C for 1hr	-	1.000	0.43	ISO 787/2
11	Residue on 325 mesh,%	-	0.150	0.13	ISO 787/7
12	Water soluble,%	-	0.300	0.19	ISO 787/3
13	Total iron as Fe ₂ O ₃ , %	95.000	99.500	98.40	IS44:1991 Annex B
14	Oil absorption ,g/100g	15.000	25.000	15.88	ISO 787/5

Remark : M/S INDUSTRIAL ASSOCIATES BHIWANDI