



100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 16.03.2026

General Description :
Product : Red Pigment **Chemical Class :** Synthetic Iron Oxide Fe₂O₃
Delivery Condition : Powder **Colour Index :** Pigment Red 101
Grade : 445 **Lot No :** 5777N-C
STD : 718B **Quantity :** 1.500 TO
Date of Mfg : 02.03.2025 **PO No :**

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Colour difference DL of Mass Tone	-0.950	0.950	-0.57	-
2	Colour difference Da of Mass Tone	-0.950	0.950	-0.90	-
3	Colour difference Db of Mass Tone	-0.950	0.950	-0.69	-
4	Colour difference DE of Mass Tone	-	1.300	1.27	-
5	Colour difference DL of Tint Tone	-0.950	0.950	0.07	-
6	Colour difference Da of Tint Tone	-0.950	0.950	-0.50	-
7	Colour difference Db of Tint Tone	-0.950	0.950	0.34	-
8	Colour difference DE of Tint Tone	-	1.300	0.61	-
9	Tinting strength,%	95.000	105.000	97.96	-
10	Volatiles,% at 105 deg C for 1hr	-	1.000	0.45	ISO 787/2
11	Residue on 325 mesh,%	-	0.150	0.12	ISO 787/7
12	Water soluble,%	-	0.300	0.25	ISO 787/3
13	Total iron as Fe ₂ O ₃ , %	95.000	99.500	98.54	IS44:1991 Annex B
14	Oil absorption ,g/100g	15.000	25.000	15.69	ISO 787/5

Remark : M/S MS ENTERPRISES