



100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 09.02.2026

General Description :			
Product	: Red Pigment	Chemical Class	: Synthetic Iron Oxide Fe2O3
Delivery Condition	: Powder	Colour Index	: Pigment Red 101
Grade	: 136	Lot No	: L 5753B
STD	: 40D	Quantity	: 2.000 TO
Date of Mfg	: 14.02.2025	PO No	:

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Colour difference DL of Mass Tone	-0.950	0.950	-0.40	-
2	Colour difference Da of Mass Tone	-0.950	0.950	-0.64	-
3	Colour difference Db of Mass Tone	-0.950	0.950	-0.39	-
4	Colour difference DE of Mass Tone	-	1.300	0.85	-
5	Colour difference DL of Tint Tone	-0.950	0.950	0.22	-
6	Colour difference Da of Tint Tone	-0.950	0.950	-0.08	-
7	Colour difference Db of Tint Tone	-0.950	0.950	0.79	-
8	Colour difference DE of Tint Tone	-	1.300	0.82	-
9	Tinting strength,%	95.000	105.000	102.39	-
10	Volatiles,% at 105 deg C for 1hr	-	1.000	0.44	ISO 787/2
11	Residue on 325 mesh,%	-	0.150	0.12	ISO 787/7
12	Water soluble,%	-	0.300	0.18	ISO 787/3
13	Total iron as Fe2O3, %	95.000	99.500	98.63	IS44:1991 Annex B
14	Oil absorption ,g/100g	15.000	25.000	16.07	ISO 787/5

Remark : M/S N R COLOURS WADA