



100 % EOU
SAHUPURAM
Thoothukudi District
Tamil Nadu-628 229



Report Date : 02.02.2026

General Description :
Product : Red Pigment **Chemical Class :** Synthetic Iron Oxide Fe₂O₃
Delivery Condition : Powder **Colour Index :** Pigment Red 101
Grade : 446 **Lot No :** L 6538N-B
STD : **Quantity :** 0.500 TO
Date of Mfg : 26.11.2025 **PO No :**

Sr No	Characteristics	Quantitative Specs		Result	Test Method
		Lower Limit	Upper Limit		
1	Colour difference DL of Mass Tone	-0.950	0.950	-0.45	-
2	Colour difference Da of Mass Tone	-0.950	0.950	-0.82	-
3	Colour difference Db of Mass Tone	-0.950	0.950	-0.10	-
4	Colour difference DE of Mass Tone	-	1.300	0.94	-
5	Colour difference DL of Tint Tone	-0.950	0.950	0.11	-
6	Colour difference Da of Tint Tone	-0.950	0.950	-0.78	-
7	Colour difference Db of Tint Tone	-0.950	0.950	0.59	-
8	Colour difference DE of Tint Tone	-	1.300	0.99	-
9	Tinting strength,%	95.000	105.000	98.03	-
10	Volatiles,% at 105 deg C for 1hr	-	1.000	0.44	ISO 787/2
11	Residue on 325 mesh,%	-	0.150	0.12	ISO 787/7
12	Water soluble,%	-	0.300	0.17	ISO 787/3
13	Total iron as Fe ₂ O ₃ , %	95.000	99.500	98.57	IS44:1991 Annex B
14	Oil absorption ,g/100g	15.000	25.000	15.54	ISO 787/5

Remark : M/S SHREE ADDITIVES,DAMAN