



100 % EOU  
SAHUPURAM  
Thoothukudi District  
Tamil Nadu-628 229



Report Date : 14.01.2026

|                              |                      |                       |                                                           |
|------------------------------|----------------------|-----------------------|-----------------------------------------------------------|
| <b>General Description :</b> |                      |                       |                                                           |
| <b>Product</b>               | <b>: Red Pigment</b> | <b>Chemical Class</b> | <b>: Synthetic Iron Oxide Fe<sub>2</sub>O<sub>3</sub></b> |
| <b>Delivery Condition</b>    | <b>: Powder</b>      | <b>Colour Index</b>   | <b>: Pigment Red 101</b>                                  |
| <b>Grade</b>                 | <b>: 110</b>         | <b>Lot No</b>         | <b>: L-6627N-D</b>                                        |
| <b>STD</b>                   | <b>: 30A</b>         | <b>Quantity</b>       | <b>: 5.000 TO</b>                                         |
| <b>Date of Mfg</b>           | <b>: 06.01.2026</b>  | <b>PO No</b>          | <b>:</b>                                                  |

| Sr No | Characteristics                                  | Quantitative Specs |             | Result | Test Method       |
|-------|--------------------------------------------------|--------------------|-------------|--------|-------------------|
|       |                                                  | Lower Limit        | Upper Limit |        |                   |
| 1     | Colour difference DL of Mass Tone                | -0.950             | 0.950       | -0.20  | -                 |
| 2     | Colour difference Da of Mass Tone                | -0.950             | 0.950       | -0.39  | -                 |
| 3     | Colour difference Db of Mass Tone                | -0.950             | 0.950       | -0.04  | -                 |
| 4     | Colour difference DE of Mass Tone                | -                  | 1.300       | 0.44   | -                 |
| 5     | Colour difference DL of Tint Tone                | -0.950             | 0.950       | -0.03  | -                 |
| 6     | Colour difference Da of Tint Tone                | -0.950             | 0.950       | -0.46  | -                 |
| 7     | Colour difference Db of Tint Tone                | -0.950             | 0.950       | 0.02   | -                 |
| 8     | Colour difference DE of Tint Tone                | -                  | 1.300       | 0.46   | -                 |
| 9     | Tinting strength,%                               | 95.000             | 105.000     | 101.00 | -                 |
| 10    | Volatiles,% at 105 deg C for 1hr                 | -                  | 1.000       | 0.38   | ISO 787/2         |
| 11    | Residue on 325 mesh,%                            | -                  | 0.150       | 0.10   | ISO 787/7         |
| 12    | Water soluble,%                                  | -                  | 0.300       | 0.21   | ISO 787/3         |
| 13    | Total iron as Fe <sub>2</sub> O <sub>3</sub> , % | 95.000             | 99.500      | 98.56  | IS44:1991 Annex B |
| 14    | Oil absorption ,g/100g                           | 15.000             | 25.000      | 15.46  | ISO 787/5         |

Remark : M/S TGR Trading