



100% EOU
Sahupuram
Dist Thoothukudi
Tamil Nadu 628 229



Date: 31.12.25

Certificate of Analysis

General Description:

Type : Yellow pigment Chemical class : Synthetic Iron oxide α Fe OOH

Delivery condition : Powder Colour index : Pigment Yellow 42

Lot No. : 3140 Quantity : 250g free trade sample

Grade : Yellow 920

S.No	Characteristics	Specification		Test results
		Lower limit	Upper limit	
1	Total Iron as Fe ₂ O ₃ , %	86	89	88.64
2	Water soluble salts, %	0	0.30	0.15
3	325 mesh sieve residue, %	0	0.15	0.13
4	pH of 10% aq extract	4	8	4.12
5	Volatile matter, at 105±5 oC	0	1.0	0.94
6	Oil absorption, g/100 g	30	39	30.84
7	Loss on ignition at 1000oC, %		13	10.68

S.Anandharaj
Sr.Manager(QA)