Complex Disordered Systems

Interactions between colloids

Francesco Turci

Today

- **Colloid-colloid interactions**
  - van der Waals interactions
  - double layer interactions
  - Entropic interactions: the Asakura-Oosawa model of depletion

Interactions between colloids

We distinguished between **fundamental** and **effective** forces between colloids

- **Fundamental forces:**
- gravity
- electro (magneto) static forces

- **Effective forces**
- Van der Waals forces
- electrostatic repulsion (DLVO)
- depletion forces
- hydrophobic/hydrophilic interactions
- steric forces

- Effective interactions emerge from the fundamental ones and structure our description at the colloidal scale.
- Fluctuations of fundamental forces are often at the origin of the effective forces.
- We focus on **effective interactions** (revise your electrostatics if needed)

van der Waals interactions

IUPAC definition:

> The **attractive** or **repulsive** forces between molecular entities (or between groups within the same molecular entity) other than those due to bond formation or to the electrostatic interaction of ions or of ionic groups with one another or with neutral molecules. The term includes:

> - **dipole–dipole**
> - **dipole-induced dipole**
> - London (instantaneous, spontaneous **dipole-induced dipole**) forces.

> The term is sometimes used loosely for the totality of nonspecific attractive or repulsive intermolecular forces.

van der Waals interactions: from dipoles to dispersion

We are focusing on atoms that are globally neutral. The first non-trivial term of the multipole expansion is the **dipole**.

- **dipole–dipole**: $U(r) \propto -\frac{\mu_1 \mu_2}{r^3}$
- **dipole–induced dipole**: a permanent dipole induces $\mu_B \propto \alpha\mu/r^3$ in a neutral atom, so $U(r) \propto -\frac{\mu^2 \alpha}{r^6}$
- **induced dipole–induced dipole**: even when the average density is neutral, quantum fluctuations of the electron density make it instantaneously **asymmetric**. These fluctuations produce the **London dispersion forces**

London dispersion interaction


$$U(r) = -\frac{C}{r^6}$$

The key insight is the $1/r^6$ decay of the interaction which decays much more rapidly than Coulomb's $1/r$. They are **short-range** in 3D, since the total energy scales like $\sim \int V(r) r^{d-1} dr$ and $6 > 3$

van der Waals attractive interaction between spheres

Take now two spherical colloids of radius R, centres at distance h: the surfaces are separated by the **gap** $D = h - 2R$.

Integrating the London interaction over all volume elements yields the **van der Waals attractive potential**



Colloid-colloid setup.

Colloid-colloid van der Waals attractive interaction

$$W_{vdW}(h) = -\frac{A_H}{6} f(h/R)$$

where A_H is the **Hamaker** constant and $f(h/R) = \left[\frac{2R^2}{h^2-4R^2} + \frac{2R^2}{h^2} + \ln\left(\frac{h^2-4R^2}{h^2}\right)\right]$.

van der Waals attractive interaction between spheres

Near contact $-W_{vdW} \approx A_H R/12D \gg k_B T$ (touching colloids stick); far away the atomic $1/h^6$ is recovered.

Python Code | Start Over | Run Code


```
R = 0.5    # radius (micron)
A_H = 2.4  # Hamaker constant (kBT) = 1e-20 J
plot(R, A_H)
```

Double-layer interaction: structure

Colloids are often charged. In the solution there will be

- **co-ions** (same charge as the colloid) that will be pushed away from the colloid surface, while
- **counter-ions** (opposite charge) will accumulate at the surface.

- A **double layer** forms due to the accumulation of counter-ions near the colloid surface, and repulsion of co-ions.
- Its width depends on the **ion concentration** in the solvent, which can be adjusted by adding or removing salts.



Double layer close to a surface (Wikimedia).

Double-layer interaction: nonlinear Poisson-Bolztmann equation

When two colloids come close, the charges in their double layers will interact, giving rise to a **repulsive interaction**.

This is not simply a Coulombic interaction, as it is mediated by the other (opposite) charges in the medium. Combining Poisson's equation with ion concentrations given by a Boltzmann weight of the electrostatic potential $\psi(\mathbf{r})$ yields the **nonlinear Poisson-Bolztmann equation**

$$\nabla^2\psi(\mathbf{r}) = -\frac{1}{\varepsilon}\left[\rho_{\text{fixed}} + \sum_i z_i e n_{s,i} \exp\left(-\frac{z_i e\psi}{k_B T}\right)\right]$$

with $n_{s,i}$ the far-away (bulk) concentration of ions of species i and $z_i e$ the ion charge (see the problem *Interaction of two charged colloidal spheres*).

No need to memorise this.

Double-layer interaction: screened repulsion

Linearisation around room temperature ($e\psi \ll k_B T$) yields the **Debye–Hückel equation**

$$\nabla^2 \psi = \psi / \lambda_D^2$$

where λ_D is the **Debye length**

$$\lambda_D = \sqrt{\frac{1}{8\pi \lambda_B n_s}}$$

itself dependent on the Bjerrum length λ_B: the scale at which two elementary charges have energy $k_B T$.

The final form of the potential is an **exponential repulsion** with scale λ_D

> **Important**
>
> $$W_{DR}(h) = B \frac{R}{\lambda_B} \exp\left(-\frac{h - 2R}{\lambda_D}\right)$$


Same h as in W_{vdW}: the repulsion decays with the gap $D = h - 2R$ between the surfaces. $B \leq 8$ depends on the surface potential.

vdW + double layer = DLVO interaction

To sum up, identical colloids in solution have two interactions of opposite sign

- a van der Waals component, typically **attractive**
- a double layer component **repulsive in nature**

The sum of the two gives rise to the DLVO (Derjaguin–Landau–Verwey–Overbeek) interaction which is an elementary model for colloid stability and aggregation.



Play with the potential

Excluded volume and generic atomistic interactions

- At very short distances the electronic clouds overlap.
- Electrons cannot share the same quantum state and must occupy different, higher energy states

→ **Large energy costs** in approaching atoms: **steric repulsive interactions** below a *van der Waals radius.*

A phenomenological model for a generic atomistic interaction potential is then

$$V_{\mathrm{LJ}}(r) = \frac{A_n}{r^n} - \frac{B_m}{r^m}$$

where the first term is the short-range repulsion and the second a generalised attraction.

A convenient choice is the **Lennard-Jones** potential of scale σ (twice the van der Waals radius)

$$V_{\mathrm{LJ}}(r) = 4\varepsilon \left[\left(\frac{\sigma}{r}\right)^{12} - \left(\frac{\sigma}{r}\right)^{6} \right],$$

where $m = 6$ is chosen to match London's forces and $n = 12$ is chosen to match experiments and computational convenience.


Atomistic, but at the heart of numerous **coarse-grained models**.

Exclusion and entropic forces

Steric repulsion (*hindrance*) means **excluded volume**: at thermal energy scales, an atom cannot be placed at the position of another atom.

Geometrical point of view:

- Excluded volume means that, neglecting attractions, atoms/molecules/macromolecules/colloids are *spheres that cannot overlap*.
- Distribute spheres in space:
  - volume exclusion means that some configurations are **forbidden**



Overlapping particles are forbidden by volume exclusion


Exclusion in one dimension

Exclusion means forbidden configurations.

Statistical mechanics approach: simplest system with the required ingredients, studied in detail.

- **Hard** identical particles on a line between two **repulsive, impenetrable walls**.

Macroscopic analogue:



Clothpins on a line

Exclusion in one dimension

Investigate the probability distribution $\rho(x)$ of finding the centre of a particle at position x. Parameters:

- clothpin horizontal size d (only size that matters)
- length of the line L
- number of clothpins N

We can treat the problem **algorithmically**

> **Algorithm**
>
> 1. position the particles in a valid configuration (no overlaps with other particles or the walls)
> 2. pick a particle at random
> 3. move it slightly along the line
> 4. test if the new position is valid (no overlaps)
> 5. if valid, accept the move; otherwise, reject
> 6. go back to (2)

Simulation of hard clothpins on a line


Play with the simulation

Python Code | Start Over | Run Code

```
N, L = 3, 24.0
positions_samples = clothpins(N,L,d=1.0,steps = 100_000)
plt.figure(figsize=(8,2.5))
plt.hist(positions_samples, bins=128, range=(0, L), density=True)
plt.gca().set(xlabel="Position [d]", ylabel="Probability density"); plt.tight_layout(); plt.show()
```

Simulation of hard clothpins on a line

- The key parameter is the **packing fraction** $\phi = \dfrac{dN}{L}$ (non-dimensional)[1].
  - **low** ϕ: almost uniform profile
  - **intermediate** ϕ: small peaks start to show close to the walls
  - **high** ϕ: strong peaks and modulation of the density along the line



Density profile at N=18, L=24, $\phi = 0.75$.

1. Our algorithm is direct and inefficient; see Krauth's, *Statistical Mechanics: Algorithms and Computations* for better approaches.

Attraction via repulsion

What do the peaks mean? It means that it is **more likely** to find the particles close to the walls:

- the walls seem to **attract** the particles
- peaks and valleys indicating layering
- the interaction with the wall vanishes as we get away from it


The source of this effect is **entropy**:

- if the first and last particles stay close to the walls, the other particles have **more available space** in the middle
- this means that there are more **configurations available** for the rest of the particles if the extreme particles are getting more localised
- more configurations → larger entropy → lower free energy = **depletion**

$$F = U - TS = \cancel{U} - TS$$

No internal energy, only entropy, so temperature is only a **scale parameter**.


Asakura-Oosawa depletion potential



More realism: Mixture of colloids (yellow) and polymers (squiggly lines inside red circles). The depletion layers are as thick as the polymer radius (red circles) and are indicated with the dashes around the colloids. When the two layers do not overlap, the osmotic pressure due to the polymers on the colloids is balanced. When there is overlap, there is a region inaccessible to the polymers (purple) and the pressure is unbalanced, leading to aggregation.

Asakura-Oosawa depletion potential

- Depletion forces play a pivotal role in colloidal **aggregation**.
- The basic mechanisms are the same as in our 1D example.
- We are going to work through the details of a particular model
  - **Asakura-Oosawa** depletion interaction



Asakura-Oosawa setting

Asakura-Oosawa model

- **Colloids**: Large spheres, diameter $2R$, impenetrable (**hard spheres**)
- **Polymeric bundles**: Smaller spheres, diameter $\sigma_p = 2\delta$.
  - cannot overlap with colloids
  - can overlap with other (**penetrable hard spheres**)
- System is at thermodynamic equilibrium:
  - same pressure, temperature and chemical potential throughout
  - can think of the system as chemostatted by a **polymer reservoir** at the same $\mu_{polymer}$


- The polymers (by themselves) are **ideal** so their chemical potential is

$$\mu_p = k_B T \ln \rho_p^r$$

- The number density is linked to the packing fraction $\phi_p^r = \rho_p v_p = \frac{\pi}{6} \rho_p^r \sigma_p^3$
- we work at constant V, T, μ: **grand canonical ensemble**
- We ignore **all internal structure** of the polymers.

Sketch of derivation of AO potential

- In the absence of colloids, the entire volume V is accessible to the polymer $V_{\text{accessible}} = V$
- Grand potential of the polymers $\Omega = -k_B T e^{\mu_p / k_B T} V_{\text{accessible}}$
- Introduce one colloid: the polymers cannot get closer than the distance $R + \delta$




Excluded volume around one polymer

- **Excluded volume** $V_{\text{exclusion}} = V_{\text{outer}} - V_{\text{inner}} = \frac{4\pi}{3}\left((R+\delta)^3 - R^3\right)$
- The accessible volume is now $V_{\text{accessible}} = V - V_{\text{exclusion}}$

Sketch of derivation of AO potential

- Introduce a second colloid at distance r from the first colloid.
- The accessible volume is $V^{\infty}_{\text{accessible}} = V - 2V_{\text{exclusion}}$
- Two situations:
  1. $\forall r > 2R_d = 2R + 2\delta$ the accessible volume remains the same, constant $\Omega(r) = \Omega_{\infty}$
  2. For $2R < r < 2R_d$ the accessible volume changes: **overlap** between exclusion volumes.



A second colloid is introduced at a short distance r. The exclusion regions overlap (light blue), increasing the accessible volume.

Sketch of derivation of AO potential

- The overlap region can be calculated from standard geometrical properties of spherical caps

$$V_{\text{overlap}}(r) = \frac{4\pi}{3} R_d^3 \left[1 - \frac{3}{4}\frac{r}{R_d} + \frac{1}{16}\left(\frac{r}{R_d}\right)^3 \right]$$

- The new accessible volume is

$$V'_{\text{accessible}} = V - (2V_{\text{exclusion}} - V_{\text{overlap}})$$

- Since $\Omega = -k_B T e^{\mu_p / k_B T} V_{\text{accessible}}$ the grand potential becomes **more negative** when the colloids are close.

Sketch of derivation of AO potential

- Free energy advantage from the overlapping excluded volumes

$$
\begin{aligned}
W_{\mathrm{AO}}(r) = \Omega(r) - \Omega^{\infty} &= -k_B T e^{\mu/k_B T} \left(V_{\text{accessible}}(r) - V_{\text{accessible}}(\infty)\right) \\
&= -k_B T e^{\mu/k_B T} \left[V - 2V_{\text{exclusion}} + V_{\text{overlap}}(r) - (V - 2V_{\text{exclusion}})\right] \\
&= -k_B T e^{\mu/k_B T} V_{\text{overlap}(r)} \\
&= -k_B T \rho_p V_{\text{overlap}(r)}
\end{aligned}
$$

The result is an attractive depletion potential controlled by the geometry of the overlap

Asakura-Oosawa potential (1954)

$$
W_{\mathrm{AO}}(r) = -\frac{4\pi\rho_p^r k_B T}{3}(R+\delta)^3 \left[1 - \frac{3}{4}\frac{r}{R+\delta} + \frac{1}{16}\left(\frac{r}{R+\delta}\right)^3\right] \quad 2R \leq r < 2(R+\delta)
$$

AO potential

Python Code | Start Over | Run Code

```
R = 1.0           # Colloid radius
r = np.linspace(2*R, 3*R, 500)
W_AO = AO_potential(r, R=R, delta=0.2*R, eta_p=0.1, kBT=1)
plt.figure(figsize=(8,3)); plt.plot(r, W_AO)
plt.gca().set(xlabel="Separation $r/R$", ylabel="$W_{AO}(r)$"); plt.tight_layout(); plt.show()
```

Summary of main colloid-colloid interactions

Interaction	Origin	Range	Control knob
Van der Waals	attractive, from fluctuating dipoles; $\approx -A_H R/12D$ near contact	tens of nm, $\propto A_H R$	materials (A_H), index matching
Double layer	repulsive, screened electrostatics	Debye length λ_D: ~ 1 nm (100 mM) to ~ 100 nm (deionised)	salt
DLVO	sum: barrier (stability) and secondary minimum	barrier at $\sim$nm, secondary minimum at several λ_D	salt switches stable $\leftrightarrow$ aggregating
Depletion	attractive, purely entropic	polymer size 2δ	polymer concentration and size