



FABRIC MANUFACTURING

Part: A

Course Code: FE 351-0723

Knitted Fabric Faults

Arnob Mahmud

Lecturer

Department of Fabric Engineering

Bangladesh University of Textiles (BUTEX)

E-mail: arnob@fe.butex.edu.bd

HOLE MARKS

Causes

- ☐ Holes are the results of yarn breakage or yarn cracks.
- ☐ During loop formation the yarn breaks in the rejoin of the needle hook.
- ☐ If the yarn count is not correct on regarding structure, gauge, course and density.
- ☐ Badly knot or splicing.
- ☐ Yarn feeder badly set.

Remedies

- ☐ Yarn strength must be sufficient to withstand the stretch as well as uniform.
- ☐ Use proper count of yarn.
- ☐ Correctly set of yarn feeder.
- ☐ Knot should be given properly.



NEEDLE MARK

Causes

- ☐ When a needle breaks down then needle mark comes along the fabrics.
- ☐ If a needle or needle hook slightly bends, then needle mark comes on the fabrics.

Remedies

- ☐ Needle should be straight as well as from broken latch be changed.



STAR

Causes

- ☐ Yarn tension variation during production.
- ☐ Buckling of the needle latch.
- ☐ Low G.S.M fabric production.

Remedies

- ☐ Maintain same Yarn tension during production.
- ☐ Use good conditioned needles.




DROP STITCHES

Causes

- ☐ Defective needle.
- ☐ If yarn is not properly fed during loop formation.
- ☐ Take-down mechanism too loose.
- ☐ Insufficient yarn tension.
- ☐ Badly set yarn feeder.

Remedies

- ☐ Needle should be straight & well.
- ☐ Proper feeding of yarn during loop formation.
- ☐ Correct take up of the fabric & correct fabric tension.
- ☐ Yarn tension should be properly.



OIL STAIN

Causes

- ❑ When oil lick through the needle trick then it pass on the fabrics and make a line.

Remedies

- ❑ Ensure that oil does not pass on the fabrics.
- ❑ Well maintenance as well as proper oiling.



SLUB

Causes

- ☐ Due to slub yarn.
- ☐ Dust or fly deposit on yarn during knitting.

Remedies

- ☐ Using slub-less yarn or less slub containing yarn.
- ☐ Using air blower and suction pipe.



LYCRA OUT

Causes

- ❑ Breakage of Lycra yarn & uneven tension of Lycra.

Remedies

- ❑ To maintain uniform tension.



SINKER DROP

Causes

- ☐ Sinker does not work properly.
- ☐ Sinker head may be broken.
- ☐ Sinker head may be bended.

Remedies

- ☐ Sinker must be changed.

PIN HOLE

Causes

- ☐ Due to break down or bend of the latch, pin hole may come in the fabric.

Remedies

- ☐ Change the needle.

PATTA

Causes

- ☐ Yarn count variation.
- ☐ Yarn tension variation.

Remedies

- ☐ Proper yarn count & tension should be maintained.

Note: For dark color & plain single jersey patta very sensitive. But in case of derivatives of single jersey, rib & interlock light patta considerable.

FLY DUST

Causes

In knitting section too much lint is flying to and fro that are created from yarn due to low twist as well as yarn friction.

This lint may adhere or attaches to the fabric surface tightly during knit fabric production.

Remedies

- ☐ Blowing air for cleaning and different parts after a certain period of time.
- ☐ By cleaning the floor continuously.
- ☐ By using ducting system for cleaning too much lint in the floor.
- ☐ Over all ensure that lint does not attach to the fabric.

YARN MISS

Causes

- ❑ Yarn breakage due to any reason and not pass through the yarn guide. It may be occur for tension variation.

Remedies

- ❑ Yarn guide and tensioner must be use.

MIXED TWIST

Causes

- ❑ Mixing of S twist and Z twist which imparts dull effects on the fabric.

Remedies

- ❑ Worker must be careful.

THANK
YOU !

