

# FEDRIGONI

IPANEMA EMBOSSED CREAM FSC / SH9020 / WG74

B1100

USC:

Edition: 1

Date of approval: 21/08/2023

## Belongs to the collections

- The Book of Labels

## Technical datasheet

### Front Label

Reference	IPANEMA EMBOSSED CREAM FSC™
General characteristics	Natural paper of pure chlorine-free cellulose (ECF), embossed on one side. Treated wet strenght.FSC certification ensures that products are made from responsibly managed forests.
Grammage (g/m²) ISO 536	92 +/- 4
Thickness (µm) ISO536	133 +/- 11
Dry opacity (%) ISO 2471	> 92
Cobb (gr/m2)	20

### Adhesive


Reference	SH9020
General characteristics	Water-based permanent acrylic adhesive. Good adhesion to polar surfaces in wet conditions and low temperatures. Especially designed for glass bottles, with excellent resistance to immersion in water/ice. It is not repositionnable.
Tack (N/ pol²) glass FTM-9	≥11
Cohesion (h) 1 kg FTM8	≥2
Labelling temperature (°C)	≥5
Service temperature (°C)	-20 / +80

### Support

Reference	WG74
General characteristics	Supercalendered glassine paper, white, siliconized on one side.
Grammage (g/m²) ISO 536	72 + / - 2
Thickness (µm) ISO536	62 + / - 4



## Schemes



### Ice bucket



### Refrigerator



### Wet opacity



### Neck Label

Not recommended

### Use and application

Specially designed for product labels of high added value bottled in glass (wine, licquors,champagne, oil, water,...)

### Certification

Fedrigoni Self adhesives has the license FSC - C114507 for trademark use FSC™

### Total Weight (g/m²)

190 +/- 9

### Total Thickness (µm)

220 +/- 18

### Futher Information

Not recommended for labeling of curved surfaces of small diameter.

### Printing

Suitable for printing in UV Offset, hot-stamping and silkscreen printing. For printing in Flexo (UV, water) it is recommended to apply a pre-impression varnish

### Application Instructions

The material must be applied on a clean and dry surface, free of dust, oil and release agent.

### Storage Warranty

2 year warranty, under storage conditions as defined by FINAT section 2.5 (20-25°C, 40-50% RH). Prolonged storage at higher

temperatures and / or humidity levels can shorten the shelf life of the product.

LIMITED WARRANTY: All information above regarding ARCONVERT's products is only for guidance. We recommend to adapt the indications on the use of our products to the local conditions, taking into account the materials and / or substrates to be used. Considering the various possible applications, ARCONVERT guarantees the quality of its products according to its specifications, but does not guarantee in any way the final use of them. The user must verify the authenticity of the product as to the specific application and take risks for misuse. If any product is found to be out of specification, ARCONVERT will replace the material and limit its responsible to the value of the product by issuing a credit or replacement of the product. No seller or representative of ARCONVERT is authorized to provide any warranty or make any representation contrary to the document above. We reserve the right to make improvements and modifications to the document and / or product mentioned above without previous notice.