

WX205

Zinc Dialkyl Dithiophosphate Antioxidant & Corrosion Inhibitor

Series: ZDDP Antioxidant & Corrosion Inhibitors

Good antioxidant, anti-corrosion and extreme-pressure anti-wear performance. Used in standard internal combustion engine oils and industrial lubricants.

ATTRIBUTES

ZDDP

END USES

Engine oils

Industrial & hydraulic oils



Technical Parameters

PROPERTY	SPECIFICATION	TEST METHOD
Appearance	Amber transparent liquid	Visual
Density @20 °C, g/cm³	1.10-1.18	GB/T 2540
Kinematic Viscosity @100 °C, mm²/s	Report	GB/T 265
Sulfur, %	16.0-18.5	SH/T 0303
Phosphorus, %	8.5-9.5	SH/T 0296
Zinc, %	9.5-10.8	SH/T 0226
Flash Point (Open Cup), °C	≥180	GB/T 3536
Color	≤4.0	GB/T 6540
Mechanical Impurities, %	≤0.07	GB/T 511
Water Content, %	≤0.06	GB/T 260
Thermal Decomposition Temperature, °C	≥220	SH/T 0561

Values are release specifications from the product TDS unless marked typical; the certificate of analysis shipped with each lot is the reference for that lot. Treat rates are guidance and depend on base oil and target performance level — our technical team is available to confirm dosage for your formulation.

Wuxi South Petroleum Additives Co., Ltd.

ADDRESS	TEL	EMAIL	WEB
48 Daqiao Road, Shitangwan, Huishan District, Wuxi, Jiangsu 214185, China	+86 510 8326 0848	sale@wxnfcn.com	www.wxnfcn.cn

pH	≥5.0	—
----	------	---

Values are release specifications from the product TDS unless marked typical; the certificate of analysis shipped with each lot is the reference for that lot. Treat rates are guidance and depend on base oil and target performance level — our technical team is available to confirm dosage for your formulation.

Wuxi South Petroleum Additives Co., Ltd.

ADDRESS

48 Daqiao Road, Shitangwan, Huishan District, Wuxi, Jiangsu
214185, China

TEL

+86 510 8326 0848

EMAIL

sale@wxnfcn.com

WEB

www.wxnfcn.cn