

WX161

High-Molecular-Weight Succinimide Ashless Dispersant

Series: Ashless Dispersants

Made with BASF polyisobutylene. Excellent high-temperature detergency and good low-temperature dispersancy. Produced by a thermal process, it outperforms conventional ashless dispersants in high- and low-temperature dispersancy and soot handling. Chlorine-free. Widely used in mid- to high-tier gasoline and diesel engine oils. Typical treat rate 1%–5%.

ATTRIBUTES

High Molecular Weight

Chlorine-Free

END USES

Engine oils



Technical Parameters

PROPERTY	SPECIFICATION	TEST METHOD
Appearance	Reddish-brown viscous transparent liquid	Visual
Kinematic Viscosity @100 °C, mm ² /s	300–500	GB/T 265
Total Base Number, mg KOH/g	15–30	SH/T 0251
Nitrogen, %	1.0–1.1	GB/T 9170
Color (Diluted)	≤3.5	GB/T 6540
Mechanical Impurities, %	≤0.08	GB/T 511
Flash Point (Open Cup), °C	≥180	GB/T 3536
Water Content, %	≤0.08	GB/T 260

Values are release specifications from the product TDS unless marked typical; the certificate of analysis shipped with each lot is the reference for that lot. Treat rates are guidance and depend on base oil and target performance level — our technical team is available to confirm dosage for your formulation.

Wuxi South Petroleum Additives Co., Ltd.

ADDRESS

48 Daqiao Road, Shitangwan, Huishan District, Wuxi, Jiangsu
214185, China

TEL

+86 510 8326 0848

EMAIL

sale@wxnfcn.com

WEB

www.wxnfcn.cn

Recommended Treat Rate

PERFORMANCE LEVEL	TREAT RATE
Typical treat rate	1%–5%

Values are release specifications from the product TDS unless marked typical; the certificate of analysis shipped with each lot is the reference for that lot. Treat rates are guidance and depend on base oil and target performance level — our technical team is available to confirm dosage for your formulation.

Wuxi South Petroleum Additives Co., Ltd.

ADDRESS

48 Daqiao Road, Shitangwan, Huishan District, Wuxi, Jiangsu
214185, China

TEL

+86 510 8326 0848

EMAIL

sale@wxnfcn.com

WEB

www.wxnfcn.cn