

# WX202

## Primary ZDDP (C4/C8 alcohols)

Series: ZDDP Antiwear & Antioxidant Additives

Good antioxidant, anti-corrosion and extreme-pressure anti-wear performance; effectively prevents engine bearing corrosion. Used in conventional engine oils and industrial lubricants.

ATTRIBUTES

ZDDP

Primary

END USES

Engine oils

Industrial & hydraulic oils



### Technical Parameters

| PROPERTY                                        | SPECIFICATION            | TEST METHOD |
|-------------------------------------------------|--------------------------|-------------|
| Appearance                                      | Amber transparent liquid | Visual      |
| Density @20 °C, g/cm <sup>3</sup>               | 1.08-1.13                | GB/T 2540   |
| Kinematic Viscosity @100 °C, mm <sup>2</sup> /s | Report                   | GB/T 265    |
| Sulfur, wt%                                     | 14.0-18                  | SH/T 0303   |
| Phosphorus, wt%                                 | 7.2-8.5                  | SH/T 0296   |
| Zinc, wt%                                       | 8.5-10                   | SH/T 0226   |
| Flash Point (Open Cup), °C                      | ≥180                     | GB/T 3536   |
| ASTM Color (diluted sample)                     | ≤2.0                     | GB/T 6540   |
| Sediment (mechanical impurities), wt%           | ≤0.07                    | GB/T 511    |
| Water Content, wt%                              | ≤0.03                    | GB/T 260    |
| Thermal Decomposition Temperature, °C           | ≥220                     | SH/T 0561   |

Values are release specifications from the product TDS unless marked typical; the certificate of analysis shipped with each lot is the reference for that lot. Treat rates are guidance and depend on base oil and target performance level — our technical team is available to confirm dosage for your formulation.

#### Wuxi South Petroleum Additives Co., Ltd.

ADDRESS

48 Daqiao Road, Shitangwan, Huishan District, Wuxi, Jiangsu  
214185, China

TEL

+86 510 8326 0848

EMAIL

sale@wxnfcn.com

WEB

www.wxnfcn.cn