









FlexChroma Blend Filament – Model Efficiency Summary (Waste Ratio & Print Time)

MIX%	M1			M2			M3			M4			S1			S2			S3			S4		
																								
	Model (g)	Flush & Tower (g)	Printing Time (h:m)	Model (g)	Flush & Tower (g)	Printing Time (h:m)	Model (g)	Flush & Tower (g)	Printing Time (h:m)	Model (g)	Flush & Tower (g)	Printing Time (h:m)	Model (g)	Flush & Tower (g)	Printing Time (h:m)	Model (g)	Flush & Tower (g)	Printing Time (h:m)	Model (g)	Flush & Tower (g)	Printing Time (h:m)	Model (g)	Flush & Tower (g)	Printing Time (h:m)
50	73.1	9.1	2:58	63.3	9.1	2:38	53.2	9.1	2:19	43.5	9.1	1:59	34.3	11.4	1:45	26.2	11.4	1:30	19.2	11.4	1:16	12.5	9.9	1:02
55	73.3	9.7	2:40	63.5	9.7	2:23	53.3	9.7	2:06	43.6	9.7	1:49	34.4	12.3	1:38	26.3	12.3	1:25	19.2	12.3	1:13	12.5	10.7	1:01
60	73.0	8.7	2:59	63.2	8.8	2:39	53.2	8.7	2:19	43.4	8.7	1:59	34.3	11.0	1:45	26.2	11.0	1:30	19.2	11.0	1:16	12.5	9.6	1:01
65	73.1	8.7	2:57	63.4	6.8	2:21	53.3	8.7	2:16	43.5	8.7	1:55	34.4	11.0	1:39	26.3	11.0	1:24	19.2	11.0	1:13	12.6	8.9	1:00
70	73.0	8.7	2:59	63.3	8.7	2:36	53.2	8.7	2:15	43.5	8.7	1:56	34.3	11.0	1:43	26.2	11.0	1:28	19.2	11.0	1:14	12.5	9.6	1:00
75	72.7	7.8	3:02	63.0	7.8	2:42	53.0	7.8	2:22	43.5	7.8	2:01	34.2	9.8	1:46	26.1	9.8	1:29	19.1	9.8	1:15	12.4	8.5	0:59
80	73.3	6.8	3:05	63.5	6.8	2:45	53.3	6.8	2:25	43.3	6.8	2:04	34.3	8.5	1:46	26.2	8.5	1:28	19.2	8.5	1:12	12.5	8.5	0:58
85	73.0	6.8	3:21	63.2	6.8	2:56	53.2	6.8	2:31	43.4	6.8	2:07	34.3	8.5	1:48	26.2	8.5	1:29	19.2	8.5	1:13	12.5	7.5	0:57
90	73.0	8.8	3:19	63.2	8.8	2:59	53.1	8.8	2:35	43.4	8.8	2:11	34.3	11.1	1:55	26.2	11.1	1:37	19.1	11.1	1:21	12.5	9.7	1:05
92.5	73.0	8.8	3:19	63.2	8.8	2:59	53.1	8.8	2:35	43.4	8.8	2:11	34.3	11.1	1:54	26.2	11.1	1:37	19.1	11.1	1:21	12.5	7.5	0:57
95	72.8	6.9	2:58	63.1	6.9	2:40	53.0	6.9	2:19	43.3	6.9	1:57	34.2	8.6	1:42	26.1	8.6	1:26	19.1	8.6	1:11	12.5	7.5	0:56
96	72.7	5.9	2:52	63.0	5.9	2:33	52.9	5.9	2:12	43.3	5.9	1:52	34.1	7.3	1:37	26.1	7.3	1:21	19.1	7.3	1:06	12.4	6.4	0:52
97	73.0	4.8	2:45	63.3	4.8	2:26	53.2	4.8	2:06	43.4	4.8	1:47	34.3	5.9	1:32	26.2	5.9	1:16	19.2	5.9	1:02	12.5	5.2	0:48
98	73.0	3.7	2:38	63.3	3.7	2:20	53.2	3.7	2:00	43.5	3.7	1:42	34.3	4.6	1:27	26.2	4.6	1:12	19.2	4.6	0:57	12.5	4.1	0:44
98.5	73.0	3.7	2:38	63.2	3.7	2:19	53.2	3.7	2:00	43.4	3.7	1:42	34.3	4.6	1:27	26.2	4.6	1:12	19.1	4.6	0:58	12.5	4.1	0:44
99	72.9	2.7	2:32	63.1	2.7	2:13	53.1	2.7	1:55	43.4	2.7	1:37	34.2	3.2	1:22	26.2	3.2	1:07	19.1	3.2	0:53	12.5	2.9	0:40
99.5	72.9	1.7	2:45	63.1	1.7	2:25	53.0	1.7	2:04	43.3	1.7	1:44	34.2	2.0	1:27	26.2	2.0	1:10	19.1	2.0	0:54	12.5	1.8	0:40
Average	Waste		Printing Time (h:m)	Waste		Printing Time (h:m)	Waste		Printing Time (h:m)	Waste		Printing Time (h:m)	Waste		Printing Time (h:m)	Waste		Printing Time (h:m)	Waste		Printing Time (h:m)	Waste		Printing Time (h:m)
	(%)	(g)		(%)	(g)		(%)	(g)		(%)	(g)		(%)	(g)		(%)	(g)		(%)	(g)		(%)	(g)	
STD	10%	8.2	3:01	11%	8.0	2:39	13%	8.2	2:19	16%	8.2	1:59	23%	10.3	1:44	28%	10.3	1:28	35%	10.3	1:14	42%	9.0	0:59
DTL	7%	5.2	2:51	8%	5.2	2:32	9%	5.2	2:11	11%	5.2	1:51	16%	6.5	1:35	20%	6.5	1:19	25%	6.5	1:04	30%	5.5	0:49
Total	8%	6.7	2:55	9%	6.6	2:34	11%	6.7	2:14	13%	6.7	1:54	20%	8.4	1:39	24%	8.4	1:23	30%	8.4	1:09	37%	7.2	0:54

*The model weight includes the weight of the brim (0.06g).

*The Flush and Tower values are for the initial filament state of the profile. Weight tends to increase with different materials (e.g., Bambu Lab PLA Basic & Generic PLA Basic).