MgO electronic structure: Sparse-DFT band analysis

direct-gap insulator · E_g = 4.664 eV · VBM Γ, CBM Γ · m_e^* 0.342–0.347 m_0 · m_h^* 1.09–4.61 m_0 · 2 atoms per cell · Sparse-DFT vs VASP 6.4.1 (matched cutoff, PAW, XC and k)













