

Testing Heat-Treated 1080 Steel

Jada Fox, Veronica Ayen

Background:

The heat treatment of 1080 steel is useful in industry, as its high carbon content makes the material’s mechanical properties highly sensitive to heating and cooling gradients. Understanding the relationship between heat treatment processes with the resulting microstructure and mechanical properties allows for the optimized performance of 1080 steel across diverse applications.

Hypothesis Tested:

Different cooling rates (water quenching vs. furnace cooling) will produce distinct microstructures, leading to significant variations in hardness and toughness.

Materials:

- 1080 Steel (three identical samples)

Processing Methods:

- Control:** As received conditions
- Water Quenched:** Austenitized at 850° C for 15 min, then rapidly quenched in agitated water.
- Furnace- Cooled:** Austenitized at 850° C for 15 min, then slowly cooled from 800° C to 650° C for over 1 hour, held for 1 hour, and quenched.

Testing Methods:

- Hardness Testing: Rockwell A Scale (HRA)
- Impact Toughness: Charpy V-Notch Test (ft-lb)
- Microstructural Analysis: Samples were cut, cold-mounted, ground, polished, etched, and observed under a microscope.
- Mechanical Behavior: Three-point bend test analysis.

Conclusions:


- Water-Quenching** produces a very hard (62-65 HRA) but brittle (5 ft-lb) material, suitable for applications requiring high wear resistance but not impact loading.
- Furnace-Cooling** produces a soft (40 HRA) but very tough (60 ft-lb) and ductile material, ideal for components that require energy absorption.
- The **Control** condition provides a balance of moderate hardness (59.5 HRA) and toughness (32 ft-lb), offering a good combination of strength and ductility.

Future work:

Study the effects of different quenching media (oil, air) or isothermal heat treatments (e.g., bainite formation) to create a more comprehensive property map for 1080 steel.

Technical Background:

Rapid cooling (quenching) traps carbon atoms, creating a hard and brittle microstructure. Slow cooling allows carbon to diffuse, forming a softer, more ductile lamellar structure.



Testing Specifications:

- Scale:** Brail Diamond Indenter
- Measurement Type:** HRA
- Range:** 20-88 HRA (all samples within optimal range)

- 1080 Steel Composition:** Eutectoid steel with ~0.8% carbon, making it ideal for studying phase transformations.
- Austenitization:** Heating to 850°C transforms the microstructure to austenite (FCC), allowing carbon to dissolve uniformly.
- Rapid Quenching:** Prevents carbon diffusion, causing a shear transformation to martensite (BCT) - a hard, brittle structure.
- Slow Cooling:** Allows carbon to diffuse and form pearlite - alternating layers of ferrite (soft) and cementite (hard).
- Structure-Property Relationship:** Mechanical properties (hardness, toughness) are directly controlled by the resulting microstructure, which is determined by the heat treatment process

Results & Discussion:

Sample	Microstructure	Hardness (HRA)	Charpy V-Notch (ft-lb)	Visual Description
Control		59.50-57.55	32	Fine, equiaxed grains Uniformly dispersed second-phase particles (darker grains); smaller than primary grain boundaries
Water-Quenched		62.45-65.03	5	Large grains Irregular second-phase particles; similar in size to primary grain boundaries Particles cluster around grain boundaries
Furnace-Cooled		40.08-39.48	60	Moderate grain size; uniform; directional Second-phase particles are partially aligned; smaller than primary grain boundaries

The data clearly shows a strong correlation between processing, microstructure, and properties. The Water-Quenched sample, with its hard martensitic structure, showed the highest resistance to indentation (hardness) but the lowest resistance to impact (brittleness).The Furnace- Cooled sample, with its soft pearlitic structure, exhibited the opposite: low hardness but high toughness and ductility. The Control sample's mixed ferrite-pearlite microstructure resulted in intermediate mechanical properties. The water-quenched sample showed highest hardness (62-65 HRA) due to rapid cooling trapping carbon atoms. The furnace-cooled sample displayed lowest hardness (40.1 HRA) from slow cooling allowing carbon diffusion. The control sample exhibited intermediate hardness (59.5 HRA) from its mixed ferrite-pearlite structure. All measurements fall within the recommended HRA scale range (20-88 HRA).

Literature Resources

Chandler, Harry. *Heat Treater’s Guide : Practices and Procedures for Irons and Steels*. Metals Park, Oh, Asm International, 1995.

“Metallographic Etching.” *Buehler.com*, 15 Nov. 2021, www.buehler.com/blog/metallographic-etching/.

Further Information

Jada Fox
jada.fox@uconn.edu

Veronica Ayen
veronica.ayen@uconn.edu