

FCO. VAZQUEZ

THIS IS THE TITLE OF THE  
THESIS



# *Contents*

<i>1</i>	<i>Introduction</i>	<i>5</i>
<i>2</i>	<i>Theoretical Framework</i>	<i>7</i>
	<i>2.1 Hydrogels</i>	<i>7</i>
	<i>2.1.1 Polymeric networks</i>	<i>7</i>
	<i>2.1.2 Types of polymeric networks: Gels</i>	<i>8</i>
	<i>2.1.3 Crosslink mechanisms</i>	<i>9</i>
	<i>2.1.4 Reverible networks</i>	<i>10</i>
	<i>2.2 Mechanical response</i>	<i>11</i>
	<i>2.2.1 Macroscopic description</i>	<i>12</i>
	<i>2.2.2 Microscopic description</i>	<i>13</i>
	<i>2.3 Molecular dynamics</i>	<i>17</i>
	<i>2.3.1 Langevin dynamics</i>	<i>17</i>
	<i>2.3.2 Velocity Verlet</i>	<i>18</i>
<i>3</i>	<i>Numerical Solutions</i>	<i>19</i>
	<i>3.1 Simulation protocol</i>	<i>19</i>
	<i>3.1.1 Description of the system</i>	<i>19</i>
	<i>3.1.2 LAMMPS</i>	<i>19</i>
	<i>3.2 Results</i>	<i>19</i>
<i>4</i>	<i>Conclusion</i>	<i>21</i>
<i>5</i>	<i>Bibliography</i>	<i>23</i>



*1*

*Introduction*



## 2

# *Theoretical Framework*

### *2.1 Hydrogels*

*Introduction* From bibliographic review, we can say that a hydrogel is a polymeric network that has the capacity of swelling[cites]. Some examples are, polyacrylamide, sodium polyacrylate, Poly(vinyl alcohol), Poly(ethylene glycol), Poly(hydroxyethyl methacrylate), agarose, alginate, gelatin, pectin, starch, cellulose-based networks, protein networks, among others. In order to try to understand (some of) the properties of the hydrogels, we are going to explore what is a polymeric network and what is the capacity of swelling.

In general terms, a polymeric network is a three dimensional structure formed by long polymer chains that are interconnected. Meanwhile, the swellability is defined as the capacity to absorb significant amounts of a solvent without dissolving, resulting in an increase volume. Since the swellability is a “capacity” of the network, we are going to start by exploring what is a polymeric structure.

#### *2.1.1 Polymeric networks*

*Introduction* From a structural perspective, polymer networks consist of network “junctions”, which consist of three or more strands connected by a mechanism. This mechanism is commonly refer as “crosslink” and can be describe through physical interactions or covalent bonds. On the other hand, we recall that a polymer is a macromolecule composed by monomers that are covalently bondend together forming a strand. Monomers can possess specific functional groups or reactive sites, which determine the manner in which monomers bind together. This, in turn, influences the structural and property characteristics of the resulting polymer. Part of the swelling capacity can be explained by the type of monomers in the network, meanwhile the structural frameworks allows to explain the mechanical response and the swelling.

*Swellability* The capacity for substantial solvent absorption and expansion of hydrogels is attributable to the expansion of the network due to osmotic

pressure and the hydrophilic functional groups of the monomers that constitute hydrogels. Some of the key hydrophilic groups are, hydroxyl group, amide group, carboxylate anion, ether group. The hydrophilic phenomenon, from a chemical perspective, occurs when molecules possess polar or charged functional groups that spontaneously form hydrogen bonds or electrostatic interactions with water, enabling water to diffuse over the surface. Nevertheless, the network's integrity remains intact due to the crosslink mechanism.

*Crosslink* The underlying principles of crosslink mechanism are the physical interactions and covalent bonds. However it is important to acknowledge that, for example, given sufficiently strong and static physical interactions, physical networks can behave identically to covalent bonded networks; alternatively, the incorporation of mechanisms for covalent bond exchange can result in chemical networks that exhibit adaptable mechanical properties regulated by external stimuli [cite]. Consequently, an emphasis on bond strengths and exchange rates provides more informative insights for accurately inferring the properties of hydrogels.

With this understanding, a covalent bond is defined as a specific type of chemical bond that occurs when two atoms share one or more pairs of electrons. On the other hand, a physical interaction is defined as a non-covalent force that describes how atoms, ions, or molecules attract or repel each other without forming new chemical entities. The covalent bond is the result of quantum mechanical interactions between atomic orbitals. In these interactions, shared electrons occupy a molecular orbital that extends over both atoms. In contrast, physical interactions are attributed to electrostatic, van der Waals, or dipole forces, arising from the redistribution of electron density and the consequent energy alterations between particles.

Now we can dive into the different types of polymer networks and the different types of crosslink mechanisms. After that, then we are going to spend some paragraphs into explore the ideas of mechanical response through constitutive relations. In order to end with the mechanical response of hydrogels and some connections with the polymeric network.

### 2.1.2 Types of polymeric networks: Gels

*Introduction* In general terms a polymeric network can be divided into one of four major classes: thermosets, thermoplastics, elastomers, and gels. Thermosets are rigid, covalently bonded polymer networks with high modulus, which are insoluble and degrade rather than melt upon heating. In contrast, thermoplastics are held together by strong physical interactions, allowing them to be remolded and recycled when heated. Elastomers are soft, deformable with covalent networks used above their glass transition temperature, capable of large reversible extensions. Finally, gels are liquid-swollen networks, either covalent or physical interactions, that are soft and highly deformable.



*Gels* In detail, a gel is a three-dimensional, crosslinked polymer network formed by physical or chemical crosslinks, which serve to trap the solvent molecules via intermolecular interactions, including hydrogen bonding and osmotic forces. This process prevents the fluid from flowing freely. This results in a material with both solid and liquid characteristics—elasticity from the polymer network and fluidity from the entrapped solvent. This description resembles that of a hydrogel. The hydrogel, however, is a specific type of gel in which the solvent is water and the polymers are hydrophilic.

*Gel point* The classification of a polymer network as a gel is characterized by the formation of a continuous, system-spanning (infinite) network through the process of polymerization or crosslinking mechanisms. This phenomenon is indicative of the percolation<sup>1</sup> of the polymeric network. And it is known as the gel point. At this point, the polymer chains become sufficiently interconnected through crosslinks to create a macroscopic network that spans the entire volume, causing the material to gain elasticity and lose fluidity, transitioning<sup>2</sup> it from a viscous liquid (sol) to a solid-like gel.

Finally, it must be mentioned that not all polymer networks can achieve a gel point. To reach this point requires sufficient network connectivity due to enough reactive sites and a high enough crosslinking density. For instance, linear, unbranched, or insufficiently crosslinked polymers remain soluble and do not gel.

### 2.1.3 Crosslink mechanisms

*Intro* According to the literature, the most common classification is typically as physical or covalent hydrogels. In regards to the main crosslink mechanism present in the polymeric network. However, it is important to note that, although the crosslink mechanism plays a significant role in network integrity, it is not the sole mechanism that can adequately describe the mechanical response in terms of network structure. In this regard, three primary crosslink mechanisms can be identified: covalent, physical interactions, and mechanical<sup>3</sup>.

*Covalent Crosslinking* Polymer chains are linked by covalent bonds, which are typically formed through free-radical polymerization, click chemistry, or UV-induced reactions. This results in a static, stable, and robust network with high mechanical strength and low reversibility. However, when dynamic covalent chemistry is applied, it can allow bond exchange and self-healing properties.

*Physical Crosslinking* Polymer chains are held together by non-covalent interactions, including hydrogen bonding, ionic interactions, hydrophobic associations, and van der Waals forces. Given the possibility of bond exchange

<sup>1</sup> In physics, percolation describes the emergence of large-scale connectivity in disordered systems. On the other hand, mathematically, is the study of cluster formation in a random graph or lattice when sites or bonds are occupied with a given probability.

<sup>2</sup> This transition is a percolation threshold where the molecular weight and network correlation length diverge.

<sup>3</sup> No estoy seguro si hablar de técnicas de sintetización o si explicar mejor los mecanismos de bond exchange en redes covalentes y en redes físicas.

under normal conditions, the network is dynamic. Therefore, they tend to be softer and less mechanically robust in comparison to covalently crosslinked hydrogels. Finally, these networks are reversible, enabling self-healing, shape-memory, and stimuli-responsive behaviors.

*Mechanical Crosslinking* Finally, these types of crosslinked networks are held together by physical entanglements or interpenetrating polymer chains. Examples include double-network hydrogels, slide-ring gels, and highly entangled architectures. This provides toughness and elasticity properties by dissipating energy through chain movement and entanglement.

#### 2.1.4 Reversible networks

*Intro* Another common classification in literature is to categorize the polymeric network as reversible or irreversible. It is a common association that networks with physical crosslink mechanisms are reversible, while covalently crosslinked networks are irreversible. However, regardless of the crosslink mechanism, the network can be shown to be reversible.

*Physical networks* The interactions can spontaneously break and reform due to thermal fluctuations or changes in the microenvironment, such as pH, ionic strength, temperature. When external stress or energy disturbs the network, some physical bonds dissociate. Free chain segments then seek new partners, allowing dynamic rejoining at different sites. This ongoing exchange can lead to self-healing, viscoelastic behavior, and adaptability of the hydrogel. The equilibrium and kinetics of bond formation/dissociation can be tuned by controlling the physical interactions.

*Covalent networks* In “dynamic” covalent bonds, such as imine, boronate ester, thioester, disulfide, and transesterification, the network has the capacity to break and reform via chemical equilibrium. This process is driven by external stimuli, including temperature, pH, or catalysts. The external stimuli facilitate the exchange of polymer chains at crosslinked points through either associative or dissociative mechanisms. The associative mechanism occurs when new bonds form before old bonds break. In contrast, the dissociative mechanism occurs when old bonds break before new bonds form. The exchange of polymer chains enables the material to exhibit self-healing, stress relaxation, and shape adaptability while maintaining the mechanical strength provided by covalent bonds to the network. Finally, it is important to note that the energy barrier for exchange, bond stability, and stimulus-dependence govern the rate and reversibility of the process.

## 2.2 Mechanical response

The concept of a material's mechanical response describes the relationship between the deformation of a material and the applied stress and/or shear rate. Nevertheless, this relationship can be described from a macroscopic scale and also from a microscopic scale. At the macroscopic level, the description captures the effective mechanical response as a continuum property. At the microscopic level, it provides insights into the origin of the mechanical response and how structural features at small scales control the macroscopic response. In this section, we will delve into the various descriptions and explore the quantification of this relationship.

*Constitutive relations* The relationship between deformation and stress is expressed through a constitutive equation. This equation is a mathematical tool that quantifies the relationship. It is used to predict or model material behavior, as reflected by empirical observations. Additionally, these equations can be defined from both the microscopic and macroscopic scale. These two scales are linked through the implementation of averaging or homogenization procedures. However, there is a difference in interpretation and application. These issues will be addressed in the following sections.

*Tensors* Before proceeding, it is necessary to know the quantitative representation of stress and strain. Both quantities are mathematically represented as second-rank tensors, which can be algebraically expressed as a  $n \times n$  matrix. Furthermore, it is important to interpret tensors as a generalization of scalars, vectors, and matrices to describe physical quantities which depend on direction and coordinate system, yet follow specific transformation rules under changes of coordinates. Allowing to quantify not just the magnitude but also orientation and how the physical quantity acts along different directions in space. In summary, the tensor enables the capture of multidirectional physical properties that remain constant under coordinate changes<sup>4</sup>. Keeping this in mind, we can proceed with a description of the strain tensor. The stress tensor will be defined until the microscopic section, together with the relation to the microscopic-macroscopic relation. This is due to the scope of the thesis.

*Strain* In physics, the deformation of a material relative to its original shape under applied forces is quantified by the relative displacement between points in the material. This measure is represented by the dimensionless strain tensor (eqn (2.1)). This quantification tool enables the description of normal strain, such as elongation or compression, through the use of diagonal terms, and shear strain via off-diagonal terms.


(Add the derivation of the book?)

In the following methodology, we will couple the macroscopic and microscopic scale: We employ the macroscopic constitutive relations; however, the stress tensor is defined from the microscopic scale.

$$\epsilon_{ij} = \frac{1}{2} \left( \frac{\partial u_i}{\partial x_j} + \frac{\partial u_j}{\partial x_i} \right) \quad (2.1)$$

This mathematical representation is only valid for infinitesimal small deformations. Where  $u_i$  are the component of the displacement vector field and  $x_j$  are the spatial coordinates.

<sup>4</sup> Quiero poner una imagen de como se ve el tensor y así con proyecciones en el plano cartesiano



### 2.2.1 Macroscopic description

Now that we know how to quantify strain, we can quantify the four main mechanical responses, elastic, plastic, viscoelastic, and viscoplastic. In a broad sense, the elastic relation is when the material returns to its original shape after load removal. In contrast, the plastic deformation is a permanent deformation once stress exceeds a yield threshold  $\sigma_y$ . Furthermore, the viscoelastic response is time-dependent combining the elastic and viscous behaviour. Finally, the viscoplastic, combines the irreversible plastic strain with a rate-dependent viscous effects.

**Elastic relation** An elastic deformation is when the material returns to its original configuration once the stress is removed. The quantification of this response is given by a linear equation (equation (2.2)), with a proportionality constant known as elastic modulus or Young's modulus. The equation (2.2) is interpreted as the stiffness, that is how the material resists deformation. Some examples of this type of deformation are the stretching of a metal spring within its elastic limit or the compression of a rubber ball.

**Plastic relation** In contrast, a plastic deformation is when the material has an irreversible change in the shape or size. It is generally accepted that a material first enters an elastic regime and then reaches a yield point. After this point, the deformation is irreversible. The quantification of the plastic relation (eqn (2.4)) typically links stress and plastic strain as a function of the current stress and internal variables. This is valid when the deformation goes beyond the yield stress and the specific algebraic expression is dictated by the material's properties.

It is important to acknowledge that the definition of yield stress is also dependent on the material and the loading conditions. For this reason, there are

Elastic deformation equations

$$\sigma = E\epsilon \quad (2.2)$$

$$\sigma_{ij} = C_{ijkl}\epsilon_{kl} \quad (2.3)$$

Plastic Deformation equations

$$\dot{\epsilon}_p = f(\sigma, \text{Internal variables}), \quad \sigma > \sigma_y. \quad (2.4)$$

Von Mises Criterion

$$\sigma_y = \sqrt{\frac{3}{2} s : s} \quad (2.5)$$

where  $s$  is the deviatoric stress tensor.

Tresca criterion

$$\sigma_y = \max(|\sigma_1 - \sigma_2|, |\sigma_2 - \sigma_3|, |\sigma_3 - \sigma_1|) \quad (2.6)$$

where  $\sigma_1, \sigma_2, \sigma_3$  are the principal stresses.

Viscoelastic deformation

The following equation is the generalized expression of the Maxwell or Kelvin-Voigt model:

$$\sigma(t) = \int_0^t G(t - \tau) \frac{d}{d\tau} \epsilon(\tau) d\tau. \quad (2.7)$$

Where  $\tau$  is a dummy variable and  $G(t)$  is the time-dependent relaxation modulus.

Viscoplastic deformation

$$\dot{\epsilon}_p = f(\sigma, \sigma_y, \dot{\epsilon}, \text{Internal variables}) \quad (2.8)$$

many yield criteria developed for different materials and conditions, such as Drucker-Prager, Mohr-Coulomb, Von Mises or Tresca criterion. The two most common yield criteria are the Von Mises and Tresca criterion. The von Mises yield criterion it is commonly used for ductile materials. It is base on the energy associated with shape change. This is defined by a critical value (as shown in the equation (2.5)) in terms of the distortional energy or equivalent shear stress and independent of hydrostatic pressure. On the other hand, the Tresca yield criterion is a max-shear based criterion. It is based on the yield strength in simple tension (see equation (2.6)).

*Viscoelastic relation* A viscoelastic deformation is defined as the process by which a material partially “stores” elastic energy and partially dissipates energy. The quantification of the relation is by relating the instantaneos stress, strain and a time-dependent relaxation modulus (equation (2.7)). This relationship also enables the description and modeling of memory effects and rate dependence, which are commonly observed in polymers, biological tissues, and certain soft solids.

**Not sure if I want to explain more the relaxation modulus.**

*Viscoplastic relation* Finally, a viscoplastic is to describe when a material flows plastically like a viscous fluid under stress beyond the yield stress. The quantification is determined by a function of strain rate, stress, yield stress, and internal variables (see equation (2.8)). As with the plastic relation, the specific algebraic expression is dictated by the material’s properties. However, this relationship is used to describe materials that initially respond as solids below the yield stress but flow like viscous fluids once yielding occurs.

**Add examples of specific constitutive equations**

### 2.2.2 Microscopic description

*Stress* In continuum mechanics and physics, the measure of internal forces distributed within a material that arise in response to external loads is refered as stress. As before, this measure is represented by a second-order tensor with units of  $\text{kg m}^{-1} \text{s}^{-2}$ . The mathematical representation of the stress tensor is given by the Cauchy stress tensor, which relates a traction vector  $\vec{T}$  acting on a surface  $\vec{n}$  with the stress tensor  $\sigma$ , equation (??).

*Motivation: Molecular stress is equivalent to continuum stress* ... This derivation can be found in the apendix of [Admal and Tadmor, 2010]<sup>5,6</sup> Consider a system of  $N$  interacting particles with each particle position given by


$$\vec{r}_\alpha = \vec{r} + \vec{s}_\alpha, \quad (2.9)$$

where  $\vec{r}$  is the position of the center of mass of the system and  $\vec{s}_\alpha$  is the position of each point relative to the center of mass. Hence, we can express the

<sup>5</sup> Describe more if what is done in this article

<sup>6</sup> (Eventualmente pondré esto en párrafo)

Notation:  $\sigma$  Tensor,  $\vec{\sigma}$  vector,  $\sigma_{i,j}$  tensor,  $\bar{\sigma}$  time average,



momentum of each particle as

$$\vec{p}_\alpha = m_\alpha (\dot{\vec{r}} + \dot{\vec{s}}_\alpha) = m_\alpha (\dot{\vec{r}} + \vec{v}_\alpha^{\text{rel}}). \quad (2.10)$$

Before starting the procedure, let's take into account that the center of mass of the system is given by

$$\vec{r} = \frac{\sum_\alpha m_\alpha \vec{s}_\alpha}{\sum_\alpha m_\alpha}, \quad (2.11)$$

and by replacing (2.9) in (2.10) we get the following relations, which will be used later,

$$\sum_\alpha m_\alpha \vec{r}_\alpha = \vec{0}, \quad \sum_\alpha m_\alpha \vec{v}_\alpha^{\text{rel}} = \vec{0}. \quad (2.12)$$

Now we can start by computing the time derivative of tensorial product  $\vec{r}_\alpha \otimes \vec{p}_\alpha$ <sup>7</sup>,

$$\frac{d}{dt}(\vec{r}_\alpha \otimes \vec{p}_\alpha) = \underbrace{\vec{v}_\alpha^{\text{rel}} \otimes \vec{p}_\alpha}_{\text{Kinetic term}} + \underbrace{\vec{r}_\alpha \otimes \vec{f}_\alpha}_{\text{Virial term}}, \quad (2.13)$$

<sup>7</sup> It is interesting to note that the tensorial product  $\vec{r}_\alpha \otimes \vec{p}_\alpha$  has units of action and by taking the time derivative we are dealing with terms that has units of energy.

which is known as the *dynamical tensor virial theorem* and it is simply an alternative form to express the balance of linear momentum. This theorem becomes useful after making the assumption that there exists a time scale  $\tau$ , which is short relative to macroscopic processes but long relative to the characteristic time of the particles in the system, over which the particles remain close to their original positions with bounded positions and velocities. Taking advantage of this property we can compute the time average of (2.13),

$$\frac{1}{\tau}(\vec{r}_\alpha \otimes \vec{p}_\alpha) \Big|_0^\tau = \overline{\vec{v}_\alpha^{\text{rel}} \otimes \vec{p}_\alpha} + \overline{\vec{r}_\alpha \otimes \vec{f}_\alpha}. \quad (2.14)$$

Assuming that  $\vec{r}_\alpha \otimes \vec{p}_\alpha$  is bounded, and the time scales between microscopic and continuum processes are large enough, the term on the left-hand side can

be as small as desired by tacking  $\tau$  sufficiently large and by summing over all particles we achieve the *tensor virial theorem*:

$$\overline{\mathbf{W}} = -2\overline{\mathbf{T}}, \quad (2.15)$$

where

$$\overline{\mathbf{W}} = \sum_{\alpha} \overline{\vec{r}_{\alpha} \otimes \vec{f}_{\alpha}} \quad (2.16)$$

is the time-average virial tensor and

$$\overline{\mathbf{T}} = \frac{1}{2} \sum_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}} \otimes \vec{p}_{\alpha}} \quad (2.17)$$

is the time-average kinetic tensor. This expression for the tensor virial theorem applies equally to continuum systems that are not in macroscopic equilibrium as well as those that are at rest.

The assumption of the difference between the time scales allow us to simplify the relation by replacing (2.10) in (2.17), so that,

$$\overline{\mathbf{T}} = \frac{1}{2} \sum_{\alpha} m_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}} \otimes \vec{v}_{\alpha}^{\text{rel}}} + \frac{1}{2} \left[ \sum_{\alpha} m_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}}} \right] \otimes \dot{\vec{r}}, \quad (2.18)$$

which is not the simplification we expected, however, by the relations from (2.12), equation (2.18) simplifies to<sup>8</sup>

$$\overline{\mathbf{T}} = \frac{1}{2} \sum_{\alpha} m_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}} \otimes \vec{v}_{\alpha}^{\text{rel}}}. \quad (2.19)$$

On the other hand, instead of reducing the expression, we start to create the conection with the Cauchy stress tensor by distributing (2.16) into an internal and external contributions,

$$\overline{\mathbf{W}} = \underbrace{\sum_{\alpha} \overline{\vec{r}_{\alpha} \otimes \vec{f}_{\alpha}^{\text{int}}}}_{\overline{\mathbf{W}}_{\text{int}}} + \underbrace{\sum_{\alpha} \overline{\vec{r}_{\alpha} \otimes \vec{f}_{\alpha}^{\text{ext}}}}_{\overline{\mathbf{W}}_{\text{ext}}}. \quad (2.20)$$

The time-average internal virial tensor takes into account the interaction between particle  $\alpha$  with the other particles in the system, meanwhile, the time-average external virial tensor considers the interaction with atoms outside the system, via a traction vector  $\vec{t}$  and external fields acting on the system represented by  $\rho \vec{b}$ , where  $\rho$  is the mass density of it and  $\vec{b}$  is the body force per unit mass applied by the external field. Therefore we can express the following,

$$\sum_{\alpha} \overline{\vec{r}_{\alpha} \otimes \vec{f}_{\alpha}^{\text{ext}}} := \int_{\delta\Omega} \vec{\xi} \otimes \vec{t} dA + \int_{\Omega} \vec{\xi} \otimes \rho \vec{b} dV. \quad (2.21)$$

Where  $\vec{\xi}$  is a position vector within the domain  $\Omega$  occupied by the system of particles with a continuous closed surface  $\delta\Omega$ . Assuming that  $\Omega$  is large enough to express the external forces acting on it in the form of the continuum traction vector  $\vec{t}$ .

<sup>8</sup> No estoy muy seguro si incluir una discusión acerca del término cinético en la expresión del virial. Posiblemente un párrafo... posiblemente lo ponga en la interpretación del teorema. También, no se si ir metiendo interpretación durante la derivación o no, pero bueno.

With this we can substitute the traction vector with  $\vec{t} = \sigma \vec{n}$ , where  $\sigma$  represent the Cauchy stress tensor and applying the divergence theorem in (2.21), we have

$$\overline{\mathbf{W}}_{\text{ext}} = \int_{\Omega} \left[ \vec{\xi} \otimes \rho \vec{b} + \text{div}_{\vec{\xi}} \left( \vec{\xi} \otimes \sigma \right) \right] dV = \int_{\Omega} \left[ \sigma^T + \vec{\xi} \otimes \left( \text{div}_{\vec{\xi}} \sigma + \rho \vec{b} \right) \right] dV \quad (2.22)$$

Since we assume that we are under equilibrium conditions, the term  $\text{div}_{\vec{\xi}} \sigma + \rho \vec{b}$  is zero (2.22) it simplifies to

$$\overline{\mathbf{W}}_{\text{ext}} = V \sigma^T. \quad (2.23)$$

By tacking into account that we integrate over the domain  $\Omega$  we can say that we compute the spatial average of the Cauchy stress tensor,

$$\sigma_{\text{av}} = \frac{1}{V} \int_{\Omega} \sigma dV, \quad (2.24)$$

in which  $V$  is the volume of the domain  $\Omega$ . Replacing (2.23) into (2.20), the tensor virial theorem (2.15) can be expressed as,

$$\sum_{\alpha} \overline{\vec{r}_{\alpha} \otimes \vec{f}_{\alpha}^{\text{int}}} + V \sigma_{\text{av}}^T = - \sum_{\alpha} m_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}} \otimes \vec{v}_{\alpha}^{\text{rel}}}. \quad (2.25)$$

Finally, solving for the Cauchy Stress tensor we get,

$$\sigma_{\text{av}} = -\frac{1}{V} \left[ \sum_{\alpha} \overline{\vec{f}_{\alpha}^{\text{int}} \otimes \vec{r}_{\alpha}} + \sum_{\alpha} m_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}} \otimes \vec{v}_{\alpha}^{\text{rel}}} \right], \quad (2.26)$$

an expression that describe the macroscopic stress tensor in terms of microscopic variables<sup>9</sup>.

To end the section it is important to show that (2.26) is symmetric. Therefore, we rewrite the internal force as the sum of forces between the particles,

$$\vec{f}_{\alpha}^{\text{int}} = \sum_{\beta \neq \alpha} \vec{f}_{\alpha\beta}, \quad (2.27)$$

and substituting (2.27) into (2.26), we have

$$\sigma_{\text{av}} = -\frac{1}{V} \left[ \sum_{\alpha, \beta \neq \alpha} \overline{\vec{f}_{\alpha\beta} \otimes \vec{r}_{\alpha}} + \sum_{\alpha} m_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}} \otimes \vec{v}_{\alpha}^{\text{rel}}} \right]. \quad (2.28)$$

Due to the property  $\vec{f}_{\alpha\beta} = -\vec{f}_{\beta\alpha}$  we obtain the following identity

$$\sum_{\alpha, \beta \neq \alpha} \vec{f}_{\alpha\beta} \otimes \vec{r}_{\alpha} = \frac{1}{2} \sum_{\alpha, \beta \neq \alpha} \left( \vec{f}_{\alpha\beta} \otimes \vec{r}_{\alpha} + \vec{f}_{\beta\alpha} \otimes \vec{r}_{\beta} \right) = \frac{1}{2} \sum_{\alpha, \beta \neq \alpha} \vec{f}_{\alpha\beta} \otimes (\vec{r}_{\alpha} - \vec{r}_{\beta}). \quad (2.29)$$

Therefore, by replacing the identity of (2.29) into (2.28), we have

$$\sigma_{\text{av}} = -\frac{1}{V} \left[ \frac{1}{2} \sum_{\alpha, \beta \neq \alpha} \overline{\vec{f}_{\alpha\beta} \otimes (\vec{r}_{\alpha} - \vec{r}_{\beta})} + \sum_{\alpha} m_{\alpha} \overline{\vec{v}_{\alpha}^{\text{rel}} \otimes \vec{v}_{\alpha}^{\text{rel}}} \right], \quad (2.30)$$

<sup>9</sup> It is important to acknowledge that several mathematical subtleties were not taken into consideration, however all the mathematical formality is addressed by Nikhil Chandra Admal and E. B. Tadmor in [Admal and Tadmor, 2010]



expressed with indexical notation and using the eistein summation convention,

$$\sigma_{ij}^{\text{av}} = -\frac{1}{V} \left[ \frac{1}{2} \sum_{\alpha, \beta \neq \alpha} \overline{f_i^{\alpha\beta} r_j^\alpha + f_i^{\beta\alpha} r_j^\beta} + \sum_{\alpha} m_{\alpha} \overline{v_i^{\alpha \text{ rel}} v_j^{\alpha \text{ rel}}} \right], \quad (2.31)$$

which is the same expression implemented in LAMMPS[Thompson et al., 2022a].<sup>10</sup>

<sup>10</sup> No se si poner la referencia a la pagina de documentacion [https://docs.lammps.org/compute\\_stress\\_atom.html](https://docs.lammps.org/compute_stress_atom.html)

## 2.3 Molecular dynamics

*Intro* Here is the intro

### 2.3.1 Langevin dynamics

From a general point of view there are two types of methods to make a quative description of systems: one focused on simulating dynamics at the microscale, and the other dedicated to deriving or establishing evolutionary equations at the macroscale[Wang et al., 2025]. Since the assumption is made that the mechanical response of a hydrogel is predominantly derived from its internal structure<sup>11</sup> we choose to simulate the dynamics at the microscale. Additionally, by treating the hyrogel as a colloid, permits applying molecular dynamics to model its response under shear deformation. Finally, there are two commonly used mathematical frameworks to model the molecular dynamics, the continuous time random walk (CTRW) model and the Langevin equation[Wang et al., 2025], in this work we decided<sup>12</sup> to use the langevin dynamics mathematical framework.

<sup>11</sup> Poner citas que desmuestren que no es hipótesis, si no que se sabe

<sup>12</sup> Supongo que eventualmente justificaré la desición.

This is because, the solid phase of the colloid has a large mass and will change their momenta after many collisions with the solvent molecules and the picture which emerges is that of the heavy particles forming a system with a much longer time scale than the solvent molecules[Thijssen, 2007] and Langevin theory takes advantage of this difference in time scale to eliminate the details of the degrees of freedom of the solvent particles and represent their effect by stochastic and dissipative forces allowing longer simulations that would be impossible if the solvent were explicitly included[Pastor, 1994]. However, the representation of the solvent by a stochastic and dissipative force, introduce the problem of characterize two very different timescales, one associated with the slow relaxation of the initial velocity of the brownian particle and another linked to the frequent collisions that the brownian particle suffers with particles of the bath[Hansen and McDonald, 2006]<sup>13</sup>. Therefore, two terms are used to create a mathematical representation of the solvent: a frictional force proportional to the velocity of the particle and a fluctuating force. Hence,

<sup>13</sup> Para traer a colación la sensibilidad de la respuesta mecánica al parámetro de damp.

$$m \frac{d\vec{v}(t)}{dt} = \vec{F}(t) - m\gamma\vec{v}(t) + \vec{R}(t). \quad (2.32)$$

The friction constant  $\gamma$ <sup>14</sup> parametrises the effect of solvent damping and activation and is commonly referred to as the collision frequency in the simulation literature, even though formally a Langevin description implies that the solute suffers an infinite number of collisions with infinitesimally small momentum transfer. Also, the fact that the second term is not a function of the position of any of the particles involves the neglect of hydrodynamic interaction or spatial correlation in the friction kernel spatial correlation in the friction kernel[Pastor, 1994]. On the other hand,  $\vec{R}(t)$ <sup>15</sup> is a “random force” subject to the following conditions

$$\begin{aligned}\langle \vec{R}(t) \rangle &= 0 \\ \langle \vec{R}(t) \vec{R}(t') \rangle &= 2k_B T \gamma \delta(t - t')\end{aligned}$$

The no time correlation is equivalent to assuming that the viscoelastic relaxation of the solvent is very rapid with respect to solute motions<sup>16</sup>.

In comparing the results of Langevin dynamics with those of other stochastic methods [28-31], the relevant variable is the velocity relaxation time,  $\tau_v$  which equals  $\gamma^{-1}$ [Pastor, 1994] The Langevin equation improves conformational sampling over standard molecular dynamics[Paquet and Viktor, 2015].

- Hablar acerca de que la fuerza aleatoria puede tener distribución gaussiana, pero no necesariamente.
- hablar de la ecuación de Green-Kubo:

$$\eta = \frac{V}{k_B T} \int_0^\infty \langle \sigma_{xy}(t) \sigma_{xy}(0) \rangle dt$$

- No se que tanto hablar de la idea de correlación y su aplicación en estos temas.

### 2.3.2 Velocity Verlet

*Intro* The core concept of the Velocity Verlet algorithm is to update particle positions and velocities using both current and predicted accelerations, ensuring time-reversibility and energy conservation over long simulations. In systems governed by Langevin dynamics, the algorithm can incorporate random forces consistent with the fluctuation-dissipation theorem to simulate physically realistic Brownian motion.

From a mathematical point of view, this algorithm is a second-order integrator for ordinary differential equations. Furthermore, from a computational perspective, Velocity Verlet is an explicit algorithm, easy to implement, and efficient in term of memory usage. It requires only the positions, velocities, and accelerations from the previous timestep. Which allows efficient parallelization and eliminates the need for additional memory allocations per step.

<sup>14</sup> Cuidado con las unidades. Hacer análisis dimensional, porque por la condición de correlación en  $R$ ,  $\gamma$  ocupa tener unidades de masa entre tiempo, pero en la ecuación, solo ocupa unidades de  $1/s$ .

<sup>15</sup> No me acuerdo en donde está que se puede asumir que tiene distribución gaussiana.

<sup>16</sup> Grote and Hynes [26] have investigated this assumption for motions involving barrier crossing and have found that while it is seriously in error for passage over sharp barriers (such as 12 recombination); it is quite adequate for conformational transitions such as might be found in polymer motions.[Pastor, 1994]

# 3

## *Numerical Solutions*

### *3.1 Simulation protocol*

Description of the system

#### *3.1.1 Description of the system*

*Physical Parameters* Particle size, box length, packing fraction, temperature.

*Interaction potentials* WCA, patch-patches and swap.

#### *3.1.2 LAMMPS*

Why use lammmps and stuff

*Implementation* About tables and the general script.

### *3.2 Results*

So.. The results and stuff



4

## *Conclusion*

We conclude that we have a conclusion in two years.

[]

## Bibliography

- Nikhil Chandra Admal and E. B. Tadmor. A unified interpretation of stress in molecular systems. *Journal of Elasticity*, 100(1):63–143, June 2010. ISSN 1573-2681. DOI: 10.1007/s10659-010-9249-6.
- Enas M. Ahmed. Hydrogel: Preparation, characterization, and applications: A review. *Journal of Advanced Research*, 6(2):105–121, March 2015. ISSN 2090-1232. DOI: 10.1016/j.jare.2013.07.006.
- Md Shahriar Ahmed, Sua Yun, Hae-Yong Kim, Sunho Ko, Mobinul Islam, and Kyung-Wan Nam. Hydrogels and microgels: Driving revolutionary innovations in targeted drug delivery, strengthening infection management, and advancing tissue repair and regeneration. *Gels*, 11(3):179, March 2025. ISSN 2310-2861. DOI: 10.3390/gels11030179.
- Shabnam Z. Bonyadi, Md. Mahmudul Hasan, Jiho Kim, Samsul Mahmood, Kyle D. Schulze, and Alison C. Dunn. Review: Friction and lubrication with high water content crosslinked hydrogels. *Tribology Letters*, 68(4): 119, October 2020. ISSN 1573-2711. DOI: 10.1007/s11249-020-01352-3.
- Moises Bustamante-Torres, David Romero-Fierro, Belén Arcentales-Vera, Kenia Palomino, Héctor Magaña, and Emilio Bucio. Hydrogels classification according to the physical or chemical interactions and as stimuli-sensitive materials. *Gels*, 7(4):182, oct 2021. DOI: 10.3390/gels7040182.
- Ramon Castaneda-Priego. Colloidal soft matter physics. *Revista mexicana de fisica*, 67(5), October 2021. ISSN 0035-001X. DOI: 10.31349/revmex-fis.67.050101.
- R. Clausius. Xvi on a mechanical theorem applicable to heat. *The London, Edinburgh, and Dublin Philosophical Magazine and Journal of Science*, 40(265):122–127, August 1870. ISSN 1941-5982, 1941-5990. DOI: 10.1080/14786447008640370.
- Jader Colombo and Emanuela Del Gado. Stress localization, stiffening, and yielding in a model colloidal gel. *Journal of Rheology*, 58(5):1089–1116, September 2014. ISSN 0148-6055, 1520-8516. DOI: 10.1122/1.4882021.

- Santiago Correa, Abigail K. Grosskopf, Hector Lopez Hernandez, Doreen Chan, Anthony C. Yu, Lyndsay M. Stapleton, and Eric A. Appel. Translational applications of hydrogels. *Chemical Reviews*, 121(18):11385–11457, September 2021. ISSN 0009-2665. DOI: 10.1021/acs.chemrev.0c01177.
- Nicoletta Gnan, Lorenzo Rovigatti, Maxime Bergman, and Emanuela Zaccarelli. In silico synthesis of microgel particles. *Macromolecules*, 50(21):8777–8786, nov 2017. ISSN 0024-9297, 1520-5835. DOI: 10.1021/acs.macromol.7b01600.
- Yuwei Gu, Julia Zhao, and Jeremiah A. Johnson. Polymer networks from plastics and gels to porous frameworks. *Angewandte Chemie International Edition*, 59(13):5022–5049, 2020. ISSN 1521-3773. DOI: 10.1002/anie.201902900.
- Jean Pierre Hansen and Ian R. McDonald. *Theory of simple liquids*. Elsevier Academic Press, 2006.
- Laura F. Hart, Jerald E. Hertzog, Phillip M. Rauscher, Benjamin W. Rawe, Marissa M. Tranquilli, and Stuart J. Rowan. Material properties and applications of mechanically interlocked polymers. *Nature Reviews Materials*, 6(6):508–530, June 2021. ISSN 2058-8437. DOI: 10.1038/s41578-021-00278-z.
- Nandan Kumar, Soumen Saha, and G. Narahari Sastry. Towards developing a criterion to characterize non-covalent bonds a quantum mechanical study. *Physical Chemistry Chemical Physics*, 23(14):8478–8488, April 2021. ISSN 1463-9084. DOI: 10.1039/D0CP05689H.
- A. K. Lele, M. M. Hirve, M. V. Badiger, and R. A. Mashelkar. Predictions of bound water content in poly(n-isopropylacrylamide) gel. *Macromolecules*, 30(1):157–159, January 1997. ISSN 0024-9297. DOI: 10.1021/ma950894l.
- Jing-Tao Lu, Bing-Zhong Hu, Per Hedegaard, and Mads Brandbyge. Semi-classical generalized langevin equation for equilibrium and nonequilibrium molecular dynamics simulation. *Progress in Surface Science*, 94(1):21–40, February 2019. ISSN 0079-6816. DOI: 10.1016/j.progsurf.2018.07.002.
- Jaya Maitra and Vivek Kumar Shukla. Cross-linking in hydrogels - a review. *American Journal of Polymer Science*, 4(2):25–31, /26/2014. ISSN 2163-1352.
- Alexander S. Novikov. Non-covalent interactions in polymers. *Polymers*, 15(5):1139, January 2023. ISSN 2073-4360. DOI: 10.3390/polym15051139.
- Eric Paquet and Herna L. Viktor. Molecular dynamics, monte carlo simulations, and langevin dynamics a computational review. *BioMed Research International*, 2015:183918, 2015. ISSN 2314-6133. DOI: 10.1155/2015/183918.



Giorgio Parisi. *Statistical field theory*. Addison Wesley, 1988.

R. W. Pastor. Techniques and applications of langevin dynamics simulations. In G. R. Luckhurst and C. A. Veracini, editors, *The Molecular Dynamics of Liquid Crystals*, pages 85–138. Springer Netherlands, Dordrecht, 1994. ISBN 978-94-011-1168-3. DOI: 10.1007/978-94-011-1168-3-5.

Francesco Picchioni and Henky Muljana. Hydrogels based on dynamic covalent and non covalent bonds: A chemistry perspective. *Gels*, 4(1):21, March 2018. ISSN 2310-2861. DOI: 10.3390/gels4010021.

Arumugasamy Sathiya Priya, Rajaraman Premanand, Indhumathi Ragupathi, Vijayabhaskara Rao Bhaviripudi, Radhamanohar Aepuru, Karthik Kannan, and Krishnamoorthy Shanmugaraj. Comprehensive review of hydrogel synthesis, characterization, and emerging applications. *Journal of Composites Science*, 8(11):457, November 2024. ISSN 2504-477X. DOI: 10.3390/jcs8110457.

Lorenzo Rovigatti, Nicoletta Gnan, Andrea Ninarello, and Emanuela Zaccarelli. Connecting elasticity and effective interactions of neutral microgels: The validity of the hertzian model. *Macromolecules*, 52(13):4895–4906, July 2019. ISSN 0024-9297. DOI: 10.1021/acs.macromol.9b00099.

Francesco Sciortino. Threebody potential for simulating bond swaps in molecular dynamics. *The European Physical Journal E*, 40(1):3, January 2017. ISSN 1292-8941, 1292-895X. DOI: 10.1140/epje/i2017-11496-5.

H. Senff and W. Richtering. Temperature sensitive microgel suspensions: Colloidal phase behavior and rheology of soft spheres. *The Journal of Chemical Physics*, 111(4):1705–1711, July 1999. ISSN 0021-9606. DOI: 10.1063/1.479430.

Sergei S. Sheiko and Andrey V. Dobrynin. Architectural code for rubber elasticity: From supersoft to superfirm materials. *Macromolecules*, 52(20):7531–7546, October 2019. ISSN 0024-9297. DOI: 10.1021/acs.macromol.9b01127.

Valerio Sorichetti, Andrea Ninarello, José M. Ruiz-Franco, Virginie Hugouvieux, Walter Kob, Emanuela Zaccarelli, and Lorenzo Rovigatti. Effect of chain polydispersity on the elasticity of disordered polymer networks. *Macromolecules*, 54(8):3769–3779, apr 2021. ISSN 0024-9297, 1520-5835. DOI: 10.1021/acs.macromol.1c00176.

Valerio Sorichetti, Andrea Ninarello, José Ruiz-Franco, Virginie Hugouvieux, Emanuela Zaccarelli, Cristian Micheletti, Walter Kob, and Lorenzo Rovigatti. Structure and elasticity of model disordered, polydisperse, and defect-free polymer networks. *The Journal of Chemical Physics*, 158, feb 2023.

- Arun K. Subramaniyan and C.T. Sun. Continuum interpretation of virial stress in molecular simulations. *International Journal of Solids and Structures*, 45(14–15):4340–4346, July 2008. ISSN 00207683. DOI: 10.1016/j.ijsolstr.2008.03.016. URL <https://linkinghub.elsevier.com/retrieve/pii/S0020768308001248>.
- Robert J. Swenson. Comments on virial theorems for bounded systems. *American Journal of Physics*, 51(10):940–942, October 1983. ISSN 0002-9505, 1943-2909. DOI: 10.1119/1.13390. URL <https://pubs.aip.org/ajp/article/51/10/940/1052035/Comments-on-virial-theorems-for-bounded-systems>.
- Johannes M. M. H. Thijssen. *Computational physics*. Cambridge University Press, 2007.
- A. P. Thompson, H. M. Aktulga, R. Berger, D. S. Bolintineanu, W. M. Brown, P. S. Crozier, P. J. in ’t Veld, A. Kohlmeyer, S. G. Moore, T. D. Nguyen, R. Shan, M. J. Stevens, J. Tranchida, C. Trott, and S. J. Plimpton. Lammmps - a flexible simulation tool for particle-based materials modeling at the atomic, meso, and continuum scales. *Comp. Phys. Comm.*, 271:108171, 2022a. DOI: 10.1016/j.cpc.2021.108171.
- Aidan P. Thompson, Steven J. Plimpton, and William Mattson. General formulation of pressure and stress tensor for arbitrary many-body interaction potentials under periodic boundary conditions. *The Journal of Chemical Physics*, 131(15):154107, October 2009. ISSN 0021-9606, 1089-7690. DOI: 10.1063/1.3245303. URL <https://pubs.aip.org/jcp/article/131/15/154107/316893/General-formulation-of-pressure-and-stress-tensor>.
- Aidan P. Thompson, H. Metin Aktulga, Richard Berger, Dan S. Bolintineanu, W. Michael Brown, Paul S. Crozier, Pieter J. Veld, Axel Kohlmeyer, Stan G. Moore, Trung Dac Nguyen, Ray Shan, Mark J. Stevens, Julien Tranchida, Christian Trott, and Steven J. Plimpton. Lammmps - a flexible simulation tool for particle-based materials modeling at the atomic, meso, and continuum scales. *Computer Physics Communications*, 271:108171, February 2022b. ISSN 0010-4655. DOI: 10.1016/j.cpc.2021.108171.
- D. H. Tsai. The virial theorem and stress calculation in molecular dynamics. *The Journal of Chemical Physics*, 70(3):1375–1382, February 1979. ISSN 0021-9606, 1089-7690. DOI: 10.1063/1.437577. URL <https://pubs.aip.org/jcp/article/70/3/1375/89129/The-virial-theorem-and-stress-calculation-in>.
- Dimitris Vlassopoulos and Michel Cloitre. Tunable rheology of dense soft deformable colloids. *Current Opinion in Colloid & Interface Science*, 19(6):561–574, December 2014. ISSN 1359-0294. DOI: 10.1016/j.cocis.2014.09.007.

Heng Wang, Xuhao Li, Lijing Zhao, and Weihua Deng. Multiscale modeling and simulation for anomalous and nonergodic dynamics: From statistics to mathematics. *Fundamental Research*, January 2025. ISSN 2667-3258. DOI: 10.1016/j.fmre.2024.12.024.

Jianyu Xu, Xin Liu, Xiuyan Ren, and Guanghui Gao. The role of chemical and physical crosslinking in different deformation stages of hybrid hydrogels. *European Polymer Journal*, 100:86–95, March 2018. ISSN 0014-3057. DOI: 10.1016/j.eurpolymj.2018.01.020.

Peter J Yunker, Ke Chen, Matthew D Gratale, Matthew A Lohr, Tim Still, and A G Yodh. Physics in ordered and disordered colloidal matter composed of poly(n-isopropylacrylamide) microgel particles. *Reports on Progress in Physics*, 77(5):056601, May 2014. ISSN 0034-4885. DOI: 10.1088/0034-4885/77/5/056601.