DECLARATION OF PERFORMANCE

No PU-PIR-W-ST/2025/4

1.	**Unique identification code of the product-type:**	PU-PIR-W-ST <d_N> <t_{Ne}/t_{Ni}>
2.	**Intended use:**	External walls and wall cladding, walls (including partitions) and ceilings within the building envelope
3.	**Manufacturer:**	BALEX METAL Sp. z o.o., ul. Wejherowska 12C, 84-239 Bolszewo
4.	**System of Assessment and Verification of Constancy of Performance:**	1
5.	**Harmonised standard:**	EN 14509:2013
6.	**Notified bodies:**	System 1 - Technický a Skúšobný Ústav Stavebný, n. o. (No 1301) System 3 - Fires, s.r.o. (No 1396)
7.	**Declared performances:**	Tables 1÷14 (PIR 40kg/m^3; S250GD + PE15, PE25, PE35, PE35M, PUR55, PVC120; INOX [1.4301])

Designations of steel cladding profiling:
M16 – micro-profile; L – lined; 1L – clearline; 2L – double clearline; F – plain
Designations of INOX cladding profiling:
L-INOX – lined

Other designations:
d_N – nominal panel thickness [mm]
t_{Ne} – nominal thickness of external cladding [mm]
t_{Ni} – nominal thickness of internal cladding [mm]
AVCP – system of Assessment and Verification of Constancy of Performance
NPD – No Performance Determined

The performance of the product identified above is in conformity with the set of declared performances. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:
Chief Executive Officer

Bolszewo, 16.12.2025

Marek Dzikiewicz

BALEXMETAL Sp. z o.o.
84-239 Bolszewo, ul. Wejherowska 12C
tel. 58 778-44-44, fax 58 778-44-55
NIP 588-11-30-299
Regon 191112216 (1)

Table 1. Performances - mechanical resistance

(t_{Ne}/t_{ni} = 0,5/0,4)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{Ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{Cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_C [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000 = 1,25$ $\phi 100000 = 1,70$							
	Shear strength f_{Cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	231	231	232	227	221	217	213	209
		L	4	217	219	220	208	195	203	211	219
		L-INOX	4	170	168	167	168	170	177	184	192
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	223	228	232	227	221	214	207	200
		L	4	217	211	205	196	186	197	208	219
		L-INOX	4	170	162	155	158	162	172	182	192
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	151	151	151	153	155	155	156	157
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	207	190	174	169	164	163	163	162
		L	4	169	159	149	153	156	156	157	157
		L-INOX	4	146	144	143	143	144	140	136	132
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	200	187	174	169	164	161	158	155
		L	4	169	154	139	144	149	152	154	157
		L-INOX	4	146	139	133	135	137	135	133	132
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	174	152	131	125	119	121	123	126

Table 2. Performances - mechanical resistance

(t_{Ne}/t_{ni} = 0,5/0,5)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{Ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{Cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_C [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000 = 1,25$ $\phi 100000 = 1,70$							
	Shear strength f_{Cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	231	231	232	227	221	217	213	209
		L	4	217	219	220	208	195	203	211	219
		L-INOX	4	170	168	167	168	170	177	184	192
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	223	228	232	227	221	214	207	200
		L	4	217	211	205	196	186	197	208	219
		L-INOX	4	170	162	155	158	162	172	182	192
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	129	128	128	130	132	132	133	134
		L-INOX	4	133	119	106	117	129	120	111	103
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	207	190	174	169	164	163	163	162
		L	4	169	159	149	153	156	156	157	157
		L-INOX	4	146	144	143	143	144	140	136	132
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	200	187	174	169	164	161	158	155
		L	4	169	154	139	144	149	152	154	157
		L-INOX	4	146	139	133	135	137	135	133	132
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	148	130	112	106	101	103	105	107
		L-INOX	4	109	102	95	94	93	93	94	95
		F	4	113	111	109	103	98	102	106	109

Table 3. Performances - mechanical resistance
(t_{Ne}/t_{ni} = 0,5/0,6)

	Nominal thickness d_N [mm]			40	50	60	80	100	110	120	130
	Essential characteristics		AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_c [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	ϕ2000 = 1,25 ϕ100000 = 1,70							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	231	231	232	227	221	217	213	209
		L	4	217	219	220	208	195	203	211	219
		L-INOX	4	170	168	167	168	170	177	184	192
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	223	228	232	227	221	214	207	200
		L	4	217	211	205	196	186	197	208	219
		L-INOX	4	170	162	155	158	162	172	182	192
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	113	113	113	114	116	116	117	118
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	207	190	174	169	164	163	163	162
		L	4	169	159	149	153	156	156	157	157
		L-INOX	4	146	144	143	143	144	140	136	132
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	200	187	174	169	164	161	158	155
		L	4	169	154	139	144	149	152	154	157
		L-INOX	4	146	139	133	135	137	135	133	132
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	130	114	98	94	89	91	92	94
		F	4	113	111	109	103	98	102	106	109

Table 4. Performances - mechanical resistance

(t_{Ne}/t_{ni} = 0,5/0,7)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_c [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	ϕ2000 = 1,25 ϕ100000 = 1,70							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	231	231	232	227	221	217	213	209
		L	4	217	219	220	208	195	203	211	219
		L-INOX	4	170	168	167	168	170	177	184	192
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	223	228	232	227	221	214	207	200
		L	4	217	211	205	196	186	197	208	219
		L-INOX	4	170	162	155	158	162	172	182	192
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	101	101	101	103	104	104	105	105
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	207	190	174	169	164	163	163	162
		L	4	169	159	149	153	156	156	157	157
		L-INOX	4	146	144	143	143	144	140	136	132
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	200	187	174	169	164	161	158	155
		L	4	169	154	139	144	149	152	154	157
		L-INOX	4	146	139	133	135	137	135	133	132
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	117	102	88	84	80	81	83	84
		F	4	113	111	109	103	98	102	106	109

Table 5. Performances - mechanical resistance
(t_{Ne}/t_{ni} = 0,6/0,4)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_C [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	ϕ2000 = 1,25 ϕ100000 = 1,70							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	201	202	202	198	193	190	186	183
		L	4	189	191	192	181	170	177	184	191
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	195	199	202	198	193	187	181	175
		L	4	189	184	179	171	163	172	182	191
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	151	151	151	153	155	155	156	157
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	180	166	152	147	143	143	142	142
		L	4	147	139	130	133	136	137	137	137
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	175	163	152	147	143	141	138	135
		L	4	147	134	121	126	130	132	135	137
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	174	152	131	125	119	121	123	126

Table 6. Performances - mechanical resistance
(t_{Ne}/t_{ni} = 0,6/0,5)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_C [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	ϕ2000 = 1,25 ϕ100000 = 1,70							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	201	202	202	198	193	190	186	183
		L	4	189	191	192	181	170	177	184	191
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	195	199	202	198	193	187	181	175
		L	4	189	184	179	171	163	172	182	191
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	129	128	128	130	132	132	133	134
		L-INOX	4	133	119	106	117	129	120	111	103
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	180	166	152	147	143	143	142	142
		L	4	147	139	130	133	136	137	137	137
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	175	163	152	147	143	141	138	135
		L	4	147	134	121	126	130	132	135	137
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	148	130	112	106	101	103	105	107
		L-INOX	4	109	102	95	94	93	93	94	95
		F	4	113	111	109	103	98	102	106	109

Table 7. Performances - mechanical resistance

(t_{Ne}/t_{ni} = 0,6/0,6)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_c [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000 = 1,25$ $\phi 100000 = 1,70$							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	201	202	202	198	193	190	186	183
		L	4	189	191	192	181	170	177	184	191
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	195	199	202	198	193	187	181	175
		L	4	189	184	179	171	163	172	182	191
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	113	113	113	114	116	116	117	118
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	180	166	152	147	143	143	142	142
		L	4	147	139	130	133	136	137	137	137
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	175	163	152	147	143	141	138	135
		L	4	147	134	121	126	130	132	135	137
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	130	114	98	94	89	91	92	94
		F	4	113	111	109	103	98	102	106	109

Table 8. Performances - mechanical resistance

(t_{Ne}/t_{ni} = 0,6/0,7)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_c [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000 = 1,25$ $\phi 100000 = 1,70$							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	201	202	202	198	193	190	186	183
		L	4	189	191	192	181	170	177	184	191
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	195	199	202	198	193	187	181	175
		L	4	189	184	179	171	163	172	182	191
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	101	101	101	103	104	104	105	105
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	180	166	152	147	143	143	142	142
		L	4	147	139	130	133	136	137	137	137
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	175	163	152	147	143	141	138	135
		L	4	147	134	121	126	130	132	135	137
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	117	102	88	84	80	81	83	84
		F	4	113	111	109	103	98	102	106	109

Table 9. Performances - mechanical resistance
(t_{Ne}/t_{ni} = 0,7/0,4)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{Ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{Cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_C [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000$ = 1,25 $\phi 100000$ = 1,70							
	Shear strength f_{Cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	180	180	181	177	173	169	166	163
		L	4	169	170	172	162	152	158	165	171
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	174	177	181	177	173	167	162	156
		L	4	169	164	160	152	145	154	162	171
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	151	151	151	153	155	155	156	157
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	161	148	135	132	128	127	127	126
		L	4	131	124	116	119	122	122	122	122
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	156	146	135	132	128	126	123	121
		L	4	131	120	108	112	116	118	120	122
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	174	152	131	125	119	121	123	126

Table 10. Performances - mechanical resistance
(t_{Ne}/t_{ni} = 0,7/0,5)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{Ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{Cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_C [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000$ = 1,25 $\phi 100000$ = 1,70							
	Shear strength f_{Cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	180	180	181	177	173	169	166	163
		L	4	169	170	172	162	152	158	165	171
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	174	177	181	177	173	167	162	156
		L	4	169	164	160	152	145	154	162	171
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	129	128	128	130	132	132	133	134
		L-INOX	4	133	119	106	117	129	120	111	103
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	161	148	135	132	128	127	127	126
		L	4	131	124	116	119	122	122	122	122
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	156	146	135	132	128	126	123	121
		L	4	131	120	108	112	116	118	120	122
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	148	130	112	106	101	103	105	107
		L-INOX	4	109	102	95	94	93	93	94	95
		F	4	113	111	109	103	98	102	106	109

Table 11. Performances - mechanical resistance
(t_{Ne}/t_{ni} = 0,7/0,6)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_c [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000$ = 1,25 $\phi 100000$ = 1,70							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	180	180	181	177	173	169	166	163
		L	4	169	170	172	162	152	158	165	171
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	174	177	181	177	173	167	162	156
		L	4	169	164	160	152	145	154	162	171
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	113	113	113	114	116	116	117	118
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	161	148	135	132	128	127	127	126
		L	4	131	124	116	119	122	122	122	122
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	156	146	135	132	128	126	123	121
		L	4	131	120	108	112	116	118	120	122
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	130	114	98	94	89	91	92	94
		F	4	113	111	109	103	98	102	106	109

Table 12. Performances - mechanical resistance
(t_{Ne}/t_{ni} = 0,7/0,7)

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Mechanical resistance	Compressive strength σ_m [MPa]		4	0,13	0,14	0,15	0,15	0,15	0,14	0,14	0,14
	Tensile strength f_{ct} [MPa]		4	0,05	0,05	0,06	0,06	0,06	0,06	0,06	0,07
	Shear strength f_{cv} [MPa]		4	0,13	0,11	0,10	0,11	0,13	0,12	0,12	0,12
	Shear modulus G_c [MPa]		4	3,30	3,10	2,90	2,95	3,00	2,93	2,86	2,80
	Creep coefficient ϕt (ceilings)		4	$\phi 2000$ = 1,25 $\phi 100000$ = 1,70							
	Shear strength f_{cv} long-term [MPa] (ceilings)		4	0,05	0,04	0,04	0,04	0,05	0,05	0,04	0,04
	Wrinkling strength σ_w in span [MPa] positive	M16	4	180	180	181	177	173	169	166	163
		L	4	169	170	172	162	152	158	165	171
		F, 1L, 2L	4	191	179	167	173	180	194	208	223
	Wrinkling strength σ_w in span [MPa] positive, elevated temperature	M16	4	174	177	181	177	173	167	162	156
		L	4	169	164	160	152	145	154	162	171
		F, 1L, 2L	4	191	179	167	173	179	194	208	223
	Wrinkling strength σ_w in span [MPa] negative	L	4	101	101	101	103	104	104	105	105
		F	4	123	124	125	125	126	129	132	135
	Wrinkling strength σ_w at central support [MPa] negative	M16	4	161	148	135	132	128	127	127	126
		L	4	131	124	116	119	122	122	122	122
		F, 1L, 2L	4	145	137	128	140	152	144	136	128
	Wrinkling strength σ_w at central support [MPa] negative, elevated temperature	M16	4	156	146	135	132	128	126	123	121
		L	4	131	120	108	112	116	118	120	122
		F, 1L, 2L	4	145	137	128	140	151	144	136	128
	Wrinkling strength σ_w at central support [MPa] positive	L	4	117	102	88	84	80	81	83	84
		F	4	113	111	109	103	98	102	106	109

Table 13. Performances - fire, valid under the conditions specified in the classification reports

Nominal thickness d_N [mm]				40	50	60	80	100	110	120	130
Essential characteristics			AVCP	**Performances**							
Reaction to fire; classification	with standard gasket		1	B-s2,d0				B-s1,d0			
	with carbon gasket			NPD			B-s1,d0				NPD
Fire resistance, classification (walls) - does not apply to INOX stainless steel cladding				span [m]							
	Orientation - horizontal [Class]*	EI15		NPD	NPD	NPD	NPD	**3,0**	**4,0**	**4,0**	**7,5**
		EI20						NPD	**4,0**	**4,0**	**4,0**
		EI30							NPD	NPD	NPD
		EI45**									
		EI60									
		EI90									
		EI120									
		EI180									
		EI240									
	Orientation - vertical [Class]*	EI15	3	NPD	NPD	NPD	**3,0**	**3,0**	**3,0**	**4,0**	**4,0**
		EI20					NPD	NPD	NPD	**3,0**	**4,0**
		EI30								NPD	NPD
		EI45**									
		EI60									
		EI90									
		EI120									
		EI180									
		EI240									
				span [m]							
	Orientation - horizontal [Class]*	EW15		NPD	NPD	NPD	**4,0**	**7,5**	**7,5**	**7,5**	**7,5**
		EW20					**4,0**	**7,5**	**7,5**	**7,5**	**7,5**
		EW30					NPD	**7,5**	**7,5**	**7,5**	**7,5**
		EW45**						**7,5**	**3,0**	**6,0**	**7,5**
		EW60						NPD	NPD	NPD	**3,0**
		EW90									NPD
		EW120									
		EW180									
		EW240									
	Orientation - vertical [Class]*	EW15		NPD	NPD	NPD	**7,5**	**7,5**	**7,5**	**7,5**	**7,5**
		EW20					**7,5**	**7,5**	**7,5**	**7,5**	**7,5**
		EW30					**6,0**	**7,5**	**7,5**	**7,5**	**7,5**
		EW45**					NPD	NPD	**6,0**	**7,5**	**7,5**
		EW60							NPD	**3,0**	**3,0**
		EW90								NPD	NPD
		EW120									
		EW180									
		EW240									

* - direction of fire (i↔o) applies to external walls only

** - applies to partition walls only

Table 14. Performances - others

Nominal thickness d_N [mm]			40	50	60	80	100	110	120	130
Essential characteristics		AVCP	**Performances**							
Thermal transmittance	Thermal transmittance coefficient $U_{d,s}$ [W/(m^{2}K)]	4	0,64	0,51	0,39	0,29	0,22	0,20	0,19	0,17
	Thermal conductivity coefficient λ_D [W/(mK)]	4	0,025		0,024		0,022			
Flexural tensile strength (ceilings)		4	NPD							
Water permeability; classification		4	NPD							
Air permeability; value *n, C*		4	NPD							
Water vapour permeability; coeff. μ		4	Pass							
Airborne sound insulation; indicators R_w (C, C_{tr}) [dB]		4	NPD							
Sound absorption; rating α_w		4	NPD							
Durability	DUR1	4	Pass							
	Resistance to point loads and access loads (ceilings)	4	Pass							
Dangerous substances		3	NPD							