

FusRock® FDM Printing Material

Technical Data Sheet

Data / Revised: 01.2025 Version No: 4.1

FusFree[™] S-Multi

FusFree™ S-Multi 快速易剥离支撑材料。

FusFree™ S-Multi Quick-Remove Support Material

产品亮点

Smart Adhesion Technology

FusFree™ S-Multi 通过配方与工艺调节与主体材料具有适中的粘接强度,既确保主体材料可以在支撑面上成型,又可以在拆除支撑过程中轻松与主体材料支撑面分离。

FusFree™ S-Multi can provide a moderate bond strength to the body material through formulation and process modifications, which ensures that the body material can be molded to the support surface and can be easily separated from the support surface of the body material during removal of the support.

Quick Remove Technology

FusFree™ S-Multi 通过配方与工艺调节大幅降低了自身的层间粘接强度,可以在拆除过程中被轻松撕除。 FusFree™ S-Multi has dramatically reduced its own interlayer bond strength through formulation and process modifications, and can be easily teared apart during removal process.

ECO Friendly

FusFree™ S-Multi 使用过程无需使用水或溶剂,不产生水污染,安全环保。

The FusFree TM S-Multi does not require the use of water or solvents during the use process, does not produce water pollution, and is safe and environmentally friendly.

产品详情

Available

颜色 Color: 纯色 Natural/ 黑色 Black

线径 Diameter: 1.75mm

净重 Net Wet: 500g, 1kg, 2.5kg, 3kg



产品介绍

Product Description

FusFree™ S-Multi 快速易剥离支撑材料,通过调节与主体材料的支撑面粘接强度与 S-Multi 的自身粘接强度实现快速易剥离功能。S-Multi 快速易剥离支撑材料在拆除支撑过程中无需使用水或溶剂,不产生水污染,安全环保。FusFree™ S-Multi 可以应用于双喷头 FDM 打印机或二进一出 FDM 打印机。

FusFree[™] S-Multi Quick-Remove Support Material can achieve fast and easy peeling by adjusting the bonding strength to the support surface of the body material and the bonding strength of S-Multi itself. S-Multi Quick-Remove Support Material does not require the use of water or solvents during the removal of the support and does not produce water pollution, which is safe and environmentally friendly. FusFree[™] S-Multi can be used in dual printhead FDM printers or 2-in/1-out FDM printers.

FusFree™ S-Multi 快速易剥离支撑材料,适配以下 FusRock®工业级材料产品:

FusFree™ S-Multi Quick-Remove Support Material is compatible with the following FusRock® industrial grade material products.

本体材料		
Compatible Materials		
FusForce™ PET-GF, PET-CF	+++	
FusFlex™ TPU85A, 95A, 64D, 78D	++	
FusCoating™ NexABS-GF25	++	
FusCoating™ NexABS-CF20	++	
FusCoating™ NexASA-CF20	++	
FusCoating™ NexTPU-GF25	++	
FusFun™ ABS-HF	+	

物性表 (v1.2)

Material Properties

测试项目	测试方法	典型值
Test item	Test method	Typical value
密度 Density	ISO 1183	1.16 g/cm³
吸湿率	ISO 62:	0 / 9/
Water absorption	Method 1	0.4 %
熔点	ISO 11357	168°C
Melting Temperature		
熔融指数	260°C, 2.16kg	5.1
Melt index	200 G, 2.10kg	J.1

建议打印参数

Recommended printing conditions

喷头温度	260-280°C	
Nozzle Temperature		
建议喷嘴大小	0.4-1.0mm	
Recommended Nozzle Diameter		
建议底板材质	涂抹 PVP 固体胶	
Recommended build surface treatment	Coating with PVP glue	
底板温度	70-90°C	
Build plate temperature		
Raft 间距	0 mm	
Raft separation distance		
建议支撑密度	15%-20%	
Recommended Support Infill Ratio		
建议致密层厚度	3-5	
Recommended Dense Support Layers	3-3	
支撑 Z 方向上/下表面距离	0	
Vertical Offset Top/Down Layers	Ü	
支撑 X/Y 方向距离	0.3-0.6 mm	
Horizontal offset		
支撑边框圏数	0-1	
Support infill outlines		
冷却风扇	关闭	
Cooling fan speed	OFF	
打印速度	30-120 mm/s	
Print speed	30-120 11111/3	
回抽距离	0.6-2 mm	
Retraction distance		



回抽速度 Retraction speed	1800-3600 mm/min
	FusFun™ ABS-HF
	FusFlex™ TPU85A-HF
	FusFlex™ TPU95A-HF
适配本体材料	FusForce™ PET-GF
Compatible materials	FusForce™ PET-CF
	FusCoating™ NexABS-GF25
	FusCoating™ NexABS-CF20
	FusCoating™ NexASA-CF20

其他建议:

Additional Suggestions:


- 1. FusFree™ S-Multi 非常容易吸收环境内的水分,吸湿后打印会出现拉丝,挤出有气泡,打印表面粗糙等现象,降低打印质量。建议您打开 FusFree™ S-Multi 真空铝箔袋包装后立即将线材放入干燥盒内(湿度控制在 15%以下)进行打印。不用的线材请放回原包装铝箔袋内密封保存。FusFree™ S-Multi very easy to absorb moisture within the environment, and printing after absorbing moisture will result ozzing, extruding with bubbles and rough surface appearance, thus reducing print quality. It is recommended that put the filament into a dry box (humidity below 15%) immediately after opening the FusFree™ S-Multi vacuum foil bag for printing. Please put the unused filament back into the original aluminum foil bag for sealed storage.
- 2. 材料受潮后会出现打印拉丝增多,挤出有气泡,打印表面质量粗糙等现象。请将线材放入 80-100℃ 烘箱内干燥 4-6h,即可恢复 FusFree™ S-Multi 的打印质量。
 After the material is damp, there will be more printing ozzing, bubbles extruded and rough printing surface. Please dry the filament in an oven at 80-100℃ for 4-6h to restore the printing quality of FusFree™ S-Multi.
- 3. 建议选用 Phaetus 硬化钢及以上等级喷嘴,可以有效提高打印质量,建议加热块厚度不小于 12mm。
 - It is recommended to use hardened steel and above grade nozzles made by Phaetus, which can effectively improve the print quality. Besides, it is recommended that the thickness of the heating block is longer 12mm.
- 4. 在双喷头打印模式下,待机喷头内的材料会因为长时间加热而老化,在打印喷头切换前需要将喷头内已老化的材料挤出干净,所以必需使用切片软件内的隔离墙(Wipe wall)或擦除塔(Wipe tower)功能。
- In dual-extruder printing mode, the material in the standby nozzle will deteriorate due to prolonged heating, and the deteriorated material needs to be squeezed out before the print nozzle is switched, so it is necessary to use the Wipe wall or Wipe tower function in the slicing software.
- 5. 打印完成后可以先对打印件进行退火处理,然后进行拆除 FusFree™ S-Multi 步骤。在退火过程中 FusFree™ S-Multi 可以起到支撑本体材料的作用,减少主体材料的尺寸变形,提高主体材料的机械 性能。退火条件:按主体材料要求进行设置。
- 5. After the printing is completed, the printed part can be annealed and then the FusFree™ S-Multi removal step can be performed. During the annealing process, FusFree™ S-Multi can play the



role of supporting the body material, reducing the dimensional deformation of the body material and improving the mechanical properties of the body material. Annealing conditions: set according to the requirements of the body material.

挤出压力与打印速度测试

Extrusion Force vs Print Speed Test



测试参数: 12mm 长度铜制加热块,BMG 挤出机,Phaetus 硬化钢喷头,喷嘴大小 0.4mm,层高 0.2mm。
Test parameters: 12mm length brass heat block, BMG extruder, Phaetus Hardened Steel Nozzle, Nozzle size 0.4mm, Layer Height 0.2mm.